

BUREAU OF ANALYSED SAMPLES LTD

Certified Reference Materials



CATALOGUE NO. 922a

SEPTEMBER 2024



4004

CERTIFICATE GB94/3993

		<u>CONTENTS</u>		
	Page			Page
INTRODUCTION	2	SPECTROSCOPIC STANDARD CERTIFIED		
GENERAL INFORMATION	2	REFERENCE MATERIALS		
CO-OPERATING ANALYSTS AND LABORATORIES	3	Plain Carbon Steels		17
BRITISH CHEMICAL STANDARD AND EURONORM		Carbon Steel Residual Series		17
CERTIFIED REFERENCE MATERIALS		High Purity Irons		18
High Purity Irons	7	Low Alloy Steels		18
Unalloyed Steels	7/8	Highly Alloyed Steels		19
High-Speed Steels	8	Austenitic Stainless Steels		19
Low Alloy Steels	9	Low Alloy Cast Steel		19
Highly Alloyed Steels	10	Plain Carbon Cast Steels		19
Special Alloys	11	Ferritic Stainless Steels		20
Cast Irons	11	High-Speed Steels		20
Blast Furnace Iron	11	High Manganese Cast Steels		20
Ferro-Alloys	11	Cast Irons		21
Aluminium Base Alloys	12	Nickel Base Alloys		21
Magnesium Base Alloys	12	SPECTROSCOPIC REFERENCE MATERIALS		
Copper Base Alloys	12	Low Alloy Cast Irons		22
Lead and Tin Base Alloys	12	High Chromium Irons		22
Nickel Base Alloys	13	Nickel Chromium Irons		22
Titanium Base Alloys	13	Austenitic (Ni-Resist) Irons		22
Chromium Metal	13	Silicon Molybdenum Cast Irons		22
Chrome Ore	13	Phosphorus Deoxidised Coppers		23
Cements	13	Main Elements in Brasses		23
Fluorspar & Bauxites	13	Admiralty & Naval Brasses		23
Iron Ores & Furnace Dust	14	Aluminium Brasses		23
Manganese Ores	14	Cartridge Brasses		23
Copper Concentrate	14	Leaded Bronzes		23
Slags	14	Aluminium Bronzes		23
Tungsten Carbide & Silicon Carbide Refractories	14	Phosphor Bronzes		23
Ceramic Materials & Minerals	15	Cupro Nickel		23
Glass Sands	15	Leaded Gunmetals		23
Soda Ash	16	Lead Base Battery Alloys		24
BRITISH CHEMICAL STANDARD REFERENCE MATERIALS		SPECTROSCOPIC SETTING-UP SAMPLES		
High Purity Metals	16	Carbon and Low Alloy Steels		24
Ceramic Materials	16	Highly Alloyed & Stainless Steels		24
Benzoic Acid	16	Cast Irons		24
		NUMERICAL INDEX (INCLUDING CERTIFICATION DATES)		25
		PURCHASE PROCEDURE		29

BUREAU OF ANALYSED SAMPLES LTD., NEWHAM HALL, NEWBY, MIDDLESBROUGH, ENGLAND, TS8 9EA.

Telephone: National:
 International:
 Website: www.basrid.co.uk

Middlesbrough (01642) 300500
 +44 1642 300500
 Email: enquiries@basrid.co.uk

INTRODUCTION

The Certified Reference Materials have been prepared under rigorous laboratory conditions and are issued by Bureau of Analysed Samples Ltd. under the auspices of an Honorary Advisory Committee and a body of approximately 150 Co-operating Analysts representing Independent Laboratories and Manufacturers and Users of the materials concerned.

(a) CERTIFIED REFERENCE MATERIALS (CRMs)

British Chemical Standard Certified Reference Materials (BCS-CRMs) are normally analysed by at least five Analysts, and a certificate showing the individual mean values obtained by each Analyst and a summary of the methods used is supplied with each sample. Certificates issued since 1984 also give the standard deviation of the intralaboratory means, and those issued since 1994 express the level of confidence of the certified value as the 95% half width confidence interval.

EURONORM Certified Reference Materials (ECRMs) were prepared under the auspices of the European Committee for Iron and Steel Standardization (ECISS). Each one is issued with a certificate giving the names of the participating laboratories, the mean values obtained by each laboratory for each element and a statistical evaluation of the laboratory means. The certificate also includes a summary of the methods of analysis used. Before publication each certificate has been approved by the Producing Organisations, namely Bureau of Analysed Samples Ltd. (BAS) in the UK, Institut de Recherches de la Siderurgie Française (IRSID) now ArcelorMittal Maizières Research (AMMZ) / Centre Technique des Industries de la Fonderie (CTIF) in France, Stahlinstitut VDEh (VDEh), BAM Bundesanstalt für Materialforschung und prüfung and Max-Planck-Institut für Eisenforschung (MPI) in Germany and the Nordic CRM Working Group (NCRMWG) in the Nordic countries. Although BAS is no longer part of the ECRM Producers Group, there are still over 50 BAS ECRMs which will be available until their exhaustion, when they will be replaced by BCS-CRMs and/or SS-CRMs.

There are also some existing BCS-CRMs which have been accepted as interim ECRMs after examination by laboratories in the EU. These are indicated with an ECRM number alongside the existing BCS-CRM number.

Bureau of Analysed Samples Ltd. act as UK distributors for ECRMs prepared by AMMZ/IRSID/CTIF in France, BAM in Germany and Jernkontoret in Sweden, and details of these samples, most of which are held in UK stock, are given in a separate BAS 'Outside Source' Reference Materials Catalogue, copies of which will be supplied on request. Further information regarding the preparation, certification and supply of ECRMs, and the use of the statistical information given on their certificates is given in Technical Reports **CEN/TR 10317:2014** and **CEN/TR 10350:2013** which are available in the UK from the BSI, 389 Chiswick High Road, London W4 4AL.

All BCS-CRM and ECRM samples are supplied in the finely divided form and many of them are also available in disc form for optical emission and X-ray fluorescence spectrometry.

Spectroscopic Standard Certified Reference Materials (SS-CRMs) have been specially prepared to provide samples of uniform composition in a form suitable for use with optical emission and X-ray fluorescence spectrometers. Each sample has been analysed by at least five laboratories, and a certificate showing the individual mean values obtained by each laboratory and a summary of the methods used is supplied with each sample or set of samples.

Steel samples are usually in the form of discs cut from round bar. Cast iron samples, which are prepared in accordance with specifications devised by the former British Cast Iron Research Association (BCIRA), are in the form of chill cast rectangular blocks.

(b) REFERENCE MATERIALS (RMs)

British Chemical Standard Reference Materials (BCS-RMs) and Spectroscopic Reference Materials, e.g. high purity metals and ceramic materials (p.16), low alloy cast irons, high chromium irons, nickel chromium irons and austenitic (Ni-resist) irons (p. 22) and copper base alloys (p. 23) are normally analysed by only two laboratories and are not given certified status.

(c) SPECTROSCOPIC SETTING-UP SAMPLES (SUS)

These Setting-up Samples (SUS) have been specially prepared to meet the day to day setting-up requirements of laboratories using direct reading spectrometers for production control analysis. Their use will conserve supplies of Spectroscopic Standard CRMs for calibration purposes only and will relieve spectrographers of the problem of finding suitable samples within their works for their daily setting-up requirements.

The steel samples are in the form of round bar. The cast iron samples, prepared in accordance with specifications devised by the former British Cast Iron Research Association (BCIRA), are in the form of chill cast rectangular blocks.

GENERAL INFORMATION

Our website, at www.basrid.co.uk, is continually being improved and now includes a page of downloadable certificates for all currently available BAS products.

Every endeavour is made to maintain a continuous supply of all samples in this catalogue by completing the preparation of an appropriate replacement by the time each sample becomes exhausted. When orders are received for obsolete samples the relevant replacements will normally be supplied. If for any reason such a sample is not acceptable, full credit will be allowed if it is returned carriage paid provided that the seal on the carton containing finely divided samples is unbroken.

Information regarding new samples in course of preparation will be supplied on request. When these are available for distribution a notice to this effect will be made on our website.

QUALITY ASSURANCE

Bureau of Analysed Samples Ltd. is very pleased to advise that in November 1994 its Quality System was formally approved and recognised by the award of a Certificate of Registration to the Quality Standard BS EN ISO 9002:1994 for the production and supply of CRMs, RMs and SUS. This certificate has now been revalidated to the new Standard BS EN ISO 9001:2015. Furthermore, BAS was accredited, in June 2006, to the International Guide, **ISO Guide 34** and the accreditation has since been updated to the full Standard **ISO 17034:2016**.

BUREAU OF ANALYSED SAMPLES LTD.

REG. No. 307549 (ENGLAND)

DIRECTORS

R.P. MEERES, *BA (Oxon), MRSC.*, (Managing Director)

G.C. FLINTOFT, *ACMA, CGMA* (Company Secretary)

Mrs J.C. MEERES

M.S. TAYLOR, *PhD, CChem, MRSC*

HONORARY ADVISORY COMMITTEE

P. BLUNDELL, *ALS Inspection UK, Prescott*

B. MARKHAM, *British Steel, Scunthorpe*

R. JOWITT, *ex Tata, Teesside Laboratories, Middlesbrough*

P. RUGG, *ex Liberty Speciality Steels, Stocksbridge*

P. J. SCRIMSHIRE, *BSc, ex IncoTest, Hereford*

D. SHAW, *Lucideon (formerly Ceram Research Ltd.), Stoke-on-Trent*

CO-OPERATING ANALYSTS AND LABORATORIES

Analysts and laboratories participating in the analysis of British Chemical Standard and Spectroscopic Standard Certified Reference Materials and EURONORM-CRMs prepared by Bureau of Analysed Samples Ltd.

UK INDEPENDENT ANALYSTS

ALS INSPECTION UK (per **P. Blundell**) Prescott

AWE PLC UK (per **T. Shaw**) Reading

BASE METAL CONCENTRATES ANALYSIS LTD (per **J. Tibbins & Mrs L. Bouacha**)..... St. Helens

BRITISH GEOLOGICAL SURVEY (per **C. Milne**) Nottingham

CERAM UK ANALYTICAL (per **Ms. S. Atherton**) Leeds

ELEMENT MATERIALS TESTING SHEFFIELD Ltd. (per **M. Maloney**) Sheffield

ELEMENT TEESSIDE (per **R. N. Coffey, Mrs E. Stowell & Miss B. Thomas**) Middlesbrough

GLASS TECHNOLOGY SERVICES LTD. (per **D. Capon**) Sheffield

INSPECTORATE INTERNATIONAL LTD. (per **K. Blaxall & Ms C. Hargreaves**) Witham

KEIGHLEY LABORATORIES LTD. (per **G. Woodward & T. D. Varley, BSc**) Keighley

A H KNIGHT INTERNATIONAL LTD. (per **N. Hampson**
& **G.P. DeRuiter, CChem, MRSC**) St. Helens

LUCIDEON (per **D. Shaw**) Stoke-on-Trent

OPEN UNIVERSITY (per **P.C. Webb**) Milton Keynes

PATTINSON & STEAD (2005) Ltd. (per **M.J. Atkinson**) Middlesbrough

RIDSDALE & CO. LTD. (per **S.M. Malik**) Middlesbrough

SHEFFIELD ASSAY OFFICE (per **Mrs J. Smethurst & Mrs F. Hudson**) Sheffield

SHEFFIELD HALLAM UNIVERSITY (per **A. Bell, PhD**) Sheffield

ALEX STEWART INTERNATIONAL CORP. (per **T. Roche, CSci, CChem, FRSC, Eurchem**) Aintree

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

UK MANUFACTURERS and USERS

ALCOA HOWMET EXETER ALLOY LTD. (per E.J. Farley & D. Cheetham)	Exeter	LIBERTY SPECIALITY STEELS (per W. Furness & M. Tunnicliffe)	Stocksbridge
AMG ANALYTICAL SERVICES LTD. (per P. Hurditch & P. Cooper)	Rotherham	MALVERN PANALYTICAL LTD. (per N. Eatherington)	Nottingham
ARDAGH GLASS (per Ms T. Marsden)	Knottingley	METALS TECHNOLOGY (TESTING) LTD. (per P.M. Brammer)	Sheffield
ATI SPECIALITY MATERIALS LTD. (per M. Blackwell & M. Webster)	Sheffield	NICHOLLS COLTON ANALYTICAL. (per J. Gane)	Leicester
BRITISH STEEL (per B. Markham)	Scunthorpe	NSG EUROPEAN TECHNICAL CENTRE (per J. Clark & Ms J. Barton)	Lathom
CALUMITE LTD. (per N. Johnson, MEng, PhD)	Scunthorpe	ST. GOBAIN GLASS UK LTD. (per Ms. F. Bazzali)	Eggborough
CLIMAX MOLYBDENUM (UK) LTD. (per K. Sutton)	Stowmarket	STL MIDLANDS (per Ms. C. Peacock)	Coventry
FIRTH RIXSON PLC (per Ms. J. Parker)	Glossop	TATA CHEMICALS EUROPE (per P. Dawson)	Northwich
INCOTEST (per A. Zielinski)	Hereford	TATA STEEL STRIP PRODUCTS (per A. Dawe & G. R. Davies PhD)	Port Talbot
JAMES HUTTON INSTITUTE (per A. Midwood & G. Newman)	Craigiebukler	TATA STEEL TECHNICAL (per P. Collins)	Rotherham

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

Overseas Laboratories Participating in the Analysis of BAS Certified Reference Materials

AUSTRALIA

CSIRO MINERALS Glen Osmond
STANDARD & REFERENCE LABORATORIES Malaga
WESTERN AUSTRALIAN SPECIALITY ALLOYS Canning Vale

AUSTRIA

VOESTALPINE BÖHLER EDELSTAHL GmbH & CO. KG Kapfenberg
VOESTALPINE STAHL GmbH Linz

BELGIUM

AGC FLAT GLASS EUROPE Jumet
CTP Tournai
INISMa - CRIBC Mons
SIBELCO Dessel

BRAZIL

MINERACAO MARACA IND e COM S/A Golas

CANADA

CLAISSE (CORPORATION SCIENTIFIQUE CLAISSE) Quebec
VALE INCO LTD Copper Cliff
VALE INCO LTD Thompson
VALE INCO LTD Port Colborne
VALE INCO TECHNICAL SERVICES LTD Mississauga

CHILE

ALFRED H. KNIGHT CHILE LTDA Las Condes

CHINA

CERAM – HUAXIA CERAMIC TESTING CENTER Guangdong Province
INSPECTORATE (SHANGHAI) LTD Shanghai

CZECH REPUBLIC

LITHEA s.r.o. Brno
TUV NORD Brno

ESTONIA

BUREAU VERITAS Harjumaa

FINLAND

NAREMA OY Närpes
RUUKKI-RAUTARUUKKI OY Raahe

FRANCE

ACIERIES DES ANCIZES - AUBERT ET DUVAL Les Ancizes
ARCELORMITTAL RESEARCH - GROUPE ARCELOR (IRSID) Maizières-les-Metz
ARCELORMITTAL ATLANTIQUE ET LORRAINE Dunkerque
ARCELORMITTAL ATLANTIQUE ET LORRAINE Florange
CORNING SAS Avon
CRPG Nancy
CTIF Sèvres
DCNS La Montagne
SHIVA TECHNOLOGIES EUROPE Tournepuile
ST GOBAIN ISOVER Isover
ST GOBAIN RECHERCHE Aubervilliers

GERMANY

AG DER DILLINGER HÜTTENWERKE Dillingen/Saar
BAM BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG Berlin
W.C. HERAEUS GmbH Hanau
IFW DRESDEN Dresden
OUTOKUMPU VDM Werdohl
SAARSTAHL AG Völklingen-Saar
SALZGITTER FLACHSTAHL GmbH Salzgitter
ST GOBAIN DEUTSCHLAND Herzogenrath
SCHOTT GLAS Mainz
STAHLINSTITUT VDEh Düsseldorf
H.C. STARCK GmbH & CO. KG, WERK GOSLAR Goslar
THYSSENKRUPP EUROPE STEEL AG Duisberg
WESER-METALL GmbH Nordenham

GHANA

GHANA MANGANESE CO. LTD Nsuta Wassa

GREECE

AGRICULTURAL RESEARCH & ANALYTICAL LABORATORIES Athens

HUNGARY

DUNAFERR LABOR NONPROFIT LTD Dunaujváros
METALCONTROL KFT Miskolc

CO-OPERATING ANALYSTS AND LABORATORIES (cont.)

Overseas Laboratories Participating in the Analysis of BAS Certified Reference Materials (cont.)

INDIA

INSPECTORATE GRIFFITH INDIA PVT LTD Bhubaneswar
 INSPECTORATE GRIFFITH INDIA PVT LTD Odisha
 INSPECTORATE GRIFFITH INDIA PVT LTD Visakhapatnam
 MICROLAB Chennai
 MINERAL & METALLURGICAL LABS Bangalore
 RAGHAVENDRA SPECTRO METALLURGICAL LABORATORY Bangalore
 TATA STEEL LIMITED Jamshedpur

ITALY

COGNE ACCIAI SPECIALI SPA Aosta
 STAZIONE SPERIMENTALE DEL VETRO Murano

JAPAN

ASAHI GLASS CO. LTD Yokohama
 NIPPON SHEET GLASS CO. LTD Itami

LUXEMBOURG

LUXCONTROL S.A. Esch sur Alzette

MACEDONIA

RZ TEHNICKA KONTROLA AD Skopje

MALAYSIA

CERAMIC RESEARCH CO. SDN BHD Selangor

MEXICO

ALFRED H. KNIGHT DE MEXICO SA de CV Colima

THE NETHERLANDS

LABORATORY SERVICES INTERNATIONAL BV Rotterdam
 LMA CV Raamsdonksveer
 PHILIPS INNOVATION SERVICES Eindhoven
 SGS NEDERLAND BV Spijkenisse
 TATA STEEL IJmuiden

PERU

ALFRED H. KNIGHT DEL PERU Lima
 INSPECTORATE SERVICES PERU SAC Callao

POLAND

ARCELORMITTAL POLAND SA Dabrowa
 IMZ Gliwice

ROMANIA

ARCELORMITTAL GALATI SA Galati

SOUTH AFRICA

BUREAU VERITAS INSPECTORATE LABS Rustenburg
 MINTEK Randburg

SPAIN

ACERINOX Europa S.A.U. Cadiz

SWEDEN

ALLEIMA TUBE AB Sandviken
 ALS ENVIRONMENTAL AB Lulea
 CHEMAL Hofors
 DEGERFORS LABORATORY Degerfors
 GUSTAVSSON CONSULTING Stockholm
 HÖGANÄS SWEDEN AB Höganäs
 JERNKONTORET Stockholm
 KANTHAL AB Hallstahammar
 LUOSSAVAARA KIIRUNAVAARA AB (LKAB) Kiruna
 LUOSSAVAARA KIIRUNAVAARA AB (LKAB) Malmberget
 OUTOKUMPU STAINLESS AB Avesta
 OVAKO – HOFORS AB Hofors
 RISE INSTITUTES INVENTIA Vaxjo
 SSAB EMEA OXELOSUND AB Oxelosund
 UPPSALA UNIVERSITY Uppsala

THAILAND

DEPARTMENT OF SCIENCE SERVICE, MINISTRY OF SCIENCE & TECHNOLOGY Bangkok
 NATIONAL METAL & MATERIALS TECHNOLOGY CENTER Pathumtani

TURKEY

TURKIYE SIS EVE CAM FABRIKALARI A.S. İş Kuleleri Kulei

USA

ALCAN PACKAGING, INC Millville
 ALFRED H. KNIGHT NORTH AMERICA LTD Spartanburg
 ATI ALLEGHENY LUDLUM Brackenridge
 ATI SPECIALITY MATERIALS Monroe
 CARPENTER TECHNOLOGIES Reading
 GUARDIAN INDUSTRIES CORPORATION Michigan
 LABORATORY TESTING, INC Hatfield
 NSL ANALYTICAL SERVICES, INC Cleveland
 SMC HUNTINGDON ALLOYS Huntingdon

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - High Purity Irons and Unalloyed Steels

The figures are listed primarily as a guide to purchasers. In some cases provisional figures are given which may differ slightly from those given on the Certificate. **Always consult the Certificate issued with the sample to obtain the accurate analysis.**

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

High Purity Irons (Finely divided material - units of 100g; 097-2 also available as 38mm dia. x 30 or 25mm discs - see page 18)

ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	N	Nb
088-2	High Purity Iron	0.0006	0.0052	0.0809	0.0048	0.0070	0.0244	<i>0.0025</i>	0.0275	<i>0.0005</i>	...	...	0.0061	0.0163	<i>0.001</i>	...
097-2(C)	High Purity Iron	<i><0.002</i>	0.00285	0.0120	0.00538	0.00181	0.0213	0.00370	0.0241	<i><0.002</i>	0.00281	0.00012	0.0139	0.00793	0.00294	<i>0.0011</i>

ECRM No.	Description	Pb	Sn	Ti	V	W	Zr	Bi	Ca	Ga	Mg	O	Sb	Ta	Zn
088-2	High Purity Iron (cont.)	...	...	...	0.00029	...	...	...	0.00072	...	...	...	...	...	...
097-2(C)	High Purity Iron (cont.)	<i><0.001</i>	0.00043	<i>0.0008</i>	0.00011	0.00386	<i><0.002</i>	<i><0.0002</i>	<i><0.001</i>	<i>0.0003</i>	<i><0.0005</i>	<i>0.005</i>	0.00012	0.00015	0.00014

ECRM 097-2(C) also has the additional information: Ag: *<0.0001%*, Al(sol.): *<0.0004% & 0.0010%*, Cd: *<0.0001%*, Ge: *0.00043% & 0.00066%*, Se: *<0.0001%*, Te: *<0.0001%*.

Unalloyed Steels (Finely divided material - units of 100g; 111/1, 115 and 116 also available as 44mm dia. x 19mm discs/055-2, 057-2, 058-2, 059-2, 084-1, 085-1, 086-1, 087-1 and 090-1 also available as 38mm dia. x 30 or 25mm discs/056-2 also available as 44mm dia. x 30 or 25mm discs - see page 17)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	As	Co	Cu	N	Nb	Pb	Sn	Ti	V	Sb	Ca	Zn
111	...	Low Carbon Steel	0.0258	0.0253	0.155	0.0033	0.0054	0.0197	0.0008	0.0387	...	0.0348	0.0017	0.0144	0.0171	0.0034	<i>0.0005</i>	<i><0.001</i>	0.0015	0.0004	0.0009	<i><0.001</i>	<i><0.0005</i>	...
111/1	...	Low Carbon Steel	0.0070	0.0039	0.1623	0.0045	0.0049	0.0055	0.0005	0.0161	...	<i><0.002</i>	0.0011	0.0053	0.0089	0.0025	...	...	0.0006	0.0004	0.0002	...	...	...
115	...	Calcium Treated Steel	0.6224	0.2078	0.682	0.0123	0.00093	0.0198	<i>0.003</i>	0.0196	...	0.0527	...	<i>0.006</i>	<i>0.009</i>	0.0067	...	<i>0.0002</i>	<i>0.002</i>	0.0027	<i>0.001</i>	...	0.0058	<i>0.0006</i>
116	...	Calcium Treated Steel	0.617	0.201	0.6756	0.0092	0.00176	0.0141	<i><0.001</i>	0.0155	...	0.0587	...	...	<i>0.014</i>	0.0069	...	0.00012	<i>0.005</i>	0.00171	...	...	0.0036	...
117	...	Nb/Ti Interstitial Free Steel	0.0015	0.00286	0.1139	0.0093	0.0061	0.0196	0.00207	0.0196	...	0.0283	0.00175	0.0065	0.0150	0.00148	0.0186	0.000069	0.00152	0.0174	0.00104	...	...	...
161/4	...	0.8% Carbon Steel	0.817	0.202	0.504	0.0105	0.0096	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
232/2	051-1	0.1% Sulphur Steel	0.181	<i>0.11</i>	1.18	<i>0.025</i>	0.126	<i>0.05</i>	...	<i>0.14</i>	...	...	...	...	<i>0.15</i>	...	...	...	...	...	...	...	...	...
237/2	060-1	0.1% Carbon Steel	0.122	<i>0.17</i>	0.45	<i>0.024</i>	<i>0.031</i>	<i>0.028</i>	<i><0.005</i>	<i>0.039</i>	...	<i>0.004</i>	...	...	<i>0.060</i>	0.004	...	...	<i>0.005</i>	...	...	...	...	...
238/2	061-1	0.2% Carbon Steel	0.21	0.12	<i>0.61</i>	<i>0.019</i>	<i>0.034</i>	...	...	<i>0.21</i>	...	...	...	...	<i>0.10</i>	...	...	...	...	...	...	...	...	...
270	054-1	0.09% Phosphorus Steel	0.22	<i>0.05</i>	<i>0.88</i>	0.092	<i>0.11</i>	<i>0.17</i>	<i>0.02</i>	<i>0.14</i>	...	...	<i>0.03</i>	...	<i>0.21</i>	...	...	...	...	<i><0.01</i>	...	...	...	...
...	055-2(C)	0.5% Carbon Steel	0.5199	0.3094	0.687	0.0102	0.0205	0.3127	0.0960	0.3121	...	<i><0.01</i>	0.0187	0.0257	0.2089	0.01069	<i><0.0005</i>	<i><0.001</i>	0.0162	0.00104	0.00245	0.00376	<i><0.005</i>	<i>0.0011</i>
...	056-2(C)	0.8% Carbon Steel	0.8181	0.2006	0.5073	0.0103	0.0093	0.0146	<i>0.0015</i>	0.0218	0.00024	<i><0.001</i>	...	<i>0.0035</i>	0.0129	<i>0.0045</i>	...	...	...	...	...	...	...	...
...	057-2(C)	0.05% Carbon Steel	0.0507	<i>0.003</i>	0.246	0.0120	0.0127	0.0114	...	0.0096	<i>0.055</i>	0.059	...	...	0.0146	0.00230	...	...	...	...	...	...	...	...
...	058-2(C)	0.15% Sulphur Steel	0.424	0.1080	1.186	0.0098	0.1712	0.1211	0.0589	0.199	...	...	0.0095	...	0.261	0.0107	...	...	...	...	...	...	...	...
...	059-2(C)	0.7% Carbon Steel	0.721	0.188	0.495	0.0046	0.0084	0.0090	0.0018	0.0198	0.00020	0.00045	...	...	0.0074	0.0051	...	...	...	...	...	...	...	...
...	064-1(C)	Nb/Ti Interstitial Free Steel	0.0026	0.0065	0.1641	0.0091	0.0104	0.0184	0.00077	0.0115	0.0302	0.0330	0.0036	0.0027	0.0077	0.0026	0.0146	0.00018	0.00051	0.0189	0.00015	...	...	...
...	084-1(C)	0.4% Carbon Steel	0.391	0.265	0.860	0.018	0.029	...	0.033	0.154	...	...	...	...	0.267	...	...	...	0.023	...	...	...	...	...
...	085-1(C)	0.3% Sulphur Steel	0.067	0.008	0.977	0.062	0.336	...	...	...	...	...	...	0.019	0.291	...	...	0.0010	...	...	0.0021	0.0073	...	0.0025
...	086-1(C)	0.3% Carbon Steel	0.297	0.206	0.879	0.0238	0.0371	0.150	...	0.168	...	...	0.0230	...	0.320	...	...	...	0.0263	...	...	...	...	...
...	087-1(C)	0.15% Carbon Steel	0.1740	0.2631	0.6711	0.0103	0.0461	0.0781	0.0206	0.1177	...	...	0.0243	0.0148	0.1707	...	...	...	0.0171	...	...	0.0046	...	...
...	090-1(C)	1% Carbon Steel	1.054	0.281	0.226	0.0128	0.0095	0.121	0.0089	0.053	...	...	...	...	...	0.0146	0.00043	0.00239	...	<i><0.0001</i>	0.204	0.00090	...	0.00209
...	091-1	0.5% Carbon Steel	0.518	...	...	...	...	0.312	0.098	0.310	...	...	...	...	...	0.0111	...	...	...	...	...	...	...	...
...	096-2(C)	Low S, Ca-Treated Steel	0.1050	0.262	1.320	0.0128	0.0016	0.0243	0.0020	0.0253	...	0.0460	...	...	0.0170	...	0.0252	...	...	...	...	...	0.0020	...

Unalloyed Steels (continued)

BCS-CRM No.	ECRM No.	Description	B	Bi	Cd	Ga	Hg	Se	Te	W	Zr
...	055-2(C)	0.5% Carbon Steel (cont.)	<i>0.0003</i>	<i><0.005</i>	...	...	...	...	...	0.0166	<i><0.005</i>
...	090-1(C)	1% Carbon Steel (cont.)	...	<i><0.00002</i>	<i><0.00002</i>	0.00228	<i><0.00001</i>	<i><0.0002</i>	<i><0.0002</i>	...	...

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Unalloyed Steels and High Speed Tool Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steels (continued) (Finely divided material - units of 100g; 431/2-435/2 and 456/3-460/2, also available as discs - see page 17)

BCS-CRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Sb
431/2	Plain Carbon Steels	0.0249	0.015	0.902	0.121	0.0065	0.049	<i>0.004</i>	0.040	...	<i>0.01</i>	<i>0.005</i>	...	<i>0.006</i>	<i>0.015</i>	0.0052	0.0040	...	<i><0.001</i>	<i>0.005</i>	<i>0.003</i>	<i>0.004</i>	...	...
432/2		0.0065	0.0822	0.712	0.0171	0.036	0.0166	<i>0.002</i>	0.0196	...	<i><0.002</i>	...	...	<i>0.006</i>	<i>0.015</i>	0.0066	0.0174	...	...	...	<i><0.001</i>	<i>0.003</i>	...	...
433/2		0.096	0.0071	1.188	0.011	0.0083	0.0262	<i>0.004</i>	0.037	...	...	...	...	<i>0.006</i>	<i>0.025</i>	...	0.0590	...	...	...	<i>0.001</i>	<i>0.003</i>	...	...
434/2		0.275	0.510	1.546	0.0611	0.0141	0.238	<i>0.014</i>	0.037	...	...	...	...	<i>0.006</i>	<i>0.025</i>	0.0104	0.038	...	...	...	<i>0.04</i>	<i>0.04</i>	...	...
435/2		0.489	0.328	0.390	0.0373	0.0424	0.184	<i>0.018</i>	0.133	...	...	...	...	0.0116	<i>0.05</i>	...	0.134	...	...	...	<i>0.005</i>	<i>0.015</i>	...	...
452/1	Carbon Steel Residual Series (Group A)	0.323	0.055	1.30	0.035	0.017	0.067	0.054	0.19	...	...	0.015	...	...	0.22	...	...	<i>0.0002</i>	0.094	0.031	...	0.054	...	...
453/1		0.160	0.34	1.38	0.044	0.026	0.26	0.081	0.11	...	...	0.052	...	...	0.099	...	...	<i>0.0001</i>	0.022	0.073	...	0.30	...	...
456/3	Carbon Steel Residual Series (Group B)	0.1215	0.267	0.2121	0.0228	0.0246	0.0257	0.0014	0.0174	...	0.0393	...	0.0014	0.0520	<i>0.013</i>	<i>0.017</i>	0.0113	0.0153	...	<i><0.005</i>	0.0214	...	...	0.0222
457/2		0.307	0.105	0.327	0.0098	0.0448	...	...	...	0.082	0.087	...	0.0046	0.0217	...	...	0.0174	0.0098	...	...	0.153	...	0.025	0.050
458/2		0.198	0.504	0.479	0.0281	0.0314	...	...	...	0.052	0.055	...	0.0069	0.198	...	...	0.0510	0.0140	...	...	0.105	...	<i>0.062</i>	0.089
459/2		0.467	0.640	0.909	0.0482	0.0481	...	...	...	0.0134	0.0154	...	0.0110	0.0890	...	...	0.0102	0.0044	...	...	0.0585	...	0.074	0.0121
460/2		0.383	0.126	0.616	0.0374	0.0099	...	...	...	0.0193	0.0240	...	0.0027	0.0106	...	...	0.068	0.0005	...	...	0.0322	...	<i><0.0005</i>	0.0006

Unalloyed Steels (continued) (Rod material – BCS-CRM 318A is a pair of 6.35mm dia. x 95mm rods, BCS-CRM 318B is a single 12.7mm dia. x 127mm rod)

BCS-CRM No.	Description	Form	C	Si	Mn	P	S	Al	O
318A	0.01% Oxygen Steel	6.35mm dia. x 95mm rod	<i>0.083</i>	<i>0.12</i>	<i>0.39</i>	<i>0.018</i>	<i>0.035</i>	<i><0.002</i>	0.0096
318B	0.01% Oxygen Steel	12.7mm dia. x 127mm rod	<i>0.083</i>	<i>0.12</i>	<i>0.39</i>	<i>0.018</i>	<i>0.035</i>	<i><0.002</i>	0.0103

High-Speed Steels (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	Sn	V	W
241/2	251-1	High-Speed Steels	0.84	0.21	0.27	0.024	0.025	5.35	0.53	0.15	<i>0.009</i>	5.70	0.08	0.025	1.59	19.9
481	...		0.69	0.14	0.29	0.021	0.027	3.56	0.22	...	...	0.21	...	...	0.52	14.2
482	...		0.70	0.13	0.28	0.021	0.025	4.09	0.27	...	...	0.24	...	...	0.98	18.1
483	...		0.67	0.11	0.29	0.019	0.025	3.21	0.17	...	...	1.94	...	...	0.54	10.8
484	...		0.85	0.20	0.21	0.030	0.024	5.17	1.07	...	...	10.2	...	...	0.93	22.4

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Alloy Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Low Alloy Steels (Finely divided material - units of 100g; 112-114 also available as 44mm dia. x 19mm discs; 186-1, 195-1, 219/4, 222/1, 225/2, 401/2-405/2, 407/2 and 421-424 also available in disc form for spectroscopic analysis - see page 18)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Ca	Zn
112	...	Low Alloy Steels	0.394	0.289	0.436	0.0043	0.0026	1.236	0.190	1.461	0.0148	0.0021	0.0007	0.0175	0.149	0.0024	0.0065	<i><0.001</i>	0.0086	0.0100	0.0088	...	<i><0.001</i>	<i><0.0005</i>	...
113	...		0.837	0.931	1.207	0.0595	0.0294	1.248	0.056	0.0784	0.0151	0.0020	0.0066	0.0415	0.179	0.0109	0.0487	<i><0.001</i>	0.0067	0.0390	0.201	0.012	0.0029	<i><0.001</i>	...
114	...		0.403	0.295	0.416	0.0044	0.0046	0.187	0.184	1.502	0.078	0.0025	0.0008	0.0171	0.360	0.0043	0.0042	<i><0.001</i>	0.041	0.0096	0.0086	<i><0.001</i>	0.0051	<i><0.001</i>	...
214/2	152-1	Mn-Mo Steel	0.39	0.18	1.61	0.032	0.043	0.09	0.26	0.15	...	...	...	...	0.21	...	...	...	...	...	<i><0.01</i>	...	...	...	...
219/4	153-1	Ni-Cr-Mo Steel	0.314	0.079	0.81	0.011	0.027	0.66	0.58	2.55	<i>0.003</i>	...	...	...	0.088	...	...	...	0.011	...	...	...	...	...	...
222/1	...	3.5% Ni Steel	0.3095	0.227	0.618	0.0175	0.0089	0.0535	0.0287	3.536	...	...	<i><0.005</i>	0.0379	0.150	0.0100	...	...	...	...	<i>0.020</i>	...	...	...	...
225/2	155-1	Ni-Cr-Mo Steel	0.40	0.23	0.56	0.019	0.012	1.08	0.34	1.43	<i>0.009</i>	<i>0.035</i>	<i>0.0007</i>	<i>0.018</i>	<i>0.17</i>	<i>0.012</i>	<i>0.003</i>	...	<i>0.017</i>	...	<i><0.01</i>	...	<i><0.01</i>	...	...
317	151-1	Low C, High Si Steel	0.028	3.49	0.085	0.015	0.023	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...
...	186-1(C)	Silico Manganese Steel	0.6104	1.719	0.870	0.0223	0.0354	0.218	0.0482	0.190	0.0143	...	...	...	0.281	...	...	...	...	...	...	...	...	...	...
...	195-1(C)	Cr-Mo-Ni Steel	0.756	0.466	0.571	0.0160	0.0121	1.566	0.768	0.327	...	...	...	...	0.0355	0.0100	...	0.0010	<i>0.002</i>	...	0.312	...	...	0.0017	0.0046
408	...	Low Alloy Steel	0.28	0.24	0.64	0.043	0.030	0.090	0.14	4.58	...	...	...	...	0.73	...	...	...	...	...	0.063	...	...	...	...
404/1	...	Low Alloy Steels	0.74	0.87	0.31	0.057	0.024	0.48	0.31	0.40	...	...	...	...	0.34	...	...	...	...	...	0.11	...	...	...	...
405/1	...		0.032	1.71	1.28	0.018	0.069	0.15	0.002	0.22	...	...	...	...	0.013	...	...	...	...	...	0.28	...	...	...	...
407/1	...		0.47	0.59	0.047	0.030	0.010	2.95	0.78	0.59	...	...	...	...	0.57	...	...	...	...	...	0.18	...	...	...	...
409/1	...		0.082	1.46	0.44	0.025	0.021	0.94	0.65	3.06	...	...	...	0.014	0.048	...	...	...	...	...	0.09	...	...	...	...
401/2	...	Low Alloy Steels	0.935	0.602	1.197	0.0265	0.0078	0.138	0.495	0.019	0.074	...	...	0.0042	0.101	0.0159	...	...	...	...	0.496	...	...	...	...
402/2	...		1.311	0.111	0.228	0.0161	0.0138	0.652	0.140	0.808	0.161	...	...	...	0.302	0.0069	...	...	...	...	0.194	...	...	...	...
403/2	...		0.750	0.209	1.677	0.055	0.0381	0.463	0.088	0.223	0.0485	...	...	...	0.221	<i>0.010</i>	...	...	...	...	0.341	...	...	...	...
404/2	...		0.696	1.121	0.532	0.0479	0.0228	0.774	0.307	0.393	0.017	...	...	...	0.427	0.0089	...	...	...	...	0.107	...	...	...	...
405/2	...		0.044	0.947	0.903	0.0095	0.058	0.206	0.025	0.102	0.330	...	...	<i>0.009</i>	0.022	<i>0.011</i>	...	...	...	...	0.411	...	...	...	...
407/2	...		0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	...	...	0.0068	0.397	<i>0.011</i>	...	...	...	...	0.19	...	...	...	...
409/2	...		0.086	1.18	0.559	0.0141	0.0179	1.318	0.599	3.02	0.094	...	...	...	0.205	0.0108	...	...	...	...	0.008	...	...	...	...
421	...	Low Tungsten Steels	<i>0.049</i>	<i>0.07</i>	<i>0.11</i>	<i>0.012</i>	<i>0.027</i>	...	<i>0.028</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	0.52	...	...	...
422	...		<i>0.036</i>	<i>0.06</i>	<i>0.09</i>	<i>0.015</i>	<i>0.025</i>	...	<i>0.033</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	1.28	...	...	...
423	...		<i>0.030</i>	<i>0.05</i>	<i>0.07</i>	<i>0.017</i>	<i>0.027</i>	...	<i>0.027</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	2.06	...	...	...
424	...		<i>0.024</i>	<i>0.05</i>	<i>0.09</i>	<i>0.02</i>	<i>0.024</i>	...	<i>0.036</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	3.02	...	...	...

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steels (Finely divided material - units of 100g; 272-1, 276-2, 285-2, 287-1, 292-1, 296-1, 340 (SS70), 461/1-468/1, 466/2, 469-473, 475, 476, 477 and 479 also available in disc form for spectroscopic analysis - see pages 19 & 20)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	Mg	Sb	Others
...	272-1(C)	12% Chromium Steel	0.2815	0.420	0.600	0.0156	0.0197	11.927	0.0030	0.244	0.0046	0.0116	0.0018	0.0145	0.0192	0.0508	0.0028	<i>0.0004</i>	<i>0.0008</i>	0.00096	0.0167	<i>0.0002</i>	0.0007	0.00090 Ca 0.0031 Zn
...	276-2(C)	5% Cr-Mo-V Steel	0.399	1.034	0.365	0.0093	0.0189	4.975	1.134	0.203	...	...	...	...	0.183	0.0116	...	...	0.0133	...	0.296	...	...	...
...	281-1	18/9 Stainless Steel & Ti	0.048	0.929	0.786	0.012	0.016	18.17	...	9.37	0.015	<i>0.015</i>	0.0012	0.023	0.076	0.023	...	0.0005	0.009	0.216	...	...	...	...
...	285-2(C)	Maraging Steel	0.0018	0.0117	0.0168	0.0053	0.0025	0.0236	4.99	18.07	0.1067	...	0.0009	7.76	0.0094	0.0007	...	...	<i>0.001</i>	0.520	...	...	...	0.0050 Zr
...	287-1(C)	High B Stainless Steel	0.0164	0.569	1.478	0.0267	0.0014	18.61	0.247	10.35	...	...	0.924	0.148	0.203	0.0194	...	...	...	...	...	...	...	...
...	292-1(C)	Nb-Stabilised Stainless Steel	0.0367	0.402	1.744	0.0175	0.0055	18.00	0.0464	10.09	<i>0.002</i>	<i>0.008</i>	<i>0.0003</i>	0.0255	0.0391	0.0640	0.571	...	...	...	...	...	...	<i>0.001 Ta</i>
...	296-1(C)	Jethete Steel	0.1166	0.242	0.676	0.0178	0.0026	11.82	1.700	2.790	0.0275	0.0139	<i>0.0003</i>	0.0218	0.1498	0.0214	...	0.00016	0.0131	...	0.363	...	...	...
332	...	Austenitic Stainless Steel	0.063	0.44	0.80	0.015	0.020	12.78	...	12.47	...	...	...	<i>0.037</i>	<i>0.10</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
339	...	Ferritic Stainless Steels	0.29	0.36	0.41	0.022	0.022	12.39	...	0.37	...	...	...	...	<i>0.08</i>	...	...	...	...	...	...	...	...	...
340	...		0.18	0.35	0.38	0.024	0.020	16.36	...	0.40	...	...	...	...	<i>0.06</i>	...	...	...	...	...	...	...	...	...
341	...		0.103	0.31	0.43	0.016	0.024	24.01	...	0.56	...	...	...	...	<i>0.10</i>	...	...	...	...	...	...	...	...	...
342	...		0.18	0.92	0.91	0.030	0.026	16.13	0.69	2.16	...	...	...	...	<i>0.08</i>	...	...	...	...	...	...	...	...	...
463	...	Austenitic Stainless Steels	0.088	0.51	0.77	0.015	0.017	18.29	...	9.65	...	...	<i>0.0004</i>	...	...	...	...	...	...	...	...	...	...	...
461/1	...		0.0103	0.374	0.686	0.0053	0.0051	14.727	0.0138	6.124	<i>0.002</i>	<i>0.004</i>	...	<i>0.004</i>	0.0091	...	...	<i>0.005</i>	...	...	...	...	...	...
462/1	...		0.0345	0.463	0.722	0.0053	0.0041	11.888	0.0304	12.85	...	...	...	...	0.0112	...	...	...	...	...	...	...	...	...
463/1	...		0.019	0.270	1.400	0.025	0.019	18.46	0.265	10.20	...	...	0.0022	0.116	0.276	0.063	...	...	...	<i><0.005</i>	<i>0.04</i>	...	...	...
464/1	...		0.086	0.57	0.791	0.020	0.028	25.39	...	20.05	...	<i>0.003</i>	...	0.054	...	...	...	0.0004	...	...	...	...	...	...
465/1	...		0.066	0.405	1.380	0.021	0.012	17.31	0.092	9.24	0.026	...	0.0006	0.053	0.098	0.010	...	<i><0.001</i>	...	0.40	0.102	...	...	...
466/2	...		0.0141	0.480	1.311	0.0105	0.0069	17.84	2.776	10.20	<i>0.002</i>	0.0020	0.0039	0.0184	0.0278	0.0508	<i>0.001</i>	<i><0.0001</i>	<i><0.001</i>	<i>0.002</i>	0.0346	...	...	...
467/1	...		0.082	0.52	0.788	0.018	0.019	18.09	...	9.21	...	0.004	...	...	...	...	0.99	0.004	...	...	...	...	...	0.0017 Ta
468/1	...		0.143	1.41	1.70	0.014	0.020	17.96	...	8.90	...	...	...	0.018	...	...	...	...	...	...	...	...	...	...
469	...	Ferritic Stainless Steels	0.279	0.421	0.598	0.015	0.020	11.93	...	0.246	...	...	...	<i>0.01</i>	<i>0.02</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
470	...		0.153	0.335	0.235	0.024	0.035	17.68	...	0.369	...	...	...	<i>0.02</i>	<i>0.02</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
471	...		0.095	0.326	0.417	0.018	0.023	23.85	...	0.96	...	...	...	<i>0.02</i>	<i>0.02</i>	...	...	...	...	...	<i>0.03</i>	...	...	...
472	...		0.227	1.05	1.02	0.032	0.029	15.82	0.661	1.95	...	...	...	<i>0.02</i>	<i>0.02</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
473	...		0.172	0.604	0.494	0.019	0.030	9.06	0.95	<i>0.06</i>	...	...	...	<i>0.01</i>	<i>0.03</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
474	...	Stainless Steels	0.022	0.17	1.70	0.008	0.020	19.06	3.55	14.74	<i>0.006</i>	0.030	...	<i>0.02</i>	0.35	...	...	...	...	...	0.30	...	...	...
475	...		0.050	0.21	0.89	0.037	0.008	14.14	1.59	5.66	0.013	...	...	0.22	1.94	...	0.22	...	0.015	...	...	...	...	...
476	...	Mo-Stabilised Stainless Steel	0.0171	0.323	1.755	0.0302	0.0234	16.88	2.049	10.17	<i><0.005</i>	0.0053	...	0.1628	0.3026	0.0794	0.0107	<i><0.002</i>	0.0059	<i><0.005</i>	0.0663	...	<i>0.001</i>	0.0419 W 0.0028 Ca
477	...	4% Mo-Cr-Ni Steel	0.0102	0.473	1.623	0.0209	0.00039	20.38	4.23	25.07	0.0303	0.00399	0.00198	0.0875	1.340	0.0562	...	...	0.00453	...	0.0527	0.00053	0.00078	...
479	...	Nb-Stabilised Stainless Steel	0.0529	0.553	0.680	0.0029	0.0030	19.922	<i>0.003</i>	24.87	<i>0.013</i>	<i>0.002</i>	<i><0.0005</i>	<i>0.002</i>	0.0052	0.0057	0.625	<i><0.001</i>	<i><0.002</i>	0.0306	0.0052	...	...	<i><0.005 Ta</i>
290/2	253-1	High Manganese Steels	1.15	0.34	12.5	0.042	0.019	0.16	<i>0.031</i>	0.29	...	...	...	<i>0.35</i>	<i>0.17</i>	<i>0.013</i>	...	...	...	...	<i>0.02</i>	...	...	...
491	...		0.92	0.90	16.10	0.026	0.012	1.45	0.60	0.046	0.042	...	...	...	<i>0.04</i>	...	...	...	...	...	<i>0.06</i>	...	...	...
494	...		1.24	0.26	13.56	0.040	0.005	0.56	0.079	0.69	0.004	...	...	<i>0.43</i>	<i>0.19</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
495	...		0.82	0.46	13.56	0.036	0.014	1.93	0.035	1.05	0.103	...	...	...	<i>0.09</i>	...	...	...	...	...	<i>0.02</i>	...	...	...
495/1	...		0.81	0.58	13.13	0.054	0.026	1.93	0.109	1.13	0.170	...	...	...	...	...	...	...	...	...	<i>0.02</i>	...	...	...

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Special Alloys, Cast Irons and Ferro-Alloys

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Special Alloys (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	S	Ni	Al	Co	Cu	Nb	Ti	Ta
383	...	Alcomax III	0.025	...	<i>0.07</i>	0.202	<i>13.2</i>	<i>7.7</i>	<i>24.4</i>	<i>2.63</i>	<i>0.51</i>	...	...
398	...	Alnico HC	0.025	0.11	0.065	0.19	16.59	9.98	14.92	6.09	0.13	0.765	...
...	376-1	24% Cobalt Magnet Alloy	0.0256	0.313	0.046	0.0040	13.37	8.12	23.70	2.94	0.309	0.158	<i>0.016</i>

Cast Irons (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Graphite	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Sn	Ti	V	Mg
...	451-2	Austenitic Cast Iron	2.059	...	2.092	1.079	0.0593	0.0315	1.097	...	14.01	...	...	6.26	...	...	...	...	...
206/3	453-1	High Si and P Iron	<i>2.44</i>	<i>2.37</i>	3.17	0.72	1.63	0.049	0.053	...	0.068	...	0.019	0.10	...	...	<i>0.040</i>	0.050	...
236/3	454-1	Hematite Iron	<i>2.53</i>	<i>1.96</i>	2.00	1.16	0.046	0.068	...	...	<i>0.21</i>	...	<i>0.025</i>	<i>0.07</i>	...	...	0.052	...	...
...	482-2	Low Alloy Cast Iron	2.599	...	1.815	0.728	0.0974	0.0491	0.675	0.454	2.284	...	...	1.231	...	...	...	...	...
...	484-1	Whiteheart Malleable Iron	3.203	...	0.717	0.395	0.121	0.230	0.155	...	...	...	...	...	...	...	...	...	...
...	486-1	Foundry Iron	2.212	...	2.429	0.841	0.996	0.0233	0.104	...	0.0571	...	...	0.548	...	0.074	...	0.0197	...
...	489-1	White Iron	2.860	...	1.524	<i>0.510</i>	0.815	0.155	...	...	...	...	...	0.274	<i>0.0056</i>	...	...	...	...
527	...	Blast Furnace Iron	3.873	...	1.000	0.316	0.1269	0.0366	<i>0.087</i>	<i>0.006</i>	0.0229	...	...	0.0104	...	...	0.0187	<i>0.010</i>	...
535	...	High Carbon Iron Powder	3.875	...	2.702	0.456	0.1438	0.0276	0.0501	0.0037	1.349	0.0087	0.0049	0.1397	...	...	...	...	...

Ferro-Alloys (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	B	Co	Cu	N	Nb	Sn	Ti	V	W	Ca	Ta	Fe
203/6	...	Low C Ferro-Chromium	0.0270	0.381	0.153	0.0195	0.004	71.01	...	0.218	...	...	...	0.0442	...	<i>0.029</i>	...	...	<i>0.003</i>	0.0729	...	...	...	...
204/6	...	High C Ferro-Chromium	8.57	0.715	0.225	0.0164	0.0190	68.77	...	0.289	...	...	...	0.0359	...	<i>0.023</i>	...	...	0.0565	0.094	...	...	...	...
208/3	...	High C Ferro-Manganese	6.834	0.603	77.91	0.137	0.006	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	...	<i>13.82</i>
231/5	...	Ferro-Molybdenum	0.212	1.663	<i>0.84</i>	0.0289	0.0424	<i>0.78</i>	61.70	...	...	...	<i>0.19</i>	...	0.270	...	<i>0.83</i>	<i>0.004</i>	...	...	...	...	...	<i>32.0</i>
231/6	...	Ferro-Molybdenum	0.0568	0.722	<i>0.21</i>	0.0211	0.0305	<i>0.21</i>	71.41	...	...	...	...	...	0.2230	...	<i>0.14</i>	<i>0.003</i>	...	...	...	...	...	<i>26.3</i>
242/2	555-1	Ferro-Tungsten	0.025	1.75	...	<i>0.02</i>	<i>0.018</i>	...	...	...	...	0.14	...	...	...	...	...	0.034	...	...	79.9	...	...	<i>15.2</i>
305/2	...	Ferro-Silicon	0.113	76.80	0.152	0.029	<i>0.002</i>	<i>0.08</i>	...	...	...	1.12	...	...	...	...	...	<i>0.08</i>	...	...	0.270	...	...	<i>20.0</i>
...	576-1	Ferro-Niobium (40% Nb)	0.201	1.79	...	...	...	...	...	...	...	2.53	...	...	...	...	43.90	0.195	1.32	...	...	...	0.306	...
...	577-1	Ferro-Vanadium	0.089	1.79	0.158	0.035	0.034	...	...	0.053	<i>0.21</i>	0.414	...	...	0.054	...	...	...	50.16	...	...	...	...	...
...	579-1	Ferro-Niobium (60% Nb)	0.037	1.03	...	0.064	0.021	...	...	...	...	1.86	...	0.0051	...	...	62.87	0.344	0.567	...	...	...	3.85	...
...	583-1	Ferro-Manganese	0.333	0.396	86.42	0.146	<i>0.007</i>	...	...	...	...	...	...	...	...	<i>0.041</i>	...	...	...	...	...	...	...	<i>12.3</i>
...	584-1	Ferro-Titanium	0.044	1.80	1.13	0.032	0.030	...	...	...	<i>6.0</i>	7.19	...	...	...	...	...	...	37.17	...	...	...	...	...
...	587-1	Ferro-Boron	0.738	<i>0.129</i>	0.272	<i>0.020</i>	<i>0.001</i>	<i>0.10</i>	<i>0.005</i>	...	...	0.047	18.7	<i>0.010</i>	...	...	...	...	<i>0.04</i>	<i>0.004</i>	...	...	...	...
...	590-1	Ferro-Tungsten	0.0250	1.05	0.136	...	<i>0.07</i>	...	0.101	...	...	<i>0.37</i>	...	...	0.0484	...	...	0.045	...	...	79.55	...	...	<i>17.9</i>

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Aluminium, Magnesium, Copper, Lead & Tin Base Alloys

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Aluminium and Magnesium Base Alloys (Finely divided material - units of 100g)

BCS-CRM No.	Description	Si	Fe	Cu	Mn	Mg	Cr	Zn	Ti	Pb	Sn	Ni	Sb	Zr	Be	Total Rare Earths	Al
181/3	2.5% Cu Aluminium Alloy	0.30	0.72	2.48	1.10	1.57	0.04	2.52	0.058	0.101	...	2.00	...	...	...	...	Bal.
182/3	11% Si Aluminium Alloy	11.03	0.51	0.037	0.26	0.068	...	0.128	0.107	0.056	0.027	0.047	...	...	...	...	Bal.
216/3	5% Cu Aluminium Alloy	0.74	0.77	5.45	0.76	0.76	0.108	0.214	0.20	0.052	0.052	0.24	0.01	0.084	...	...	Bal.
262/1	10% Mg Aluminium Alloy	0.16	0.20	0.039	0.084	10.74	0.002	0.084	0.005	0.05	0.04	0.071	...	...	<0.01	...	Bal.
263/2	5% Mg Aluminium Alloy	0.14	0.26	0.019	0.36	4.67	0.074	0.056	0.022	...	...	...	...	...	<0.001	...	Bal.
268/1	5% Si Aluminium Alloy	5.49	0.47	1.35	0.24	0.49	...	0.028	0.008	0.028	0.031	0.16	...	...	...	...	Bal.
300/1	6% Zn Aluminium Alloy	0.14	0.24	1.27	0.33	2.74	0.13	5.87	0.09	...	...	...	...	0.18	...	...	Bal.
343	Wrought Aluminium Alloy	0.52	0.39	0.28	0.69	0.70	0.14	0.028	0.024	...	...	...	...	...	...	...	Bal.
349	3.5% Cu Aluminium Alloy	1.19	0.154	3.40	0.111	0.024	<0.001	0.298	0.034	0.077	0.074	...	...	...	<0.001	...	Bal.
380/1	2% Si Aluminium Alloy	1.93	1.24	0.91	0.094	0.24	<0.001	0.025	0.024	0.014	...	0.94	...	...	...	...	Bal.
307	Magnesium Alloy (ZRE 1)	<0.001	0.002	0.005	0.006	Bal.	...	2.08	...	...	<0.001	<0.001	...	0.56	...	2.84	0.008
316	8% Al Magnesium Alloy	0.054	0.009	0.040	0.28	Bal.	...	0.68	...	0.024	0.005	0.004	...	...	...	...	8.01
505	Aluminium-Silicon Alloy	12.8	0.30	0.05	0.52	0.05	...	0.24	0.03	0.09	0.17	0.20	...	...	...	...	Bal.

Copper Base Alloys (Finely divided material - units of 100g)

BCS-CRM No.	Description	Cu	Sn	Zn	Pb	P	Ni	Fe	Al	Mn	Sb	As	Si	Bi	Mg	S	C	Cd
179/2	High Tensile Brass (Cast)	58.5	0.70	35.8	0.35	...	0.56	1.02	2.22	0.86	...	0.008	0.044	...	...	...	...	0.003
180/2	Copper Nickel	68.12	...	...	0.003	...	30.35	0.68	...	0.75	...	...	0.018	...	...	0.006	0.04	...
183/4	Leaded Gunmetal	84.08	7.27	3.47	3.15	0.090	1.30	0.056	<0.002	0.01	0.23	0.13	0.01	0.005	...	0.11	...	...
207/2	Gunmetal	87.35	9.74	1.60	0.70	0.018	0.28	0.029	0.013	...	0.10	0.066	0.016	0.04	...	...	...	...
304/1	Copper-Aluminium	80.23	0.03	0.31	0.010	...	4.82	4.64	9.71	0.12	...	...	0.08	...	<0.01	...	...	...
344	70/30 Brass	68.98	...	30.98	...	...	...	...	...	...	...	...	...	...	...	...	...	...
364	Leaded Bronze	80.7	9.36	0.13	9.24	0.057	0.28	<0.005	<0.002	...	0.18	0.07	<0.005	<0.01	...	0.06	...	...
374	Phosphor Bronze	89.5	9.80	0.006	0.064	0.59	0.014	<0.005	<0.005	...	0.01	...	<0.005	0.007	...	0.012	...	...
385	Leaded Brass	58.7	0.27	38.5	2.24	...	0.13	0.15	<0.005	<0.005	<0.01	...	...	...	...	...	...	...
390	High Tensile Brass (Wrought)	57.1	0.34	38.6	1.04	...	0.033	0.83	0.83	1.30	...	...	0.023	...	...	...	...	0.011
399	Phos. Deoxidised Copper	99.93	0.003	0.003	0.002	0.045	0.002	0.006	...	...	<0.001	<0.001	...	0.001	...	...	...	0.003

Lead and Tin Base Alloys (Finely divided material - units of 100g)

BCS-CRM No.	Description	Pb	Sn	Sb	Cu	As	Bi	Cd	Fe	Ni	Zn	Al	Ag	Au	In
177/2	Lead Base White Metal	84.5	5.07	10.1	0.12	0.05	0.028	...	...	0.007	...	...	0.008	...	...
178/2	Tin Base White Metal	3.18	82.2	9.45	4.58	0.15	0.11	0.14	0.024	0.17	0.040	0.005	0.02	...	...
347	Electronic Flowsolder	Bal.	62.6	0.191	0.169	0.02	0.080	0.0040	0.002	0.0072	0.0015	<0.001	0.099	0.037	0.006

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Nickel & Titanium Base Alloys, Chromium Metal, Cements, Fluorspar & Bauxites

CHEMICAL COMPOSITION - Figures in bold type certified, figures in small italic type only approximate.

Nickel Base Alloys (Finely divided material - units of 100g - 345, 346 (346A), 350, 351/1, 363/1 & 387/1 also available in disc form for spectroscopic analysis - see page 21)

MAJOR ELEMENTS - nominal mass content in %

BCS-CRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Nb	Ti	V	W	Zr	Fe
310/1	Nimonic '90' Alloy	0.068	0.46	0.35	...	...	19.43	...	58.6	1.06	...	17.0	...	...	...	2.43	...	...	...	0.25
345	IN 100 Alloy	0.153	...	...	...	...	9.95	3.01	Bal.	5.58	0.019	14.71	...	...	...	4.74	1.00	...	0.044	...
346	IN 100 Alloy	<i>0.15</i>	...	...	...	...	<i>10</i>	<i>3</i>	Bal.	<i>5.5</i>	...	<i>15</i>	...	...	...	<i>5</i>	<i>1</i>	...	...	...
350	IN 713 Alloy	0.138	0.110	0.019	...	...	13.43	4.29	70.8	5.97	0.013	0.338	...	...	2.17	0.87	...	0.094	0.072	1.50
351/1	IN 718 Alloy	0.0255	0.080	0.0562	0.0045	0.00037	19.14	3.04	53.35	0.554	0.0035	0.145	0.0222	0.0077	5.31	0.938	0.0181	0.0209	0.0017	17.20
363/1	Monel Alloy 400	0.140	0.028	1.26	...	<i>0.002</i>	<i>0.05</i>	...	64.7	0.027	...	0.032	31.90	...	...	<i>0.03</i>	...	...	...	1.86
371	Commercial Nickel	0.30	0.34	...	...	0.013	...	...	Bal.	...	...	0.39	...	...	...	...	...	...	...	...
387/1	Nimonic 901 Alloy	0.033	0.06	0.025	0.0033	0.0028	11.35	5.83	41.2	0.24	0.017	0.020	0.0076	...	<i>0.006</i>	3.00	...	...	...	38.4
478	Incoloy 800 Alloy	0.0710	0.290	0.512	0.0057	0.0010	19.69	0.0061	30.90	0.544	...	<i>0.01</i>	<i>0.005</i>	0.0076	...	0.479	<i>0.02</i>	<i><0.001</i>	...	...

Nickel Base Alloys (continued)

TRACE ELEMENTS - nominal mass content in µg/g

BCS-CRM No.	Description	Pb	Bi	Ag	Se	Te	Tl	Sb	Ta	As	Cd	Ga	Sn	Zn	Mg	Ca	In
345	IN 100 Alloy	0.21	<0.2	<0.2	<0.5	<0.2	<0.2	<2	...	<i>2</i>	<0.1	8.2	5.6	<0.5	5.5	<5	...
346	IN 100 Alloy	21.0	10.4	35.0	9.1	11.7	1.8	47	...	50.3	0.42	50.6	91	28.9	147	39	19
351/1	IN 718 Alloy	<1	<1	<1	<1	<1	<1	2.4	33	<10	<0.1	<20	3.3	<10	16	<10	...
371	Commercial Nickel	...	...	...	...	...	...	...	...	...	...	...	...	...	600	...	...
387/1	Nimonic 901 Alloy	<i>0.3</i>	<i><1.0</i>	<i>≤0.2</i>	...	...	...	3	...	...	...	...	...	...	...	...	...

Titanium Base Alloys (Finely divided material - units of 50g)

nominal mass content in %

BCS-CRM No.	Description	Al	V	Fe	Cu	Ni	Cr	Mo	N	Sn	Si	W	C	H	O	B	Zr	Y
356	Titanium Alloy	6.25	4.05	0.124	0.0055	0.0070	0.0112	0.0020	0.0103	<i>0.0155</i>	<i>0.0200</i>	<i>0.0010</i>	<i>0.0085</i>	<i>0.0019</i>	<i>0.2000</i>	<i><0.0005</i>	<i><0.0005</i>	...
357	Titanium Alloy	5.46	3.53	0.202	0.0537	0.0511	0.0521	0.053	0.0148	<i>0.0620</i>	<i>0.0500</i>	<i><0.001</i>	<i>0.0072</i>	<i>0.0012</i>	<i>0.2500</i>	<i>0.0013</i>	<i>0.0455</i>	<i>0.0046</i>

Chromium Metal (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	C	Si	S	N	Fe	O	Al (Total)
361	Chromium Metal	0.0039	0.0449	0.0043	0.0079	0.092	0.101	<i>0.083</i>

Chrome Ore (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	FeO*	SiO ₂	Al ₂ O ₃	Cr ₂ O ₃	TiO ₂	CaO	MgO	MnO	P	Na ₂ O	K ₂ O	Cr (VI)
308/1	Chrome Ore	26.58	1.194	15.10	44.91	0.74	0.65	9.15	0.230	<i><0.006</i>	<i><0.015</i>	<i><0.0054</i>	<i>0.0006</i>

*Total Iron expressed as FeO

Cements (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	Cr ₂ O ₃	Mn ₂ O ₃	CaO	MgO	Na ₂ O (Acid Sol)	K ₂ O (Acid Sol)	P ₂ O ₅	SO ₃	SrO	Cl
353	Sulphate-Resisting Portland Cement	20.5	3.77	0.16	4.82	<i>0.02</i>	0.23	64.8	2.42	0.10	0.49	0.077	2.25	0.23	<i>0.01</i>
354	White Portland Cement	21.8	4.85	<i>0.04</i>	0.30	<i>0.003</i>	0.057	70.0	0.42	0.10	0.11	0.12	2.25	0.11	<i>0.005</i>

Fluorspar & Bauxites (Finely divided material - units of 100g)

nominal mass content in %

BCS-CRM No.	Description	Fe ₂ O ₃	SiO ₂	Al ₂ O ₃	CaF ₂	TiO ₂	CaO	MgO	P ₂ O ₅	BaO	Na ₂ O	K ₂ O	S	CO ₂	Cr	Cu	Mn	Ni	Pb	Sr	Zn	L.O.I.
392	Fluorspar	...	0.67	...	97.2	...	0.52	...	...	0.37	...	...	0.12	0.48	...	...	...	...	0.18	...	...	...
394/1	Calcined Bauxite	1.372	6.47	88.88	...	2.967	0.0173	0.0047	0.0574	...	<0.01	<0.01	...	...	...	...	...	...	...	...	...	0.05
395	Bauxite	16.3	1.24	52.4	...	1.93	0.05	0.02	...	...	0.02	0.02	...	...	0.0453	0.0021	0.0042	0.0034	0.0028	0.0023	0.0043	27.8

BRITISH CHEMICAL STANDARD AND EURONORM CERTIFIED REFERENCE MATERIALS - Non-Metallic Materials

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Iron Ores & Furnace Dust (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	F	V	Cr	Zn	LOI
301/1	651-1	Lincolnshire Iron Ore	23.85	3.46	16.1	1.04	2.25	0.10	0.97	0.35	0.40	0.05	0.26	...	...	...	...	25.8
377/6	...	Iron Ore Sinter	54.78	2.982	5.74	0.907	0.783	0.1001	0.604	0.0586	0.04	0.10	0.57	0.30	0.0178	0.0154	1.002	...
517	...	Brazilian Iron Ore	66.30	0.519	0.033	0.0311	0.508	0.0332	0.679	0.0408	0.0090	0.0097	0.0105	...	0.0040	...	0.0047	1.898
...	676-1	Iron Ore Sinter	39.76	6.40	12.78	1.16	3.40	0.19	0.83	0.59	0.12	0.095	0.43	0.10	0.070	...	...	...
...	682-2	Iron Ore	66.12	0.833	0.007	0.0133	0.325	0.0441	0.0311	0.0529	0.0140	0.002	...	...	0.0015	0.0015	0.0014	3.01
...	690-1	Haematite Iron Ore	66.70	0.881	0.269	0.815	0.198	0.229	0.0337	0.0085	0.001	0.0312	0.0158	...	0.1417	0.0113	0.002	...
...	884-1	Furnace Dust	31.67	2.101	5.22	1.848	0.379	0.0230	5.85	0.079	0.49	0.585	0.979	0.411	0.0303	1.86	17.50	2.94

Iron Ores & Furnace Dust (continued)

BCS-CRM No.	ECRM No.	Description	Ni	Pb	C	Co	Cu	Ag	As	Ba	Bi	Cd	Mo	Sn	Cl _(sol)	Cl	Hg	H ₂ O
301/1	651-1	Lincolnshire Iron Ore (cont.)	...	...	6.0	...	...	...	...	...	...	...	...	...	...	...	...	5.3
377/6	...	Iron Ore Sinter (cont.)	0.009	0.1485	...	<0.002	0.08	...	...	0.01	...	...	...	...	...	...	...	...
517	...	Brazilian Iron Ore (cont.)	0.0003	0.0028	0.061	0.0003	0.0088	...	0.0004	0.015	...	≤0.0001	...	...	0.00075	...	...	...
...	682-2	Iron Ore (cont.)	...	0.0004	...	0.0006	0.0005	...	...	...	...	...	...	...	...	...	<0.0001	...
...	690-1	Haematite Iron Ore (cont.)	0.0200	<0.002	...	0.0089	0.0006	...	...	...	...	...	...	0.001	...	0.001	...	...
...	884-1	Furnace Dust (cont.)	0.197	0.442	0.82	0.0046	0.1569	0.0028	0.0054	...	0.0280	0.0045	0.208	0.0186	...	0.991	0.0002	0.30

Manganese Ores (Finely divided material - units of 100g)

BCS-CRM No.	Description	Mn	Fe	SiO ₂	Al ₂ O ₃	TiO ₂	CaO	MgO	P	Na ₂ O	K ₂ O	BaO	Co	Cu	S	As ₂ O ₃	B
176/3	Manganese Ore	27.69	0.976	14.31	2.504	0.0972	6.83	4.72	0.0602	0.285	0.363	0.0157	0.0056	0.0054	0.235	0.049	0.009
176/4	Manganese Ore	29.13	0.839	13.09	2.236	0.0854	5.59	5.36	0.0582	0.321	0.261	0.0135	0.0050	0.0041	0.160	0.051	0.011

Copper Concentrate / Zinc Concentrate (Finely divided material - units of 100g)

BCS-CRM No.	Description	SiO ₂	MgO	CaO	Cu	Zn	Pb	S	Fe	Ag	Au	Cd	Mn	Ni	Al ₂ O ₃	Na ₂ O	K ₂ O	As	Bi
514	Copper Concentrate	2.97	0.184	0.263	25.24	0.268	0.010	35.89	31.41	0.0034	0.00193	0.0043	0.0027	0.0021	0.59	0.074	0.070	<0.005	<0.005
520	Zinc Concentrate	1.78	0.266	0.125	0.568	52.50	0.820	31.78	9.88	0.0036	...	0.0735	...	...	0.334	...	...	0.0228	...

BCS-CRM No.	Description	C	Mo	Cl	Co	Cr	F	Hg	In	P	Sb	Se	Te	Ti	Ba	Be	Ge	Sn	Tl
514	Copper Concentrate (cont.)	0.064	0.058	<0.005	0.010	<0.005	0.005	<0.0005	<0.003	0.006	<0.01	0.021	<0.005	0.017	<0.005	<0.0005	<0.002	<0.01	<0.002

Slags (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	SiO ₂	TiO ₂	Al ₂ O ₃	Fe	FeO	CaO	MgO	Cr ₂ O ₃	MnO	V ₂ O ₅	P ₂ O ₅ (Cit. Sol.)	P ₂ O ₅ (Form. Sol.)	P ₂ O ₅ (Total)	S	F
381	...	Basic Slag	8.78	0.35	0.67	13.3	3.69	49.0	1.03	0.33	3.16	0.94	15.2	...	15.7	0.19	...
...	879-1	Basic Slag	8.82	0.535	0.803	18.97	...	43.70	2.19	0.477	4.45	0.738	7.59	5.73	8.46	0.102	0.368

Tungsten Carbide and Silicon Carbide Refractories (Finely divided material - units of 100g)

BCS-CRM No.	ECRM No.	Description	C (Total)	Si (Total)	Al (Total)	C (Free)	Si (Free)	Fe (Total)	Mn	P	Cr	Mo	Ni	B	O	N	Ti	V	Ca	Mg	Na	K
...	783-1	Tungsten Carbide	6.188	...	...	0.04	...	0.0022	...	...	...	...	...	...	0.01	...	...	...	...	...	...	...
...	781-1	Silicon Carbide Refractory	48.25	35.56	4.39	37.22	4.646	0.8061	0.0274	0.0117	0.0240	0.0264	0.0210	0.0149	10.5	0.0282	0.0320	0.0216	0.0433	0.0421	0.0308	0.3765
359	...	Nitrogen Bearing Silicon Carbide	23.46	67.6	0.118	0.061	0.325	0.175	<0.01	...	...	...	0.014	...	0.532	7.84	0.022	0.027	0.108	<0.01	<0.01	<0.01
360	...	Sialon Bonded Silicon Carbide	23.53	60.8	6.52	0.085	0.538	0.19	<0.01	...	<0.01	...	0.013	...	4.03	4.77	0.025	...	0.115	<0.02	<0.01	<0.01

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE MATERIALS - Ceramic Materials and Minerals

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ceramic Materials, Minerals & Glass Sands (All finely divided material - units of 100g, except BCS-CRM 525 – units of 25g)

BCS-CRM No.	ECRM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	Mn ₃ O ₄	CaO	MgO	Na ₂ O	K ₂ O	BaO	Cr ₂ O ₃	PbO	ZnO
309	...	Sillimanite	34.1	61.1	1.92	1.51	0.03	...	0.22	0.17	0.34	0.46	0.006	...	...	...
313/2	...	High Purity Silica	99.73	0.068	0.0243	0.0229	0.00032	...	0.0160	0.0038	0.0057	0.0108	0.00067	...	...	0.0014
319/1	...	Magnesia	1.093	0.109	0.0070	0.291	0.108	...	3.00	95.38	...	...	0.0038	0.0035	...	...
348	...	Ball Clay	51.1	31.6	1.08	1.04	...	...	0.17	0.30	0.34	2.23	0.04	0.016	...	...
358	...	Zirconia	0.21	0.08	0.20	0.065	...	...	1.50	3.42	<0.01	<0.01	0.10	...	...	...
362*	...	Mine Tailings Sample	9.03	0.667	0.047	0.483	...	0.829	44.21	0.068	0.084	0.14	2.02	0.003	2.63	2.59
369	...	Magnesite-Chrome	2.59	14.7	0.14	10.3	0.11	...	1.17	53.5	0.05	0.03	<0.01	17.2	...	...
370	...	Magnesite-Chrome	3.01	12.3	0.13	7.23	0.11	...	1.54	61.8	0.06	0.03	<0.01	13.4	...	...
375/1	...	Soda Feldspar	69.26	17.89	0.313	0.291	...	Mn ₂ O ₃	0.78	0.180	8.89	1.47	0.0106	0.0018	0.0004	0.0005
376/1	...	Potash Feldspar (SGT Feldspar 1)	65.77	18.63	<0.01	0.085	...	0.004	0.421	0.03	3.00	11.59	0.0210	0.001	0.0090	...
388	...	Zircon	32.7	0.291	0.232	0.049	...	...	0.04	<0.05	<0.02	<0.03	...	...	...	...
389/1	...	High Purity Magnesite	0.274	0.104	0.0051	0.607	0.100	...	0.880	97.89	...	...	0.0015	0.004	...	0.0029
393	752-1	Limestone	0.70	0.12	0.009	0.045	0.010	...	55.4	0.15	0.02	0.02	0.006	...	...	...
396	...	Low Silica Magnesite Chrome	1.37	5.73	0.26	10.9	0.17	...	1.12	64.6	0.06	0.03	...	15.6	...	...
512	...	Dolomite (SGT Dolomite 1)	0.379	0.055	0.0020	0.030	0.0036	...	30.61	21.59	0.1	<0.02	<0.02	<0.001	<0.001	<0.01
513	...	Limestone (SGT Limestone 1)	0.228	0.108	0.004	0.0275	0.0095	...	55.59	0.182	<0.3	0.0150	0.01	0.0012	0.0009 Pb	0.0014 Zn
516	...	Standard Glass Sand (SGT Glass Sand 10)	98.73	0.513	0.172	0.0596	...	0.0012	0.0243	0.0387	0.0195	0.127	0.0040	0.0081	0.0127	<0.01
525	...	Low Iron Float Glass	72.55	0.167	0.021	0.0166	...	0.0012	8.91	4.28	13.43	0.087	0.0041	0.0003	0.0004	...
528	...	Standard Glass Sand (SGT Glass Sand 11)	95.62	2.447	0.0486	0.1111	...	...	0.237	0.0887	0.101	0.875	0.0298	0.0008	0.0006	0.001
529	...	Anorthic Feldspar	56.24	26.84	0.087	0.273	...	...	9.58	0.045	5.58	0.42	0.093	0.002	...	...
531	...	Low Iron Sand	99.74	0.0327	0.0160	0.00636	0.00014	...	0.0040	0.00132	0.003	0.0039	0.00112	<0.0002	<0.001	...
532	...	Swedish Feldspar	77.07	13.46	0.019	0.1813	...	...	0.212	0.159	4.35	3.80	0.015	0.004	...	...
...	776-1	Firebrick	62.76	29.28	1.62	1.43	...	...	0.310	0.476	0.488	2.92	0.122	0.022	...	...
...	782-1	Dolomite	0.266	0.104	0.0042	0.450	0.081	...	30.34	21.29	...	0.0260	0.0008	0.0009	0.0029	0.0082

*Additional certified values available for Aqua Regia soluble content and pH in BCS-CRM 362: As=0.0030%, Cd=0.0200%, Cr=0.0011%, Cu=0.0056%, Ni=0.0012%, Pb=2.30%, Zn=2.03% and pH=8.14

Ceramic Materials, Minerals & Glass Sands (continued)

BCS-CRM No.	ECRM No.	P ₂ O ₅	ZrO ₂	S	L.O.I.	B ₂ O ₃	HfO ₂	Li ₂ O	SrO	ThO ₂	U ₃ O ₈	Y ₂ O ₃	As	C	Cd	F	Mn	Ni	Sn
309	...	...	...	...	0.1	...	...	0.01	0.003	...	...	...	...	...	...	...	...	...	...
313/2	...	0.0022	...	...	0.14	...	...	...	0.00024	...	...	...	...	...	...	...	...	...	...
319/1	...	0.007	0.0008	...	...	0.002	...	...	0.0060	...	...	0.0014	...	...	...	...	...	0.0075	...
348	...	0.071	0.03	0.1	11.8	...	...	...	...	...	...	...	...	1.64	...	...	...	...	...
358	...	...	92.70	...	0.08	...	1.63	...	0.07	0.0007	0.08	...	...	...	...	...	...	...	...
362*	...	0.014	...	1.48	32.81	...	...	...	0.034	...	...	...	...	9.9	0.020	...	...	0.001	...
369	...	...	...	...	...	...	...	0.03	<0.01	...	...	...	...	...	...	...	...	0.15	...
370	...	...	...	...	...	...	...	0.03	<0.01	...	...	...	...	...	...	...	...	0.08	...
375/1	...	0.226	0.0107	...	0.72	...	0.0004	...	0.012	0.0011	0.0002	0.0023	...	...	...	...	...	...	...
376/1	...	0.02	<0.01	...	0.203	...	...	...	...	...	...	...	...	...	...	...	...	...	...
388	...	0.122	64.9	...	0.20	...	1.28	...	...	0.019	0.034	0.136	...	...	...	...	...	...	...
389/1	...	0.0295	0.0008	...	...	0.015	...	...	0.0007	...	...	0.0029	...	...	...	...	...	0.0012	...
393	752-1	0.005	...	0.007	43.4	...	...	...	0.019	...	...	...	...	...	<0.01	...	...	...	...
396	...	...	...	...	0.04	0.09	...	0.05	...	...	...	...	...	...	...	...	...	...	...
512	...	<0.02	...	<0.05	46.80	...	...	...	0.024	...	...	...	<0.003	12.4	<0.001	0.01	...	<0.001	...
513	...	0.005	...	0.0097	43.61	...	...	...	0.0176	...	...	...	<0.001	11.9	<0.001	<0.005	...	<0.001	...
516	...	0.013	0.075	SO ₃	0.24	...	<0.01	...	<0.01	...	...	...	...	...	...	...	...	...	...
525	...	0.004	0.0045	0.284	0.43	...	...	...	0.0038	...	...	...	...	...	...	...	...	...	...
528	...	0.20	0.014	...	0.271	...	...	...	...	...	...	...	...	...	...	...	<0.002	...	0.0016
529	...	0.047	...	0.135	0.550	...	...	...	0.323	...	...	...	...	...	...	...	...	0.15	...
531	...	0.00082	0.002	0.0009	0.12	...	...	...	0.00017	...	...	...	...	...	...	...	...	...	<0.001
532	...	...	...	...	0.56	...	...	...	...	...	...	...	...	...	...	...	...	...	...
...	776-1	0.062	0.04	...	0.3	...	...	0.019	...	...	...	...	...	...	...	...	...	...	...
...	782-1	0.0128	...	0.016	47.25	0.0039	...	...	...	...	...	...	...	...	...	...	...	0.0004	...

BRITISH CHEMICAL STANDARD CERTIFIED REFERENCE AND REFERENCE MATERIALS - Soda Ash, High Purity Metals, Ceramic Materials and Benzoic Acids

Although the High Purity Metals, Ceramic Materials and Benzoic Acid samples below have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

CHEMICAL COMPOSITION (nominal mass content in %)

Soda Ash Certified Reference Material (Finely divided material - units of 100g)

BCS-CRM No.	Description	Na ₂ CO ₃	NaCl	Fe ₂ O ₃	Na ₂ SO ₄	Insoluble Residue
526	Soda Ash (SGT Soda Ash 1)	99.74	0.126	0.0005	0.008	<0.02

Glass Certified Reference Materials (BCS-CRM 533 supplied in units of 25g broken pieces. BCS-CRM 534 supplied in 40mm dia. x 5mm discs)

BCS-CRM No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	BaO	Na ₂ O	K ₂ O	TiO ₂	SO ₃
533	Container Glass	72.57	1.447	0.0191	9.66	2.16	0.0024	13.66	0.0293	0.0393	0.221
534	Float Glass	71.62	0.428	0.057	9.92	3.40	0.0094	13.95	0.234	0.0233	0.222

High Purity Metal Reference Materials (Finely divided material or blocks/bars - see below)

BCS-RM No.	Description	Ag	As	Bi	C	Cd	Co	Cu	Fe	Ga	In	Mn	Ni
192j	High Purity Tin (100g millings or 300g blocks)	...	<0.0001	<0.0001	0.001	<0.0001	...	<0.0001	<0.0005	...	<0.0001	...	<0.0001
194e	High Purity Zinc (300g blocks)	...	<0.00005	...	...	<0.0005	...	<0.0005	0.001	...	<0.0005	...	...
195g	High Purity Aluminium (100g millings or 300g blocks)	...	...	...	...	...	...	0.001	0.080	0.009	...	0.001	...
198f	Super Pure Aluminium (100g blocks)	...	...	...	...	...	...	0.005	0.001	...	...	...	...
210e	High Purity Lead (500g bars)	0.0001	<0.002	0.0008	...	<0.0001	<0.005	0.0006	0.0005	...	...	<0.001	<0.001

High Purity Metal Reference Materials (continued)

BCS-RM No.	Description	S	Sb	Si	Ti	Tl	V	Al	Pb	Sn	Zn	Melting Point
192j	High Purity Tin (continued)	0.0002	<0.001	...	...	...	...	...	<0.001	99.996	<0.0001	231.9°C
194e	High Purity Zinc (continued)	...	...	...	...	<0.0005	...	...	0.002	<0.001	99.99	419.5°C
195g	High Purity Aluminium (continued)	...	...	0.035	0.002	...	0.004	99.85	...	...	0.015	659.2°C
198f	Super Pure Aluminium (continued)	...	...	0.002	...	...	...	99.99	...	...	...	...
210e	High Purity Lead (continued)	...	<0.002	...	...	0.001	...	<0.001	99.996	<0.002	<0.005	327.3°C

Ceramic Reference Materials (Finely divided material - units of 100g). These samples have been prepared jointly by Ceram Research Limited (now Lucideon) and BAS.

BCS-RM No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	BaO	Mn ₂ O ₃	SnO ₂	SrO	SO ₃	ZrO ₂ +HfO ₂	L.O.I.
201a	Nepheline Syenite	57.3	23.54	0.05	0.12	1.07	0.025	7.53	8.90	0.025	0.37	0.007	...	0.43	...	...	0.76
202a	Plaster (Gypsum)	1.38	0.33	0.03	0.10	37.4	0.39	<0.03	0.10	<0.01	...	...	...	0.33	53	...	7.0
203a	Talc	59.7	0.30	<0.01	0.22	0.25	32.08	0.02	0.005	0.13	...	...	...	...	...	...	6.78
204a	Zircon	37.6	0.74	2.22	0.18	0.15	0.012	0.014	0.017	0.77	...	...	1.69	...	...	53.8	0.50
205a	Borax Frit	52.16	5.38	0.04	0.15	12.58	0.62	8.53	1.04	...	0.03	...	...	0.01	...	...	0.24

Ceramic Reference Materials (continued)

BCS-RM No.	Description	B ₂ O ₃	ZrO ₂	PbO	ZnO	Li ₂ O
205a	Borax Frit (cont.)	18.46	0.34	0.05	0.16	<0.01

Benzoic Acid Reference Materials (BCS-RM 190t supplied in units of 100 x 0.2g tablets; BCS-RM 190v supplied in units of 100g of crystals or 100 x 1.0g tablets)

BCS-RM No.	Description	
190t	Benzoic Acid	Purity 100.0±0.05%, Calorific Value, 26,439.7±12.2 joules per gramme based on mass (Certified by Pattinson and Stead, Middlesbrough, UK)
190v	Benzoic Acid	Purity 100.0±0.06%, Calorific Value, 26,443.2±6.6 joules per gramme based on mass (Certified by Pattinson and Stead, Middlesbrough, UK)

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Unalloyed Steels

The figures are listed primarily as a guide to purchasers. In some cases provisional figures are given which may differ slightly from those given on the Certificate. **Always consult the Certificate issued with the sample to obtain the accurate analysis.**

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Plain Carbon Steels (Wrought) (SS-CRM: 38mm dia. x 19mm discs ECRM: 38mm dia. x 30 or 25mm discs except 056-2(D): 44mm dia. x 30 or 25mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	As	Co	Cu	N	Nb	Pb	Sn	V	W	Sb	Others
SS-CRM 431/2	Plain Carbon Steels	0.0249	0.015	0.902	0.121	0.0065	0.049	0.004	0.040	...	...	0.005	0.006	0.015	0.0052	0.0040	...	<0.001	0.003	0.004	...	...
SS-CRM 432/2		0.0065	0.0822	0.712	0.0171	0.036	0.0166	0.002	0.0196	...	<0.002	...	0.006	0.015	0.0066	0.0174	...	...	<0.001	0.003	...	...
SS-CRM 433/2		0.096	0.0071	1.188	0.011	0.0083	0.0262	0.004	0.037	...	...	...	0.006	0.025	...	0.0590	...	...	0.001	0.003	...	...
SS-CRM 434/1		0.41	0.31	1.49	0.050	0.027	0.055	...	0.044	...	...	...	...	...	...	0.078	...	...	...	...	...	...
SS-CRM 434/2		0.275	0.510	1.546	0.0611	0.0141	0.238	0.014	0.037	...	...	...	0.006	0.025	0.0104	0.038	...	...	0.04	0.04	...	...
SS-CRM 435/2		0.489	0.328	0.390	0.0373	0.0424	0.184	0.018	0.133	...	...	...	0.0116	0.05	...	0.134	...	...	0.005	0.015	...	...
ECRM 055-2(D)	0.5% Carbon Steel	0.5199	0.3094	0.687	0.0102	0.0205	0.3127	0.0960	0.3121	...	<0.01	0.0187	0.0257	0.2089	0.01069	<0.0002	<0.001	0.0162	0.00245	0.0166	0.00376	<0.005 Ca
ECRM 056-2(D)	0.8% Carbon Steel	0.8181	0.2006	0.5073	0.0103	0.0093	0.0146	0.0015	0.0218	0.00024	<0.001	...	0.0035	0.0129	0.0045	...	...	...	...	...	...	...
ECRM 057-2(D)	0.05% Carbon Steel	0.0507	0.003	0.246	0.0120	0.0127	0.0114	...	0.0096	0.055	0.059	...	...	0.0146	0.0023	...	...	...	...	...	...	...
ECRM 058-2(D)	0.15% Sulphur Steel	0.424	0.1080	1.186*	0.0098	0.1712*	0.1211	0.0589	0.199	...	...	0.0095	...	0.261	0.0107	...	...	...	...	...	...	...
ECRM 059-2(D)	0.7% Carbon Steel	0.721	0.188	0.495	0.0046	0.0084	0.0090	0.0018	0.0198	0.00020	0.00045	...	...	0.0074	0.0051	...	...	...	...	...	...	...
ECRM 064-2(D)	Nb/Ti Interstitial Free Steel	0.0026	0.0065	0.1641	0.011	0.012	0.024	0.00077	0.0115	...	0.05	0.0036	0.0027	0.0077	0.0026	0.0146	0.00018	0.00051	0.00015	0.0002	...	...
ECRM 084-1(D)	0.4% Carbon Steel	0.391	0.265	0.860	0.018	0.029	...	0.033	0.154	...	...	...	...	0.267	...	...	...	0.023	...	...	...	...
ECRM 085-1(D)	0.3% Sulphur Steel	0.067	0.008	0.977*	0.062	0.336*	...	...	...	...	...	...	0.019	0.291	...	...	0.0010	...	0.0021	...	0.0073	0.0025 Zn
ECRM 086-1(D)	0.3% Carbon Steel	0.297	0.206	0.879	0.0238	0.0371	0.150	...	0.168	...	...	0.0230	...	0.320	...	...	...	0.0263	...	...	...	...
ECRM 087-1(D)	0.15% Carbon Steel	0.1740	0.2631	0.6711	0.0103	0.0461	0.0781	0.0206	0.1177	...	...	0.0243	0.0148	0.1707	...	...	...	0.0171	...	...	0.0046	...

*The metallurgical conditions of **ECRMs 058-2(D)** and **085-1(D)** render them unsuitable for the determination of Mn and S by Optical Emission Spectrometry.

Plain Carbon Steels (Wrought) (continued)

Ref No.	Description	Bi	Cd	Ga	Hg	Se	Te	Ti	Zn
ECRM 055-2(D)	0.5% Carbon Steel (cont.)	<0.005	...	...	...	...	...	0.00104	0.0011
ECRM 090-1(D)	1% Carbon Steel (cont.)	<0.00002	<0.00002	0.00228	<0.00001	<0.0002	<0.0002	<0.0001	0.00209

Carbon Steels Residual Series (Wrought) (38mm dia. x 19mm discs, except 456/3 which is 44mm dia.)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	Cu	Pb	Sn	Ti	W	Sb
SS-CRM 452/1	Carbon Steel Residual	0.323	0.055	1.30	0.035	0.017	0.067	0.054	0.19	...	0.015	0.22	0.0002	0.094	0.031	0.054	...

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	B	Co	Nb	Pb	V	Zr	Sb
SS-CRM 456/3	Carbon Steel Residual Series	0.1215	0.267	0.2121	0.0228	0.0246	0.0257	0.0014	0.0174	...	0.0393	0.0014	0.0520	0.0113	0.0153	0.0214	...	0.0222
SS-CRM 457/2		0.307	0.105	0.327	0.0098	0.0448	...	...	...	0.082	0.087	0.0046	0.0217	0.0174	0.0098	0.153	0.025	0.050
SS-CRM 458/2		0.198	0.504	0.479	0.0281	0.0314	...	...	...	0.052	0.055	0.0069	0.198	0.0510	0.0140	0.105	0.062	0.089
SS-CRM 459/2		0.467	0.640	0.909	0.0482	0.0481	...	...	...	0.0134	0.0154	0.0110	0.0890	0.0102	0.0044	0.0585	0.074	0.0121
SS-CRM 460/2		0.383	0.126	0.616	0.0374	0.0099	...	...	...	0.0193	0.0240	0.0027	0.0106	0.068	0.0005	0.0322	<0.0005	0.0006

Many of the above samples are also available in the finely divided form - see pages 7 and 8.

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - High Purity Iron, Unalloyed and Low Alloy Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

High Purity Iron (Wrought) (38mm dia. x 30 or 25mm discs)

ECRM No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	N	Nb
097-2(D)	High Purity Iron	<i><0.002</i>	0.00285	0.0120	0.00538	0.00181	0.0213	0.00370	0.0241	<i><0.002</i>	0.00281	0.00012	0.0139	0.00793	0.00294	<i>0.0011</i>

ECRM No.	Description	Pb	Sn	Ti	V	W	Zr	Bi	Ca	Ga	Mg	O	Sb	Ta	Zn
097-2(D)	High Purity Iron (cont.)	<i><0.001</i>	0.00043	<i>0.0008</i>	0.00011	0.00386	<i><0.002</i>	<i><0.0002</i>	<i><0.001</i>	<i>0.0003</i>	<i><0.0005</i>	<i>0.005</i>	0.00012	0.00015	0.00014

ECRM 097-2(D) also has the additional information: Ag: *<0.0001%*, Al(sol.): *<0.0004% & 0.0010%*, Cd: *<0.0001%*, Ge: *0.00043% & 0.00066%*, Se: *<0.0001%*, Te: *<0.0001%*.

Low Alloy Steels (Wrought) (SS-CRM 111/1-116: 44mm dia. x 19mm discs. SS-CRM 214/2: 42mm dia. x 19mm discs. Other SS-CRM: 38mm dia. x 19mm discs. ECRM: 38mm dia. x 30 or 25mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Zr	Ca	Zn
SS-CRM 111/1	Low Carbon Steel	0.0070	0.0039	0.1623	0.0045	0.0049	0.0055	0.0005	0.0161	<i><0.002</i>	0.0011	...	0.0053	0.0089	0.0025	...	...	0.0006	0.0004	0.0002	...	...	...	...
SS-CRM 112	Low Alloy Steels	0.394	0.289	0.436	0.0043	0.0026	1.236	0.190	1.461	0.0148	0.0021	0.0007	0.0175	0.149	0.0024	0.0065	<i><0.001</i>	0.0086	0.0100	0.0088	...	<i><0.001</i>	<i><0.0005</i>	...
SS-CRM 113		0.837	0.931	1.207	0.0595	0.0294	1.248	0.056	0.0784	0.0151	0.0020	0.0066	0.0415	0.179	0.0109	0.0487	<i><0.001</i>	0.0067	0.0390	0.201	0.012	0.0029	<i><0.001</i>	...
SS-CRM 114		0.403	0.295	0.416	0.0044	0.0046	0.187	0.184	1.502	0.078	0.0025	0.0008	0.0171	0.360	0.0043	0.0042	<i><0.001</i>	0.041	0.0096	0.0086	<i><0.001</i>	0.0051	<i><0.001</i>	...
SS-CRM 115	Calcium Treated Steels	0.6224	0.2078	0.682	0.0123	0.00093	0.0198	<i>0.003</i>	0.0196	0.0527	...	<i><0.0001</i>	<i>0.006</i>	<i>0.009</i>	0.0067	...	<i>0.0002</i>	<i>0.002</i>	0.0027	<i>0.001</i>	...	...	0.0058	<i>0.0006</i>
SS-CRM 116		0.617	0.201	0.6756	0.0092	0.00176	0.0141	<i><0.001</i>	0.0155	0.0587	...	...	...	<i>0.014</i>	0.0069	...	0.00012	<i>0.005</i>	0.00171	...	...	...	0.0036	...
SS-CRM 117	Nb/Ti Interstitial Free Steel	0.0015	0.00286	0.1139	0.0093	0.0061	0.0196	0.00207	0.0196	0.0283	0.00175	...	0.0065	0.0150	0.00148	0.0186	0.000069	0.00152	0.0174	0.00104				
SS-CRM 214/2	Mn-Mo Steel	0.39	0.18	1.61	0.032	0.043	0.09	0.26	0.15	...	...	...	...	0.21	...	...	...	...	...	<i><0.01</i>	...	...	...	...
SS-CRM 219/4	Ni-Cr-Mo Steel	0.314	0.079	0.81	0.011	0.027	0.66	0.58	2.55	<i>0.003</i>	...	...	...	0.088	...	...	...	0.011	...	...	...	...	...	...
SS-CRM 222/1	3.5% Ni Steel	0.3095	0.227	0.618	0.0175	0.0089	0.0535	0.0287	3.536	...	...	<i><0.005</i>	0.0379	0.150	0.0100	...	...	...	...	<i>0.020</i>	...	...	...	...
SS-CRM 225/2	Ni-Cr-Mo Steel	0.40	0.23	0.56	0.019	0.012	1.08	0.34	1.43	<i>0.009</i>	<i>0.035</i>	<i>0.0007</i>	<i>0.018</i>	<i>0.17</i>	<i>0.012</i>	<i>0.003</i>	...	<i>0.017</i>	...	<i><0.01</i>	...	<i><0.01</i>	...	...
SS-CRM 405/1	Low Alloy Steels	0.032	1.71	1.28	0.018	0.069	0.15	0.002	0.22	...	...	...	...	0.013	...	...	...	...	...	0.28	...	...	...	...
SS-CRM 409/1		0.082	1.46	0.44	0.025	0.021	0.94	0.65	3.06	...	...	...	0.014	0.048	...	...	...	...	...	0.09	...	...	...	...
SS-CRM 401/2	Low Alloy Steels	0.935	0.602	1.197	0.0265	0.0078	0.138	0.495	0.019	0.074	...	...	0.0042	0.101	0.0159	...	...	...	...	0.496	...	...	...	...
SS-CRM 402/2		1.311	0.111	0.228	0.0161	0.0138	0.652	0.140	0.808	0.161	...	...	...	0.302	0.0069	...	...	...	...	0.194	...	...	...	...
SS-CRM 403/2		0.750	0.209	1.677	0.055	0.0381	0.463	0.088	0.223	0.0485	...	...	...	0.221	<i>0.010</i>	...	...	...	...	0.341	...	...	...	...
SS-CRM 404/2		0.696	1.121	0.532	0.0479	0.0228	0.774	0.307	0.393	0.017	...	...	...	0.427	0.0089	...	...	...	...	0.107	...	...	...	...
SS-CRM 407/2		0.490	0.66	0.195	0.038	0.0105	3.03	0.83	0.527	0.040	...	...	0.0068	0.397	<i>0.011</i>	...	...	...	...	0.19	...	...	...	...
SS-CRM 421	Low Tungsten Steels	<i>0.049</i>	<i>0.07</i>	<i>0.11</i>	<i>0.012</i>	<i>0.027</i>	...	<i>0.028</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	0.52	...	...	...
SS-CRM 422		<i>0.036</i>	<i>0.06</i>	<i>0.09</i>	<i>0.015</i>	<i>0.025</i>	...	<i>0.033</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	1.28	...	...	...
SS-CRM 423		<i>0.030</i>	<i>0.05</i>	<i>0.07</i>	<i>0.017</i>	<i>0.027</i>	...	<i>0.027</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	2.06	...	...	...
SS-CRM 424		<i>0.024</i>	<i>0.05</i>	<i>0.09</i>	<i>0.02</i>	<i>0.024</i>	...	<i>0.036</i>	...	...	...	...	...	...	...	...	...	...	...	<i><0.02</i>	3.02	...	...	...
ECRM 186-1(D)	Silico-Manganese Steel	0.6104	1.719	0.870	0.0223	0.0354	0.218	0.0482	0.190	0.0143	...	...	...	0.281	...	...	...	...	...	...	...	...	...	...
ECRM 195-1(D)	Cr-Mo-Ni Steel	<i>0.73</i>	0.466	0.571	0.0160	0.0121	1.566	0.768	0.327	...	...	...	...	0.0355	0.0100	...	0.0010	<i>0.002</i>	...	0.312	...	...	0.0017	0.0046

Most of these samples are also available in the finely divided form - see page 7 and 9

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels and Plain Carbon and Low Alloy Cast Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steels (Wrought) (38mm dia. x 30 or 25mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	Zr	Sb	Fe	Others
ECRM 272-1(D)	12% Chromium Steel	0.2815	0.420	0.600	0.0156	0.0197	11.927	0.0030	0.244	0.0046	0.0116	0.0018	0.0145	0.0192	0.0508	0.0028	0.0004	0.0008	0.00096	0.0167	...	0.00070	...	0.00090 Ca 0.0031 Zn
ECRM 276-2(D)	5% Cr-Mo-V Steel	0.399	1.034	0.365	0.0093	0.0189	4.975	1.134	0.203	...	...	...	...	0.183	0.0116	...	...	0.0133	...	0.296	...	...	...	...
ECRM 285-2(D)	Maraging Steel	0.0018	0.0117	0.0168	0.0053	0.0025	0.0236	4.99	18.07	0.1067	...	0.0009	7.76	0.0094	0.0007	...	...	0.0011	0.520	...	0.0050	...	...	...
ECRM 287-1(D)	High B Stainless Steel	0.0164	0.569	1.478	0.0267	0.0014	18.61	0.247	10.35	...	...	0.924	0.148	0.203	0.0194	...	...	...	...	...	...	...	...	...
ECRM 292-1(D)	Nb-Stabilised Stainless Steel	0.0367	0.402	1.744	0.0175	0.0055	18.00	0.0464	10.09	0.002	0.008	0.0003	0.0255	0.0391	0.0640	0.571	...	...	...	...	...	...	...	{ 0.001 Ta 0.0006 Ca
ECRM 295-1(D)	4% Mo-Cr-Ni Steel	0.0166	0.418	1.758	0.0167	0.0003	19.51	3.996	24.40	0.0203	0.0041	0.0018	0.0450	1.481	0.0615	...	...	0.0025	...	0.0456	...	0.0007	48.36	0.0003 Mg
ECRM 296-1(D)	Jethete Steel	0.1166	0.242	0.676	0.0178	0.0026	11.82	1.700	2.790	0.0275	0.0139	0.0003	0.0218	0.1498	0.0214	...	0.00016	0.0131	...	0.363	...	...	...	...

These samples are also available in the finely divided form - see page 10

Austenitic Stainless Steels (Wrought) (38mm dia. x 19mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Pb	Sn	Ti	V	W	Ta	Others
SS-CRM 461/1	Austenitic Stainless Steels	0.0103	0.374	0.686	0.0053	0.0051	14.727	0.0138	6.124	0.002	0.004	...	0.004	0.0091	...	...	0.0005	...	...	...	...	...	...
SS-CRM 462/1		0.0345	0.463	0.722	0.0053	0.0041	11.888	0.0304	12.85	...	...	...	...	0.0112	...	...	...	...	...	...	...	...	...
SS-CRM 463/1		0.019	0.270	1.400	0.025	0.019	18.46	0.265	10.20	...	...	0.0022	0.116	0.276	0.063	...	...	...	<0.005	0.04	...	...	...
SS-CRM 464/1		0.086	0.57	0.791	0.020	0.028	25.39	...	20.05	...	0.003	...	0.054	...	...	...	0.0004	...	...	...	...	...	...
SS-CRM 465/1		0.066	0.405	1.380	0.021	0.012	17.31	0.092	9.24	0.026	...	0.0006	0.053	0.098	0.010	...	<0.001	...	0.40	0.102	...	...	...
SS-CRM 466/2		0.0141	0.480	1.311	0.0105	0.0069	17.84	2.776	10.20	0.002	0.0020	0.0039	0.0184	0.0278	0.0508	0.001	<0.0001	<0.001	0.002	0.0346	...	...	...
SS-CRM 467/1		0.082	0.52	0.788	0.018	0.019	18.09	...	9.21	...	0.004	...	...	...	...	0.99	0.004	...	...	...	...	0.0017	...
SS-CRM 468/1		0.143	1.41	1.70	0.014	0.020	17.96	...	8.90	...	...	...	0.018	...	...	...	...	...	...	...	...	...	...
SS-CRM 475	Stainless Steel	0.050	0.21	0.89	0.037	0.008	14.14	1.59	5.66	0.013	...	...	0.22	1.94	...	0.22	...	0.015	...	...	...	...	...
SS-CRM 476	Mo Stabilised Stainless Steel	0.0171	0.323	1.755	0.0302	0.0234	16.88	2.049	10.17	<0.005	0.0053	...	0.1628	0.3026	0.0794	0.0107	<0.002	0.0059	<0.005	0.0663	0.0419	<0.001	0.0028 Ca <0.003 Zr
SS-CRM 477	4% Mo-Cr-Ni Steel	0.0102	0.473	1.623	0.0209	0.00039	20.38	4.23	25.07	0.0303	0.00399	0.00198	0.0875	1.340	0.0562	...	...	0.00453	...	0.0527	...	...	0.00053 Mg 0.00078 Sb
SS-CRM 479	Niobium Stabilised Stainless Steel	0.0529	0.553	0.680	0.0029	0.0030	19.922	0.003	24.87	0.013	0.002	<0.0005	0.002	0.0052	0.0057	0.625	<0.001	<0.002	0.0306	0.0052	...	<0.005	...

These samples are also available in the finely divided form - see page 10

Plain Carbon Cast Steels (SS-CRM 601/3 – 38mm dia. x 19mm disc, SS-CRM 602/2-605/2 - 44mm dia. x 19mm discs)

Ref No.	Description	C	Si	Mn	P	S	Al (Total)	Al (Acid Sol.)	Cr	Mo	Ni	Co	Cu	V	Zr
SS-CRM 601/3	Low Alloy Cast Steels	0.197	0.323	1.248	0.0292	0.0279	0.0600	...	...	...	...	...	...	...	...
SS-CRM 602/2		0.94	0.057	0.66	0.023	0.031	0.096	0.094	0.03	0.004	0.02	0.007	0.06	0.001	<0.005
SS-CRM 603/2		0.79	0.97	0.236	0.020	0.056	0.076	0.075	0.04	0.004	0.03	0.01	0.05	0.001	<0.005
SS-CRM 604/2		0.199	0.75	1.91	0.016	0.072	0.008	0.005	0.06	0.02	0.09	0.01	0.07	0.001	<0.005
SS-CRM 605/2		0.400	0.54	0.345	0.054	0.015	0.027	0.026	0.06	0.01	0.05	0.008	0.06	0.001	0.12

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Highly Alloyed Steels

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ferritic Stainless Steels (Wrought) (SS-CRM 469-473: 38mm dia. x 19mm discs)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	V
SS-CRM 469	Ferritic Stainless Steels	0.279	0.421	0.598	0.015	0.020	11.93	...	0.246	<i>0.01</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 470		0.153	0.335	0.235	0.024	0.035	17.68	...	0.369	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 471		0.095	0.326	0.417	0.018	0.023	23.85	...	0.96	<i>0.02</i>	<i>0.02</i>	<i>0.03</i>
SS-CRM 472		0.227	1.05	1.02	0.032	0.029	15.82	0.661	1.95	<i>0.02</i>	<i>0.02</i>	<i>0.02</i>
SS-CRM 473		0.172	0.604	0.494	0.019	0.030	9.06	0.95	<i>0.06</i>	<i>0.01</i>	<i>0.03</i>	<i>0.02</i>

Samples 469 to 473 are also available in the finely divided form - see page 10

High-Speed Steels (Wrought) (38mm dia. x 19mm discs)

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	Co	Sn	V	W
SS-CRM 483/1	High-Speed Steels	0.650	0.16	0.22	0.023	0.023	2.90	0.18	<i>0.08</i>	...	...	2.06	...	0.22	9.28
SS-CRM 485/1		0.94	0.30	0.41	0.043	0.039	4.02	0.66	<i>0.14</i>	<i>0.006</i>	<i>0.022</i>	4.97	0.019	1.02	17.79
SS-CRM 486/1		0.74	0.27	0.21	0.029	0.021	4.54	5.20	<i>0.06</i>	<i><0.005</i>	<i>0.016</i>	0.08	0.014	1.82	5.80
SS-CRM 487/1		1.02	0.18	0.26	0.022	0.029	3.91	9.41	<i>0.14</i>	0.006	<i>0.012</i>	7.95	<i>0.006</i>	1.14	1.80

High Manganese Steels (Cast) (48mm x 42mm x 12mm blocks). These samples have been prepared jointly by Replicast Ltd./Castings Technology International (formerly BCIRA) and BAS.

Ref Nos.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	Co	Cu	N	V	As	Ti
SS-CRM 492/3	High Manganese Steels	1.18	0.299	8.33	0.0318	0.0093	1.076	1.318	4.17	0.131	0.0048	0.0211	0.0225	<i>0.004</i>	<i>0.002</i>	0.0024
SS-CRM 493/3		0.819	0.861	11.15	0.12	0.009	0.259	1.04	3.24	0.035	...	0.017	0.025	0.025	...	...

SPECTROSCOPIC STANDARD CERTIFIED REFERENCE MATERIALS - Cast Irons and Nickel Base Alloys

CHEMICAL COMPOSITION - Figures in bold type certified, figures in small italic type only approximate.

Cast Irons (The material for these SCRM's were prepared using a special method of casting devised by the former British Cast Iron Research Association (BCIRA). All are 48mm x 42mm x 12mm chill cast blocks except SCRM 675 which is a 40mm x 37mm x 10mm chill cast block. Nominal mass content in %)

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	Sn	Ti	V	Ce	Mg	Zn
SCRM 656/9	Low Phosphorus Engineering Irons	2.537	2.504	0.820	0.060	0.108	0.03	...	0.03	...	...	...	...	...	...	...	...	...	...
SCRM 657/9		3.157	3.209	0.112	0.101	0.0401	...	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 658/13		3.106	1.973	0.563	0.259	0.0547	...	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 659/9		4.174	1.361	1.010	0.0215	0.0372	...	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 660/11		3.621	1.747	0.444	0.137	0.115	...	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 661/4	High Phosphorus Engineering Irons	2.56	2.96	0.30	0.84	0.068	1	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 662/4		2.95	2.33	0.76	0.30	0.087	1	...	...	...	...	...	...	...	...	...	...	...	...
SCRM 666/12	Ductile (Nodular) Irons	3.599	1.763	0.106	...	...	0.102	0.0979	1.709	...	...	...	0.0581	...	0.1069	0.0486	0.006	0.0838	...
SCRM 667/13		3.04	2.866	0.222	...	...	0.294	0.006	1.303	...	...	...	0.497	...	0.007	0.103	0.110	0.070	...
SCRM 668/14		3.772	1.729	0.702	0.0454	0.0220	0.998	0.0179	0.096	...	...	...	0.658	...	0.086	0.195	0.0230	0.0097	...
SCRM 669/15		3.093	2.410	0.522	0.0410	0.0108	0.260	0.0570	0.481	...	...	...	0.217	...	0.0584	0.504	0.0402	0.0229	...
SCRM 670/25		3.178	2.152	0.324	0.0466	0.0085	0.488	0.0110	0.965	...	...	...	0.978	...	0.0820	0.0125	0.0092	0.0414	...
SCRM 671/1	Blast Furnace Irons	3.165	0.868	0.811	0.108	0.0503	0.0609	0.0259	0.0627	0.030	...	0.098	...	0.0103	0.0407	0.0122	...	...	<0.002
SCRM 673/1		2.455	1.702	0.123	0.317	0.0112	0.0423	0.0092	0.103	0.0287	...	0.053	...	0.0206	0.0718	0.052	...	...	<0.001
SCRM 674/1		3.71	0.484	1.437	0.0180	0.078	0.0296	0.0497	0.161	0.0061	...	0.0066	...	0.0164	0.0131	0.0125	...	...	...
SCRM 675		1.916	1.300	1.798	0.0453	0.0724	0.0794	0.0342	0.205	0.0072	0.0342	0.0230	0.0117	0.0062	0.0070	0.179	...	...	0.0006

Nickel Base Alloys (All at 13mm thickness except 363/1 which is 19mm thickness)

MAJOR ELEMENTS - nominal mass content in %

Ref. No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Nb	Ti	V	W	Zr	Fe
SS-CRM 345	IN 100 Alloy (cast) (35mm dia.)	0.153	...	...	...	...	9.95	3.01	Bal.	5.58	0.019	14.71	...	...	...	5	1.00	...	0.044	...
SS-CRM 346A	IN 100 Alloy (cast) (38mm dia.)	0.15	...	...	...	...	10	3	60	5.5	...	15	...	...	...	5	1	...	...	...
SS-CRM 350	IN 713 Alloy (cast) (50mm dia.)	0.138	0.110	0.019	...	...	13.43	4.29	70.8	5.97	0.013	0.338	...	...	2.17	0.87	...	0.094	0.072	1.50
SS-CRM 351	IN 718 Alloy (wrought) (41mm dia.)	0.025	0.14	0.037	0.006	0.0006	18.12	3.06	53.1	0.55	0.0051	0.136	0.016	...	5.20	1.06	...	...	...	18.26
SS-CRM 351/1	IN 718 Alloy (wrought) (44mm dia.)	0.0255	0.080	0.0562	0.0045	0.00037	19.14	3.04	53.35	0.554	0.0035	0.145	0.0222	0.0077	5.31	0.938	0.0181	0.0209	0.0017	17.20
SS-CRM 363/1	Monel Alloy 400 (wrought) (38mm dia.)	0.140	0.028	1.26	...	0.002	0.05	...	64.7	0.027	...	0.032	31.90	...	...	0.03	...	...	...	1.86
SS-CRM 387/1	Nimonic 901 Alloy (wrought) (41mm dia.)	0.033	0.06	0.025	0.0033	0.0028	11.35	5.83	41.2	0.24	0.017	0.020	0.0076	...	0.006	3.00	...	...	...	38.4

Nickel Base Alloys (continued)

TRACE ELEMENTS - nominal mass content in µg/g

Ref. No.	Description	Pb	Bi	Ag	Se	Te	Tl	Sb	Ta	As	Cd	Ga	Sn	Zn	Mg	Ca	In
SS-CRM 345	IN 100 Alloy (cont.)	0.21	<0.2	<0.2	<0.5	<0.2	<0.2	<2	...	2	<0.1	8.2	5.6	<0.5	5.5	<5	...
SS-CRM 346A	IN 100 Alloy (cont.)	22.2	10.3	42.5	5.7	9.3	1.9	45	...	50.4	0.37	49.6	93	28.8	130	22	20
SS-CRM 351/1	IN 718 Alloy (wrought) (cont.)	<1	<1	<1	<1	<1	<1	2.4	33	<10	<0.1	<20	3.3	<10	16	<10	...
SS-CRM 387/1	Nimonic 901 Alloy (cont.)	0.3	<1.0	≤0.2	...	...	...	3	...	...	...	...	...	...	...	...	...

SPECTROSCOPIC REFERENCE MATERIALS - Cast Irons

These samples are intended for the calibration of optical emission and XRF instruments with respect to the alloying and trace elements below. Although they have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

CHEMICAL COMPOSITION (nominal mass content in %)

Cast Iron Reference Materials (The materials for these Cast Iron RMs were prepared using a special method of casting devised by the former British Cast Iron Research Association (BCIRA). All are 40mm x 37mm x 10mm chill cast blocks except LARM 5/1, CRRM 1/2, CRRM 3/2, CRRM 4/2, CRRM 5/2, NIRM 2/2, NIRM 5/1, NIRM 6/1, NIRM 8/2, SIMO 1/6 and SIMO 2/4 which are approximately 48mm x 42mm x 12mm chill cast blocks).

Ref No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	Nb	Pb	Sn	Ti	V	Bi	Ce	Mg
LARM 1	Low Alloy Cast Irons	(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	0.50	0.002	0.49	0.002	...	0.006	...	2.49	...	0.0003	...	0.14	0.11	0.011	0.005	...
LARM 2		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	2.50	0.22	0.030	0.066	0.044	...	...	0.021	...	0.007	0.22	0.33	0.0028	<0.001	0.008	...
LARM 3		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	0.045	0.008	1.80	0.042	0.092	0.003	...	1.20	...	0.0006	...	0.015	0.55	0.022	<0.008	...
LARM 4		(3.0)	(2.0)	(0.3)	(0.05)	(<0.01)	1.19	1.00	0.028	0.014	...	...	...	0.26	...	0.018	0.11	0.17	0.014	<0.001	0.008	...
LARM 5/1		2.98	2.02	0.33	0.049	0.012	...	0.58	2.56	...	...	0.0016	...	...	...	<0.001	0.023	...	0.23	0.0012	...	...
CRRM 1/2	High Chromium Cast Irons	1.70	1.84	1.43	0.16	0.099	11.28	3.06	2.03	0.140	...	...	...	1.97	...	...	...	0.054	0.063	...	...	...
CRRM 2/1		1.92	1.18	1.11	0.097	0.079	14.13	2.44	1.61	0.054	...	...	...	1.59	...	...	...	0.070	0.063	...	...	...
CRRM 3/2		2.37	1.21	0.92	0.073	0.087	18.78	1.58	1.35	0.102	...	...	...	1.09	...	...	...	0.015	0.042	...	...	...
CRRM 4/2		2.93	0.45	0.58	0.049	0.042	21.93	1.15	0.58	<0.005	...	...	...	0.53	...	...	...	0.008	0.11	...	...	...
CRRM 5/2		3.43	0.20	0.30	0.029	0.018	30.35	0.63	0.36	0.15	...	...	...	0.22	...	...	...	0.009	0.11	...	...	...
NCRM 1	Nickel Chromium Cast Irons	3.05	0.95	1.21	0.300	0.156	0.55	1.02	0.57	...	...	...	...	2.17	...	...	...	...	...	...	...	...
NCRM 2		2.97	1.82	0.95	0.068	0.119	1.99	0.36	2.10	...	...	...	...	1.67	...	...	...	...	...	...	...	...
NCRM 3		3.24	0.29	0.67	0.125	0.090	3.95	0.78	3.64	...	...	...	...	1.21	...	...	...	...	...	...	...	...
NCRM 4		2.66	2.13	0.40	0.203	0.012	7.94	0.57	5.34	...	...	...	...	0.68	...	...	...	...	...	...	...	...
NCRM 5		3.70	1.15	0.27	0.025	0.015	10.44	0.10	6.74	...	...	...	...	0.204	...	...	...	...	...	...	...	...
NIRM 1/1	Austenitic (Ni-Resist) Cast Irons	1.83	3.26	6.74	0.058	0.015	0.300	...	11.8	...	...	...	...	0.20	...	...	...	...	...	...	0.022	0.021
NIRM 2/2		2.94	1.43	2.01	0.096	0.007	1.48	...	13.69	...	...	...	...	5.93	...	...	...	...	...	...	0.018	0.044
NIRM 3		2.51	2.21	0.51	0.208	0.096	2.43	...	17.8	...	...	...	...	1.00	0.09	...	...	...	...	...	0.007	...
NIRM 4		1.97	3.03	2.37	0.051	0.008	3.56	...	20.2	...	...	...	...	0.52	0.37	...	...	...	...	...	0.011	0.014
NIRM 5/1		2.95	1.50	1.01	0.103	0.005	0.51	...	21.7	...	...	...	...	0.21	0.15	...	...	...	...	...	0.016	0.055
NIRM 6/1		2.53	2.68	4.07	0.225	0.049	1.02	0.51	26.9	...	...	...	...	0.11	...	...	...	...	...	...	0.006	...
NIRM 8/2		1.45	5.61	1.58	0.105	0.014	2.47	0.77	35.3	...	...	...	...	0.23	...	...	...	...	...	...	0.013	0.033
SIMO 1/6	Silicon Molybdenum	2.50	4.04	0.372	0.036	0.005	0.750	0.727	0.060	0.025	0.001	...	0.025	0.016	...	...	0.053	0.010	0.020	...	...	0.002
SIMO 2/4	Cast Irons	2.26	4.49	0.440	0.026	0.009	0.896	0.443	0.015	0.013	0.002	...	0.005	0.009	...	...	0.056	0.006	0.008	...	0.006	0.002

SPECTROSCOPIC STANDARD REFERENCE MATERIALS - Copper Base Alloys

These samples are intended for the calibration of optical emission and XRF instruments with respect to the alloying and trace elements below. Although they have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

Note that most CURM samples are available in the finely divided (chip) form as well as in disc form

CHEMICAL COMPOSITION (nominal mass content in %)

Copper Base Alloy Reference Materials (Approx. 50mm dia. x 10mm discs, except CURM H30.24 which is approx. 35mm dia. x 10mm)

Ref. No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	S	Mg	Cr	Cd	Co	Ag	Te
CURM 09.01-4	Phosphorus	99.82	<0.001	<0.0005	0.0008	<0.0005	0.151	0.0019	<0.001	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	...	...	...	...	<0.0005	0.011	<0.001
CURM 09.02-4	Deoxidised Coppers	99.90	<0.001	<0.001	<0.001	<0.0005	0.078	0.0042	<0.002	<0.0005	<0.001	<0.0005	<0.0005	<0.0005	...	...	...	...	<0.0005	0.0055	<0.001
CURM 30.05-4	Main Elements in Brasses	69.48	<0.001	<0.002	30.53	<0.0005	...	<0.003	<0.001	<0.0005	<0.001	<0.005	<0.003	<0.001	...	...	...	...	...	...	...
CURM 30.09-4		89.53	<0.001	<0.001	10.45	<0.0003	...	0.0005	<0.001	<0.0003	<0.001	<0.001	<0.001	<0.001	...	...	...	...	...	...	...
CURM 30.11-4		59.86	<0.002	0.005	38.17	1.70	...	0.002	<0.001	0.23	<0.001	<0.001	<0.002	<0.001	...	...	...	...	...	...	...
CURM 30.15-4		60.66	<0.002	<0.005	38.88	<0.001	...	0.50	<0.005	<0.001	<0.005	<0.001	<0.001	<0.001	...	...	...	...	...	...	...
CURM 30.16-4		60.53	<0.002	<0.005	38.33	<0.001	...	1.14	<0.005	<0.001	<0.005	<0.001	<0.001	<0.001	...	...	...	...	...	...	...
CURM 30.18-4		63.66	0.58	<0.005	32.33	<0.001	...	0.006	0.13	<0.001	<0.005	<0.001	<0.001	3.28	...	...	...	...	...	...	...
CURM 30.20-4		61.46	0.40	<0.002	35.71	<0.001	...	<0.005	0.17	<0.001	<0.001	<0.002	<0.002	2.32	...	...	...	...	...	...	...
CURM 30.21-4		56.23	2.01	0.004	40.08	<0.001	...	0.003	0.213	<0.001	<0.001	<0.002	...	1.44	...	...	...	...	...	...	...
CURM H 30.24		58.87	<0.001	3.02	37.92	<0.001	...	0.005	<0.001	<0.001	<0.001	<0.001	<0.001	<0.001	...	...	...	...	...	...	...
CURM 42.21-2	Admiralty & Naval Brasses	66.78	0.60	0.259	31.61	0.120	0.087	0.119	0.15	<0.001	<0.003	0.25	0.013	0.003	0.034	...	...	...	...	...	...
CURM 42.23-2		74.36	1.63	0.575	22.13	0.168	0.128	0.354	0.015	0.019	0.168	0.356	0.034	0.008	0.045	...	...	...	...	...	...
CURM 42.25-2		57.78	2.72	0.0023	39.20	<0.001	0.050	0.003	<0.001	0.169	0.118	<0.001	<0.001	0.021	0.005	...	...	...	...	...	...
CURM 43.01-4	Aluminium Brasses	74.36	0.116	<0.002	22.44	0.121	...	0.008	0.063	0.064	0.118	<0.001	<0.002	2.75	...	...	...	...	...	...	...
CURM 43.02-4		76.21	0.060	0.064	20.82	0.068	...	0.128	0.038	0.035	0.083	<0.001	<0.001	2.40	...	...	...	...	...	...	...
CURM 48.01-1	Cartridge Brasses	66.98	<0.002	0.106	32.6	0.134	0.016	0.049	0.041	<0.001	0.067	0.047	0.038	<0.001	<0.001	0.0008	<0.0005	<0.0003	...	...	...
CURM 48.02-1		67.16	0.035	0.084	32.58	<0.001	0.012	0.053	0.010	0.067	0.025	0.037	0.004	0.013	0.007	<0.0005	0.004	<0.0005	...	...	...
CURM 48.04-1		72.68	0.018	0.043	26.99	0.096	0.006	0.008	0.004	0.012	0.034	0.026	0.014	<0.001	0.011	0.0005	<0.002	<0.0003	...	...	...
CURM 48.05-1		68.69	0.083	<0.003	31.0	0.117	0.007	0.066	0.026	0.016	<0.001	<0.0005	<0.0005	<0.002	0.013	<0.0005	<0.0005	<0.0003	...	...	...
CURM 50.01-5	Leaded Bronzes	75.38	9.01	11.13	0.91	1.93	0.069	0.074	<0.001	<0.001	0.19	0.50	0.024	<0.0005	0.188	...	...	...	...	...	...
CURM 50.02-4		78.84	10.34	10.67	0.006	<0.0005	0.046	<0.001	<0.002	<0.0005	<0.002	<0.0005	<0.0005	<0.001	<0.001	...	...	...	...	...	...
CURM 50.02-5		77.89	10.31	11.28	0.128	0.005	0.041	0.055	0.021	0.003	<0.001	<0.005	<0.0005	<0.001	<0.001	...	...	...	...	...	...
CURM 50.03-4		77.42	8.41	8.86	1.72	2.89	0.159	0.018	0.005	0.037	0.11	0.24	0.051	0.005	0.064	...	...	...	...	...	...
CURM 51.11-4	Aluminium Bronzes	93.95	0.027	0.33	0.111	0.012	0.035	0.060	0.159	<0.001	<0.001	...	...	5.27	...	...	...	...	...	...	...
CURM 51.12-4		88.29	0.196	0.219	0.45	0.112	<0.001	2.87	0.005	1.33	0.111	...	...	6.36	...	...	...	...	...	...	...
CURM 51.13-4		88.79	0.270	0.104	0.335	0.057	0.022	1.81	0.174	0.898	0.215	...	...	7.30	...	...	...	...	...	...	...
CURM 51.14-4		88.57	0.113	0.003	0.656	0.219	0.012	0.72	0.286	0.55	0.44	...	...	8.42	...	...	...	...	...	...	...
CURM 52.54-4		81.59	0.135	0.086	0.39	5.40	...	3.31	0.022	1.20	...	...	...	7.85	...	<0.005	<0.005	...	...	...	...
CURM 54.01-4	Phosphor Bronzes	95.42	3.17	0.307	0.346	0.348	0.053	0.028	0.039	0.158	0.044	0.070	...	0.040	0.023	0.008	...	...	...	...	...
CURM 54.02-4		92.87	5.53	0.663	0.410	0.109	0.107	0.102	0.012	0.101	0.023	0.026	...	0.020	0.030	0.0020	...	...	...	...	...
CURM 62.12-4	Cupro-Nickel	89.42	0.111	0.053	0.180	7.94	...	0.45	0.109	1.59	...	...	...	...	0.034	0.002	...	...	0.081	...	...
CURM 71.33-8	Leaded Gunmetals	83.60	4.96	6.84	3.60	0.938	<0.001	0.018	<0.005	<0.0005	<0.001	<0.002	<0.002	<0.001	<0.001	...	<0.0005	...	...	<0.002	...
CURM 71.34-8		86.74	8.19	2.48	1.54	<0.005	0.019	0.29	0.03	0.05	0.18	0.072	0.031	0.008	0.18	...	0.04	...	...	0.023	...

SPECTROSCOPIC REFERENCE MATERIALS – Lead Base Alloys

These samples are intended for the calibration of optical emission and XRF instruments with respect to the alloying and trace elements below. Although they have been carefully analysed by both BAS Ltd. and an independent laboratory, they have been classified as RMs and not CRMs in order to distinguish them from BAS CRMs which are normally analysed by at least five laboratories.

CHEMICAL COMPOSITION (nominal mass content in %)

Lead Base Alloy Reference Materials (Approx. 50mm x 50mm x 20mm chill cast blocks, also available as finely divided material – units of 100g). These samples have been prepared jointly by Castings Technology International (formerly BCIRA) and BAS

Ref No.	Description	Cu	Sn	Zn	Ni	Cd	As	Sb	Bi	Ca	Ag	Al	Pb
PBRM L21.01-2	Battery Alloys	0.0003	0.11	0.002	<0.0005	0.0003	<0.0005	0.0006	<0.001	0.051	<0.001	0.012	Bal
PBRM L21.02-2		0.002	0.28	0.004	<0.0005	0.0010	0.0003	0.0013	0.013	0.020	0.007	0.004	Bal
PBRM L21.03-2		<0.0005	0.38	0.002	<0.0005	0.003	<0.0005	<0.0005	0.023	0.089	0.010	0.011	Bal
PBRM L21.04-2		0.005	0.47	0.007	<0.0005	0.003	0.0002	0.0003	0.027	0.084	0.017	<0.001	Bal

SETTING-UP SAMPLES FOR DIRECT READING SPECTROGRAPHS

These samples have been thoroughly examined both spectrographically and chemically to confirm the homogeneity of the bulk samples. Their compositions have NOT, however, been accurately determined since it is not intended that they should be used as Spectroscopic Standard CRMs or as RMs. An Information Sheet is supplied with each sample giving the approximate composition.

Carbon, Low Alloy and Stainless Steels (Wrought) (Approx. 44mm dia. x 25 or 75 lengths. G/8a also available in 150mm length)

Ref. No.	Description	Approximate Chemical Compositions (mass content in %)																					
		C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Nb	Sn	Ti	V	W	Zr	Ca	Others
SUS D/11	Low Alloy Steel	0.80	0.80	0.40	0.01	0.03	3.0	1.3	0.10	0.19	...	<0.001	0.29	0.11	0.01	0.05	0.01	0.10	0.12	0.16	...	...	...
SUS G/8a	Stainless Steel	0.02	0.33	1.7	0.03	0.02	16.8	2.1	10.0	0.003	...	...	0.16	0.33	0.08	0.01	0.006	<0.005	0.08	0.04	<0.005	0.003	<0.001 Ta

Cast Irons (Approx. 60mm x 35mm x 18mm chill cast blocks.) The materials for these Cast Iron SUS were prepared using a special method of casting devised by the former British Cast Iron Research Association (BCIRA)

Ref. No.	Description	Approximate Chemical Compositions (mass content in %)																		
		C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Cu	Sn	Ti	V	Bi	Mg	Sb	Ce
SUS 1/20	Low Phosphorus Iron	3.2	2.7	0.45	0.06	0.06	0.48	0.34	0.21	0.02	...	...	0.53	0.05	0.013	0.04	...	...	...	...
SUS 2/50	Medium Phosphorus Iron	3.6	1.8	0.71	0.28	0.10	0.04	0.09	0.48	0.01	...	...	0.41	0.13	0.05	0.54	...	...	...	...
SUS 3/21	High Phosphorus Iron	3.4	2.2	0.90	1.0	0.10	0.25	<0.005	0.01	<0.005	...	...	0.01	<0.005	0.11	0.27	...	...	...	...
SUS 4/29	Ductile (Nodular) Iron	3.2	2.7	0.15	...	0.01	0.10	...	0.10	0.01	<0.005	...	0.78	<0.005	0.06	0.51	...	0.02	<0.005	...
SUS 5/59	Ductile (Nodular) Iron	3.5	1.9	0.66	...	0.008	0.01	...	1.06	0.04	0.002	...	0.006	0.07	0.004	0.46	...	0.10	0.05	0.03
SUS 7/8	Malleable Iron	2.8	0.94	0.29	0.09	0.18	0.07	...	...	0.02	...	0.004	0.21	<0.01	...	0.06	<0.001	...	...	...

NUMERICAL INDEX (Including Certification Dates)

Certificates may be reprinted from time to time to accommodate updated text or statistical treatment. In certain cases, where chemical analyses carried out after issuance of the original certificate lead to additional or revised certified data, the "Date of Latest Certificate" below is stated in bold. If the certificate in your possession is not the current one, we shall gladly supply this to you on request.

BRITISH CHEMICAL STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
BCS-CRM 111	Low Carbon Steel	Mar 14	7
BCS-CRM 111/1	Low Carbon Steel	Jan 18	7
BCS-CRM 112, 113, 114	Low Alloy Steels	Mar 14	9
BCS-CRM 115	Calcium Treated Steel	Jun 16	7
BCS-CRM 116	Calcium Treated Steel	Sep 17	7
BCS-CRM 117	Nb/Ti Interstitial Free Steel	Feb 24	7
BCS-CRM 161/4	0.8% Carbon Steel	Sep 15	7
BCS-CRM 176/3	Manganese Ore	Sep 15	14
BCS-CRM 176/4	Manganese Ore	Sep 15	14
BCS-CRM 177/2	Lead Base White Metal	Aug 12	12
BCS-CRM 178/2	Tin Base White Metal	Aug 12	12
BCS-CRM 179/2	High Tensile Brass	Aug 12	12
BCS-CRM 180/2	Copper-Nickel	Aug 12	12
BCS-CRM 181/3	2.5% Cu Aluminium Alloy	Jun 13	12
BCS-CRM 182/3	11% Si Aluminium Alloy	Aug 15	12
BCS-CRM 183/4	Leaded Gunmetal	Jun 13	12
BCS-CRM 203/6	Low C Ferro-Chromium	Feb 19	11
BCS-CRM 204/6	High C Ferro-Chromium	Sep 17	11
BCS-CRM 206/3 (ECRM 453-1)	High Si and P Cast Iron	May 11	11
BCS-CRM 207/2	Gunmetal	Sep 12	12
BCS-CRM 208/3	High C Ferro-Manganese	Nov 19	11
BCS-CRM 214/2 (ECRM 152-1)	Mn-Mo Steel	Jun 19	9
BCS-CRM 216/3	5% Cu Aluminium Alloy	Oct 12	12
BCS-CRM 219/4 (ECRM 153-1)	Ni-Cr-Mo Steel	Feb 03	9
BCS-CRM 222/1	3.5% Ni Steel	Dec 16	9
BCS-CRM 225/2 (ECRM 155-1)	Ni-Cr-Mo Steel	Dec 10	9
BCS-CRM 231/5	Ferro-Molybdenum	Jan 21	11
BCS-CRM 231/6	Ferro-Molybdenum	Jan 21	11
BCS-CRM 232/2 (ECRM 051-1)	0.1% Sulphur Steel	Oct 10	7
BCS-CRM 236/3 (ECRM 454-1)	Hematite Iron	May 11	11
BCS-CRM 237/2 (ECRM 060-1)	0.1% Carbon Steel	Oct 10	7
BCS-CRM 238/2 (ECRM 061-1)	0.2% Carbon Steel	Oct 10	7
BCS-CRM 241/2 (ECRM 251-1)	High Speed Steel	Nov 10	8
BCS-CRM 242/2 (ECRM 555-1)	Ferro-Tungsten	Jun 11	11
BCS-CRM 262/1	10% Mg Aluminium Alloy	Jul 13	12
BCS-CRM 263/2	5% Mg Aluminium Alloy	Jul 13	12
BCS-CRM 268/1	5% Si Aluminium Alloy	Jul 13	12
BCS-CRM 270 (ECRM 054-1)	0.09% Phosphorus Steel	Nov 10	7
BCS-CRM 290/2 (ECRM 253-1)	13% Manganese Steel	Jun 11	10
BCS-CRM 300/1	6% Zn Aluminium Alloy	Jul 13	12
BCS-CRM 301/1 (ECRM 651-1)	Lincolnshire Iron Ore	Aug 11	14
BCS-CRM 304/1	Copper Aluminium	Dec 08	12
BCS-CRM 305/2	Ferro-Silicon	Sep 20	11

BCS-CRM 307	Ce-Zn-Zr Magnesium Alloy	Apr 13	12
BCS-CRM 308/1	Chrome Ore	Sep 15	13
BCS-CRM 309	Sillimanite	May 12	15
BCS-CRM 310/1	Nimonic 90	Aug 15	13
BCS-CRM 313/2	High Purity Silica	Sep 13	15
BCS-CRM 316	8% Al Magnesium Alloy	Jun 12	12
BCS-CRM 317 (ECRM 151-1)	Low C High Si Steel	Sep 11	9
BCS-CRM 318A	0.01% O Steel	Jul 18	8
BCS-CRM 318B	0.01% O Steel	Jul 18	8
BCS-CRM 319/1	Magnesia	Mar 09	15
BCS-CRM 332	Austenitic Stainless Steel	May 13	10
BCS-CRM 339	Ferritic Stainless Steel	Aug 13	10
BCS-CRM 340	Ferritic Stainless Steel	Aug 13	10
BCS-CRM 341	Ferritic Stainless Steel	Aug 13	10
BCS-CRM 342	Ferritic Stainless Steel	Aug 13	10
BCS-CRM 343	Wrought Aluminium Alloy	Jul 13	12
BCS-CRM 344	70/30 Brass	Jan 16	12
BCS-CRM 345	Nickel Alloy IN100	May 12	13
BCS-CRM 346	Nickel Alloy IN100	Oct 19	13
BCS-CRM 347	Electronic Flowsolder	Aug 15	12
BCS-CRM 348	Ball Clay	Jun 11	15
BCS-CRM 349	3.5% Cu Aluminium	Jan 16	12
BCS-CRM 350	Nickel Alloy IN713	Oct 19	13
BCS-CRM 351/1	Nickel Alloy IN718	May 15	13
BCS-CRM 353	Sulphate Resisting Portland Cement	Oct 11	13
BCS-CRM 354	White Portland Cement	Oct 11	13
BCS-CRM 356	Titanium Alloy	Jan 94	13
BCS-CRM 357	Titanium Alloy	Jan 94	13
BCS-CRM 358	Zirconia	Aug 15	15
BCS-CRM 359	Nitrogen Bearing Silicon Carbide	Oct 18	14
BCS-CRM 360	Sialon Bonded Silicon Carbide	Oct 18	14
BCS-CRM 361	Chromium Metal	May 09	13
BCS-CRM 362	Mine Tailings Sample	Sep 10	15
BCS-CRM 363/1	Monel Alloy 400	Apr 16	13
BCS-CRM 364	Leaded Bronze	Aug 15	12
BCS-CRM 369	Magnesite Chrome	Aug 15	15
BCS-CRM 370	Magnesite Chrome	Aug 15	15
BCS-CRM 371	Commercial Nickel	Aug 15	13
BCS-CRM 374	Phosphor Bronze	Aug 15	12
BCS-CRM 375/1	Soda Feldspar	Nov 04	15
BCS-CRM 376/1	Potash Feldspar	May 09	15
BCS-CRM 377/6	Iron Ore Sinter	Sep 15	14
BCS-CRM 380/1	2% Si Aluminium Alloy	Jan 16	12
BCS-CRM 381	Basic Slag	Oct 12	14
BCS-CRM 383	Alcomax III	Jan 16	11
BCS-CRM 385	Leaded Brass	Oct 14	12
BCS-CRM 387/1	Nimonic 901 Alloy	Apr 16	13

NUMERICAL INDEX (Including Certification Dates)

BCS-CRM 388	Zircon	Aug 15	15
BCS-CRM 389/1	High Purity Magnesia	Jun 13	15
BCS-CRM 390	High Tensile Brass	Oct 14	12
BCS-CRM 392	Fluorspar	May 12	13
BCS-CRM 393 (ECRM 752-1)	Limestone	Dec 10	15
BCS-CRM 394/1	Calcined Bauxite	Sep 15	13
BCS-CRM 395	Bauxite	May 12	13
BCS-CRM 396	Low Silica Magnesite Chrome	Jun 13	15
BCS-CRM 398	Alnico H C	Sep 17	11
BCS-CRM 399	Phosphorus Deoxidised Copper	Jan 16	12
BCS-CRM 408	Low Alloy Steel	Jan 10	9
BCS-CRM 404/1, 405/1	Low Alloy Steels	Dec 09	9
BCS-CRM 401/2	Low Alloy Steel	Feb 19	9
BCS-CRM 402/2, 404/2, 405/2	Low Alloy Steels	Dec 05	9
BCS-CRM 403/2	Low Alloy Steel	Jun 15	9
BCS-CRM 407/1, 409/1	Low Alloy Steels	Dec 09	9
BCS-CRM 407/2, 409/2	Low Alloy Steels	Feb 06	9
BCS-CRM 421-424	Low Tungsten Steels	Jul 16	9
BCS-CRM 431/2-435/2	Plain Carbon Steels	Sep 18	8
BCS-CRM 452/1, 453/1	Carbon Steels - Residual Series (Gp A)	Aug 10	8
BCS-CRM 456/3	Carbon Steel – Residual	Mar 22	8
BCS-CRM 457/2, 458/2, 459/2, 460/2	Carbon Steels - Residual Series (Gp B)	Jun 19	8
BCS-CRM 463	Austenitic Stainless Steel	May 16	10
BCS-CRM 461/1, 462/1	Austenitic Stainless Steels	Jun 19	10
BCS-CRM 463/1-465/1	Austenitic Stainless Steels	Jun 10	10
BCS-CRM 466/2	Austenitic Stainless Steel	Jul 19	10
BCS-CRM 467/1, 468/1	Austenitic Stainless Steels	Jun 10	10
BCS-CRM 469-473	Ferritic Stainless Steels	Sep 10	10
BCS-CRM 474, 475	Stainless Steels	Sep 10	10
BCS-CRM 476	Mo-stabilized Stainless Steel	Jul 19	10
BCS-CRM 477	4% Mo-Cr-Ni Steel	Jul 21	10
BCS-CRM 478	Incoloy 800 Alloy	Feb 21	13
BCS-CRM 479	Nb-stabilized Stainless Steel	May 15	10
BCS-CRM 481-484	High Speed Steels	Sep 17	8
BCS-CRM 491, 494, 495	High Manganese Steels	Nov 16	10
BCS-CRM 495/1	High Manganese Steel	Nov 16	10
BCS-CRM 505	Aluminium-Silicon Alloy	Jun 18	12
BCS-CRM 512	Dolomite	Jul 15	15
BCS-CRM 513	Limestone	Jun 15	15
BCS-CRM 514	Copper Concentrate	Sep 15	14
BCS-CRM 516	Standard Glass Sand	May 09	15
BCS-CRM 517	Brazilian Iron Ore	Dec 09	14
BCS-CRM 520	Zinc Concentrate	Mar 19	14
BCS-CRM 525	Low Iron Float Glass	Jul 17	15
BCS-CRM 526	Soda Ash	Sep 15	16
BCS-CRM 527	Blast Furnace Iron	Sep 15	11
BCS-CRM 528	Standard Glass Sand	Sep 15	15
BCS-CRM 529	Anorthic Feldspar	Jul 19	15
BCS-CRM 531	Low Iron Sand	Oct 15	15
BCS-CRM 532	Swedish Feldspar	Jul 19	15
BCS-CRM 535	High Carbon Iron Powder	Feb 23	11
BCS-CRM 533	Container Glass	Feb 24	16
BCS-CRM 534	Float Glass	Feb 24	16

EURONORM CRMs		Date of Latest Certificate	Page
Ref No.	Description		
ECRM 055-2(C)	0.5% Carbon Steel	Sep 13	7
ECRM 056-2(C)	0.8% Carbon Steel	May 09	7
ECRM 057-2(C)	0.05% Carbon Steel	Mar 99	7
ECRM 058-2(C)	0.15% Sulphur Steel	Aug 02	7
ECRM 059-2(C)	0.7% Carbon Steel	Nov 02	7
ECRM 064-1(C)	Nb/Ti Interstitial Free Steel	Nov 02	7
ECRM 084-1(C)	0.4% Carbon Steel	Feb 00	7
ECRM 085-1(C)	0.3% Sulphur Steel	Feb 03	7
ECRM 086-1(C)	0.3% Carbon Steel	Jan 01	7
ECRM 087-1(C)	0.15% Carbon Steel	Aug 07	7
ECRM 088-2	High Purity Iron	Jan 01	7
ECRM 090-1(C)	1% Carbon Steel	May 00	7
ECRM 091-1	0.5% Carbon Steel	Feb 05	7
ECRM 096-2(C)	Low S, Ca-Treated Steel	Mar 99	7
ECRM 097-2(C)	High Purity Iron	Jan 13	7
ECRM 186-1(C)	Silico Manganese Steel	Jul 08	9
ECRM 195-1(C)	Cr-Mo-Ni Steel	Mar 92	9
ECRM 272-1(C)	12% Chromium Steel	Jul 05	10
ECRM 276-2(C)	5% Cr-Mo-V Steel	Feb 93	10
ECRM 281-1	18/9 Stainless Steel + Ti	Oct 16	10
ECRM 285-2(C)	Maraging Steel	May 97	10
ECRM 287-1(C)	High Boron Stainless Steel	Jul 04	10
ECRM 292-1(C)	Nb Stabilized Stainless Steel	Nov 90	10
ECRM 296-1(C)	Jethete Steel	Mar 97	10
ECRM 376-1	24% Co Magnet Alloy	Nov 90	11
ECRM 451-2	Austenitic Cast Iron	Jan 99	11
ECRM 482-2	Low Alloy Cast Iron	Jan 19	11
ECRM 484-1	Whiteheart Malleable Iron	Mar 14	11
ECRM 486-1	Foundry Iron	Mar 04	11
ECRM 489-1	White Iron	Dec 91	11
ECRM 576-1	Ferro-Niobium	Jul 14	11
ECRM 577-1	Ferro-Vanadium	Jul 14	11
ECRM 579-1	Ferro-Niobium	Jul 14	11
ECRM 583-1	Ferro-Manganese	Mar 16	11
ECRM 584-1	Ferro-Titanium	Mar 16	11
ECRM 587-1	Ferro-Boron	Mar 16	11
ECRM 590-1	Ferro-Tungsten	Mar 91	11
ECRM 676-1	Iron Ore Sinter	Mar 16	14
ECRM 682-2	Iron Ore	Apr 09	14
ECRM 690-1	Haematite Iron Ore	Feb 13	14
ECRM 776-1	Firebrick	Aug 16	15
ECRM 781-1	Silicon Carbide Refractory	Mar 93	14
ECRM 782-1	Dolomite	Jul 96	15
ECRM 783-1	Tungsten Carbide	Jul 05	14
ECRM 879-1	Basic Slag	Aug 16	14
ECRM 884-1	Furnace Dust	Mar 11	14

NUMERICAL INDEX (Including Certification Dates)

SPECTROSCOPIC STANDARD CRMs		Date of Latest Certificate	Page
Ref. No.	Description		
SS-CRM 111/1	Low Carbon Steel	Jan 18	18
SS-CRM 112-114	Low Alloy Steels	Mar 14	18
SS-CRM 115	Calcium Treated Steel	Jun 16	18
SS-CRM 116	Calcium Treated Steel	Sep 17	18
SS-CRM 117	Nb/Ti Interstitial Free Steel	Feb 24	18
SS-CRM 214/2	Mn-Mo Steel	Jun 20	18
SS-CRM 219/4	Ni-Cr-Mo Steel	Apr 14	18
SS-CRM 222/1	3.5% Ni Steel	Dec 16	18
SS-CRM 225/2	Ni-Cr-Mo Steel	Mar 14	18
SS-CRM 345	Nickel Alloy IN100	May 12	21
SS-CRM 346A	Nickel Alloy IN100	Oct 19	21
SS-CRM 350	Nickel Alloy IN713	Oct 19	21
SS-CRM 351	Nickel Alloy IN718	Nov 05	21
SS-CRM 351/1	Nickel Alloy IN718	May 15	21
SS-CRM 363/1	Monel Alloy 400	Apr 16	21
SS-CRM 387/1	Nimonic 901 Alloy	Apr 16	21
SS-CRM 405/1, 409/1	Low Alloy Steels	Dec 09	18
SS-CRM 401/2	Low Alloy Steel	Feb 19	18
SS-CRM 402/2, 404/2	Low Alloy Steels	Dec 05	18
SS-CRM 403/2	Low Alloy Steel	Jun 15	18
SS-CRM 407/2	Low Alloy Steel	Feb 06	18
SS-CRM 421-424	Low Tungsten Steels	Jul 16	18
SS-CRM 431/2-435/2	Plain Carbon Steels	Sep 18	17
SS-CRM 452/1	Carbon Steels - Residual Series (Gp A)	Aug 10	17
SS-CRM 456/3	Carbon Steel Residual	Mar 22	17
SS-CRM 457/2-460/2	Carbon Steels - Residual Series (Gp B)	Jun 19	17
SS-CRM 461/1, 462/1	Austenitic Stainless Steels	Jun 19	19
SS-CRM 463/1-465/1	Austenitic Stainless Steels	Jun 10	19
SS-CRM 466/2	Austenitic Stainless Steel	Jul 19	19
SS-CRM 467/1, 468/1	Austenitic Stainless Steels	Jun 10	19
SS-CRM 469-473	Ferritic Stainless Steels	Sep 10	20
SS-CRM 475	Stainless Steel	Sep 10	19
SS-CRM 476	Mo-stabilized Stainless Steel	Jul 19	19
SS-CRM 477	4% Mo-Cr-Ni Steel	Jul 21	19
SS-CRM 479	Nb-stabilized Stainless Steel	May 15	19
SS-CRM 483/1-487/1 (less 484/1)	High-Speed Steels	Nov 13	20
SS-CRM 492/3, 493/3	High Manganese Steel (Cast)	Jul 15	20
SS-CRM 601/3	Plain Carbon Cast Steel	Feb 23	19
SS-CRM 602/2-605/2	Plain Carbon Cast Steels	Jul 16	19
ECRM 055-2(D)	0.5% Carbon Steel	Sep 13	17
ECRM 056-2(D)	0.8% Carbon Steel	May 09	17
ECRM 057-2(D)	0.05% Carbon Steel	Mar 99	17

ECRM 058-2(D)	0.15% Sulphur Steel	Aug 02	17
ECRM 059-2(D)	0.7% Carbon Steel	Nov 02	17
ECRM 064-2(D)	Nb/Ti Interstitial Free Steel	Jul 13	17
ECRM 084-1(D)	0.4% Carbon Steel	Feb 00	17
ECRM 085-1(D)	0.3% Sulphur Steel	Feb 03	17
ECRM 086-1(D)	0.7% Carbon Steel	Jan 01	17
ECRM 087-1(D)	0.15% Carbon Steel	Aug 07	17
ECRM 090-1(D)	1% Carbon Steel	May 00	17
ECRM 097-2(D)	High Purity Iron	Jan 13	18
ECRM 186-1(D)	Silico Manganese Steel	Jul 08	18
ECRM 195-1(D)	Cr-Mo-Ni Steel	Mar 92	18
ECRM 272-1(D)	12% Chromium Steel	Jul 05	19
ECRM 276-2(D)	5% Cr-Mo-V Steel	Feb 93	19
ECRM 285-2(D)	Maraging Steel	May 97	19
ECRM 287-1(D)	High Boron Stainless Steel	Jul 04	19
ECRM 292-1(D)	Nb-Stabilized Stainless Steel	Nov 90	19
ECRM 295-1(D)	4% Mo-Cr-Ni Steel	Mar 95	19
ECRM 296-1(D)	Jethete Steel	Mar 97	19
SCRM 656/9	Low Phosphorus Engineering Iron	Oct 16	21
SCRM 657/9	Low Phosphorus Engineering Iron	Feb 19	21
SCRM 658/13	Low Phosphorus Engineering Iron	Nov 23	21
SCRM 659/9	Low Phosphorus Engineering Iron	Jun 14	21
SCRM 660/11	Low Phosphorus Engineering Iron	Feb 19	21
SCRM 661/4, 662/4	High Phosphorus Engineering Irons	Oct 17	21
SCRM 666/12	Ductile (Nodular) Iron	Jun 13	21
SCRM 667/13	Ductile (Nodular) Iron	Jan 14	21
SCRM 668/14	Ductile (Nodular) Iron	Jun 20	21
SCRM 669/15	Ductile (Nodular) Iron	Sep 20	21
SCRM 670/25	Ductile (Nodular) Iron	Jun 24	21
SCRM 671/1	Blast Furnace Iron	Sep 16	21
SCRM 673/1	Blast Furnace Iron	Sep 16	21
SCRM 674/1	Blast Furnace Iron	Oct 17	21
SCRM 675	Blast Furnace Iron	Jan 05	21

NUMERICAL INDEX (Including Certification Dates)

REFERENCE MATERIALS & SETTING-UP SAMPLES		Date of Latest Analysis Report or Information Sheet	Page
Ref. No.	Description		
BCS-RM 190t	Benzoic Acid	Aug 04	16
BCS-RM 190v	Benzoic Acid	Jul 14	16
BCS-RM 192j	High Purity Tin (300g blocks)	Jun 18	16
BCS-RM 192j	High Purity Tin (millings)	Jun 18	16
BCS-RM 194e	High Purity Zinc (300g blocks)	Jun 18	16
BCS-RM 195g	High Purity Aluminium (300g blocks)	Jun 18	16
BCS-RM 195g	High Purity Aluminium (millings)	Jun 18	16
BCS-RM 198f	Super Pure Aluminium (100g blocks)	Jun 18	16
BCS-RM 201a	Nepheline Syenite	Jul 18	16
BCS-RM 202a	Plaster (Gypsum)	Jul 18	16
BCS-RM 203a	Talc	Jul 18	16
BCS-RM 204a	Zircon	Jul 18	16
BCS-RM 205a	Borax Frit	Sep 18	16
BCS-RM 210e	High Purity Lead (500g bars)	Jun 18	16
LARM 1-4	Low Alloy Cast Irons	Dec 17	22
LARM 5/1	Low Alloy Cast Iron	Nov 21	22
CRRM 1/2	High Chromium Iron	Oct 20	22
CRRM 2/1	High Chromium Iron	Jul 19	22
CRRM 3/2, 4/2, 5/2	High Chromium Irons	Jul 19	22
NCRM 1-5	Nickel Chromium Irons	Jul 18	22
NIRM 1/1	Austenitic (Ni-Resist) Iron	Feb 22	22
NIRM 2/2	Austenitic (Ni-Resist) Iron	Dec 20	22
NIRM 3, 4	Austenitic (Ni-Resist) Irons	Jun 18	22
NIRM 5/1	Austenitic (Ni-Resist) Iron	Aug 19	22
NIRM 6/1	Austenitic (Ni-Resist) Iron	Aug 19	22
NIRM 8/2	Austenitic (Ni-Resist) Iron	Aug 19	22
PBRM L21.01-2 - L21.04-2	Lead Base Battery Alloys	Mar 18	24
SIMO 1/6	Silicon Molybdenum Cast Iron	Mar 23	22
SIMO 2/4	Silicon Molybdenum Cast Iron	Jan 24	22
SUS D/11	Low Alloy Steel	Aug 97	24
SUS G/8a	Stainless Steel	Mar 21	24
SUS 1/20	Low Phosphorus Iron	Dec 20	24
SUS 2/50	Medium Phosphorus Iron	May 22	24
SUS 3/21	High Phosphorus Iron	Oct 14	24
SUS 4/29	Ductile (Nodular) Iron	Mar 22	24
SUS 5/59	Ductile (Nodular) Iron	Jan 23	24
SUS 7/8	Malleable Iron	May 95	24

SPECTROSCOPIC REFERENCE MATERIALS		Date of Latest Analysis Report	Page
Ref. No.	Description		
CURM 09.01-4	Phosphorus Deoxidised Copper	Feb 21	23
CURM 09.02-4	Phosphorus Deoxidised Copper	Feb 21	23
CURM 30.05-4	Main Elements in Brass	Feb 21	23
CURM 30.09-4	Main Elements in Brass	Feb 21	23
CURM 30.11-4	Main Elements in Brass	Feb 21	23
CURM 30.15-4	Main Elements in Brass	Feb 21	23
CURM 30.16-4	Main Elements in Brass	Feb 21	23
CURM 30.18-4	Main Elements in Brass	Feb 21	23
CURM 30.20-4	Main Elements in Brass	Feb 21	23
CURM 30.21-4	Main Elements in Brass	Feb 21	23
CURM H 30.24	Main Elements in Brass	Feb 21	23
CURM 42.21-2	Admiralty & Naval Brass	Feb 21	23
CURM 42.23-2	Admiralty & Naval Brass	Feb 21	23
CURM 42.25-2	Admiralty & Naval Brass	Feb 21	23
CURM 43.01-4	Aluminium Brass	Feb 21	23
CURM 43.02-4	Aluminium Brass	Feb 21	23
CURM 48.01-1	Cartridge Brass	Feb 21	23
CURM 48.02-1	Cartridge Brass	Feb 21	23
CURM 48.04-1	Cartridge Brass	Feb 21	23
CURM 48.05-1	Cartridge Brass	Feb 21	23
CURM 50.01-5	Leaded Bronze	Feb 21	23
CURM 50.02-4	Leaded Bronze	Feb 21	23
CURM 50.02-5	Leaded Bronze	Feb 21	23
CURM 50.03-4	Leaded Bronze	Feb 21	23
CURM 51.11-4	Aluminium Bronze	Feb 21	23
CURM 51.12-4	Aluminium Bronze	Feb 21	23
CURM 51.13-4	Aluminium Bronze	Feb 21	23
CURM 51.14-4	Aluminium Bronze	Feb 21	23
CURM 52.54-4	Aluminium Bronze	Feb 21	23
CURM 54.01-4	Phosphor Bronze	Feb 21	23
CURM 54.02-4	Phosphor Bronze	Feb 21	23
CURM 62.12-4	Cupro-Nickel	Feb 21	23
CURM 71.33-8	Leaded Gunmetal	Feb 21	23
CURM 71.34-8	Leaded Gunmetal	Feb 21	23

PURCHASE PROCEDURE

ORDERING PROCEDURE

Please give the quantity, unit size or weight, reference number and description of the samples required, and ensure we have your full delivery and invoice address.

PRICES

For prices see separate price list. Prices are stated in £ Sterling (GBP) and are subject to revision without notice. They exclude packing, despatch and VAT where applicable but do include a Certificate of Analysis, which accompanies each CRM. If additional Certificates of Analysis are required we will charge a nominal price of £10.00 each for these.

TERMS

The following terms apply:-

- (i) **United Kingdom.** Net monthly account (subject to approved bank and trade references.) Insurance and freight are charged extra, and Value Added Tax at the standard rate is charged on the net invoice value.
- (ii) **Overseas.** Packing, documentation, insurance and carriage are charged extra at cost. We shall be pleased to forward a quotation detailing these costs upon request. Prepayment is required on all orders.

PAYMENT

To enable us to meet customer requirements with the minimum of delay, new and occasional customers are asked to make payment in advance using one of the following options:-

By BACS or inter-bank transfer to Barclays Bank PLC, Middlesbrough, Sort Code 20-56-74, SWIFT No BUKBGB22

In **Sterling** to Account No 90217506, IBAN No GB16 BUKB 2056 7490 2175 06

In **Euros** to Account No 85465422, IBAN No GB19 BUKB 2056 7485 4654 22

We accept Barclays charges in the UK but not your own bank's charges.

By credit/debit card.

Customers who indicate that they wish to purchase by this method will receive a secure link for Worldpay by email. The link will only be sent at our request and is not available from our web site. For additional security we do not require you to send us any card details to our address.

OUTSIDE-SOURCE REFERENCE MATERIALS

Bureau of Analysed Samples Ltd also distribute reference materials from any recognised Producer in the world. Many such reference materials are maintained in our UK stock for immediate despatch if required. Further information on all such samples is given in the BAS Outside-Source Reference Materials Catalogue which is available on request.

Please send all orders, enquiries and correspondence to:-

BUREAU OF ANALYSED SAMPLES LTD.

NEWHAM HALL, NEWBY,

MIDDLESBROUGH, ENGLAND, TS8 9EA.

Telephone: National: Middlesbrough (01642) 300500

International: +44 1642 300500

Website: www.basrid.co.uk

Email: enquiries@basrid.co.uk

BAS

MIDDLESBROUGH

U.K.