

OUTSIDE-SOURCE REFERENCE MATERIALS

	Page		Page
ACIRS: Australian Coal Industry Reference Samples, Australia	3	IMI: IMI Wolverhampton Metal, UK	33
AR: Alpha Resources Inc., USA	3	IA: Industrial Analytical, South Africa	34
ARCELORMITTAL: ArcelorMittal Maizières Research SA (formerly IRSID), France	4	IPT: Instituto de Pesquisas Tecnológicas, Brazil	35
BAM: Bundesanstalt für Materialforschung und -prüfung, Germany	6	JK: Jernkontoret / Narema, Nordic Countries	36
BNF: BNF-Fulmer, UK	12	LUCIDEON: (formerly CERAM Research), UK	39
BS: Brammer Standard Company Inc., USA	16	NILAB: Nordisk Industrilaboratorium AB, Sweden	26
CANMET: Canada Centre for Mineral and Energy Technology, Canada	20	NIST: National Institute of Standards and Technology, USA	40
CTIF: Centre Technique des Industries de la Fonderie, France	24	SABS: South African Bureau of Standards, South Africa	46
D-LAB: Degerfors Laboratorium AB, Sweden	26	SGT: Society of Glass Technology, UK	32
DL: Dillinger Laboratory, Germany	27	SPL: SPL-LABMAT s.r.o., Czech Republic	49
FLX: FluXana GmbH & Co. KG, Germany	31	SUS: SUS, Germany	50
HSL: Health and Safety Laboratory, UK	33	VASKUT: Vasipari Kutato es Fejlesztó Vallalat, Hungary	52
IGS: Institute of Geological Sciences/British Geological Survey, UK	32		

Distributed by

BUREAU OF ANALYSED SAMPLES LTD



CATALOGUE NO. 926b

SEPTEMBER 2024



4004

Certificate GB94/3993

PRODUCT INDEX

FERROUS METALS

	Page
(a) Steels	
Alloy Steel CRMs (BAM)	6
Alloy Steel CRMs (ARCELORMITTAL)	4
Alloy Steel CRMs (JK)	36
Alloy Steel CRMs (NILAB)	26
Calcium Treated Steel RMs (BS)	16
C, S, N, H & O in Steel RMs (BS)	16
C, S, N & O in Steel RMs (JK)	37
High Temperature and Specialty Steel CRMs (NIST) ..	43
High Manganese Steel RMs (BS)	16
Highly Alloyed Steel CRMs (BAM)	7
Highly Alloyed Steel CRM (CTIF)	24
Highly Alloyed Steel CRMs (ARCELORMITTAL)	4
Highly Alloyed Steel CRMs (JK)	36
Highly Alloyed Steel CRMs (VASKUT)	52
H, O & N in Steel RMs (AR)	3
Low Alloy Steel CRMs (NIST)	42
Low Alloy Steel CRMs (VASKUT)	52
Special Alloy CRMs (BAM)	7
Special Alloy CRM (JK)	36
Stainless and High Temperature Steel RMs (BS)	17
Tool Steel CRMs (NIST)	43
Unalloyed Steel CRMs (BAM)	6
Unalloyed Steel CRMs (ARCELORMITTAL)	4
Unalloyed Steel CRM (JK)	36
Unalloyed Steel CRMs (VASKUT)	52
Steel SUS (SUS)	50
(b) Cast Irons	
Austenitic (Ni-resist) Iron RMs (CTIF)	25
Cast Iron CRMs (BAM)	7
Cast Iron CRMs (CTIF)	24
Cast Iron CRMs (IPT)	35
Cast Iron CRMs (SPL)	49
Chromium Iron RMs (CTIF)	25
Cu-Ni-Cr-Mo Iron RMs (CTIF)	25
Electrolytic Iron CRM (NIST)	42
Iron Powder (JK)	37
Iron SUS (SUS)	50
Low Alloy Iron RMs (CTIF)	24
White Cast & Ductile Iron CRMs (NIST)	43
(c) Ferro-Alloys	
Ferro-Alloy CRMs (BAM)	8
Ferro-Alloy CRMs (D-Lab)	26
Ferro-Alloy RMs (DL)	27
Ferro-Alloy CRMs (ARCELORMITTAL)	5
Ferro-Alloy CRM (JK)	37
Ferro-Alloy CRMs (SABS)	48
Ferro-Alloy Slag RMs (IA)	34
Ferro-Chrome Slag CRM (SABS)	48

NON-FERROUS METALS

	Page
Aluminium Alloy CRMs (BAM)	10
Aluminium Alloy RMs (IMI)	33
Aluminium and Aluminium Alloy SUS (SUS)	50
Cobalt Base RMs (BS)	19
Cobalt and Cobalt Alloy SUS (SUS)	50
Copper Anode CRM (CANMET)	23
Copper Base Alloy RMs (BS)	19
Copper Base RMs (BNF)	12/15
Copper Base CRMs (IPT)	35
Copper and Copper Alloy CRMs (BAM)	9
Copper and Copper Alloy SUS (SUS)	50
Gold Alloy CRMs (BAM)	10
H, O & N in Titanium RMs (AR)	3
Lead Alloy CRMs (BAM)	10
Lead Base RM (BNF)	15
Lead and Lead Alloy SUS (SUS)	51
Magnesium and Magnesium Alloy SUS (SUS)	51
Nickel Base Alloy RMs (BNF)	14/15
Nickel Base Alloy RMs (BS)	18
Nickel and Nickel Alloy SUS (SUS)	51
Silicon Metal CRMs (IPT)	35
Special Alloy CRMs (CTIF)	24
Zinc-Aluminium Foundry Alloy CRMs (CANMET)	23
Zinc SUS (JK)	38
Zinc and Zinc Alloy SUS (SUS)	51
Zinc discs (JK)	58

ORES, ROCKS AND MINERALS

Andalusite CRM (SABS)	47
Coal and Coal Fly Ash RMs (ACIRS)	3
Coal CRMs (SABS)	47
Cover Powder and Rutile RMs (DL)	29
Fluorspar CRMs (JK)	37
Fluorspar CRMs (SABS)	47
Fly Ash CRM (JK)	38
Iron Ore CRMs (JK)	37
Iron Ore and Sinter RMs (DL)	30
Mineral CRMs (IPT)	35
Mineral RMs (DL)	29
Mineral, Concentrate and Ore CRMs (ARCELORMITTAL)	5
Ore and Concentrate CRMs (NIST)	42
Ore and Concentrate RMs (IGS)	32
Ore Concentrate and Tailing RMs (IA)	34
Ore Concentrate CRMs (Cu, Pb, Zn) (CANMET)	21
Ore CRMs (Base Metal) (CANMET)	20
Ore CRMs (Cr, Fe, Ti & Zr) (SABS)	46
Ore CRMs (Au & Pt) (SABS)	47
Ore CRMs (Fe & Mn) (BAM)	8

ORES, ROCKS AND MINERALS (continued)

	Page
Ore CRMs (Mn) (SABS)	47
Ore CRMs (Noble Metal) (CANMET)	20
Ore CRMs (Sulphide Mill Tailings) (CANMET)	21
Rare Earth Elements with Zr & Nb CRMs (CANMET)	23
Rock and Mineral CRMs (CANMET)	22
Rock CRMs (Igneous) (SABS)	47
Rock CRM (Phosphate) (SABS)	48
Rock and Mineral CRMs (NIST)	43
Rock, Mineral and Sediment CRMs (SABS)	48
Siliceous RMs (LUCIDEON)	39
Soil and Till RMs (CANMET)	22
Zircon Bearing and Basic RMs (LUCIDEON)	39

ENVIRONMENTAL MATERIALS

Dust CRMs (Ferrous) (ARCELORMITTAL)	5
Environmental CRMs (NIST)	45
Respirable α -quartz RM (HSL)	33
PGE in Auto Catalyst (BAM)	11
Welding Fume RMs (HSL)	33

REFRACTORIES, SLAGS AND CEMENTS

Basic Slag CRMs (BAM)	8
Blast Furnace and Basic Slag CRMs (ARCELORMITTAL)	5
Blast Furnace and Steelmaking Slag CRMs (JK)	38
Cement CRMs (FluXana)	31
Cement CRMs (NIST)	45
Cement RMs (DL)	30
Ceramic CRMs (BAM)	8
Ceramic (High Oxygen) SUS (JK)	38
Dust and Slag RMs (DL)	28
Glass and Glass Sand CRMs (SGT)	32
Industrial Fly Ash CRMs (JK)	38
Refractory CRMs (IPT)	35
Refractory CRMs (ARCELORMITTAL)	5
Refractory CRMs (NIST)	43
Refractory RMs (DL)	28

BIOLOGICAL MATERIALS

Biological CRMs (NIST)	44
------------------------------	----

OTHERS

Depth Profile SUS (JK)	38
Glass CRMs containing Iron (BAM)	10
Glass CRM containing hexavalent chromium (BAM)	11
Glass CRM – multielement (BAM)	11
Glass CRMs (FluXana)	31
High Purity Substances (BAM)	11
Molybdenum Oxide CRM (BAM)	8
Tungsten Metal Powder CRM (BAM)	11
Vanadium Pentoxide CRM (SABS)	47
XRF Monitor Sample (FluXana)	31

INTRODUCTION

For over eighty years Bureau of Analysed Samples Ltd (BAS) has been preparing British Chemical Samples, now known as BCS Certified Reference Materials (CRMs) for the metallurgical industries. Full particulars of all BAS-produced materials are given in a separate catalogue.

When the UK joined the EEC in 1973 BAS was invited to co-operate with BAM in Germany and IRSID in France in the production of CRMs for the iron and steel industry on a European basis and this European Producers Group has been augmented by the inclusion of the Nordic CRM Working Group: this work was under the auspices of the European Committee for Iron and Steel Standardization (ECISS). These EURONORM Certified Reference Materials (ECRMs) are normally analysed by approximately twenty laboratories from countries in the European Economic Area (EEA) and are issued with a Certificate of Analysis approved by the participating laboratories and the producing organizations. These ECRMs are indicated by an asterisk in this list. Although BAS is no longer a part of the ECRM Producers Group, all ECRMs (prepared by BAM, IRSID (now ARCELORMITTAL), CTIF and Jernkontoret) are available from BAS. Data regarding the BAS-produced ECRMs are given in the BAS Certified Reference Materials Catalogue, whilst the data re BAM, ARCELORMITTAL, CTIF and Jernkontoret -produced ECRMs are given in this catalogue.

Further details of ECRMs, including their method of preparation, certification and supply and the use of the statistical information given on ECRM certificates are given in Technical Reports CEN/TR 10317:2014 and CEN/TR 10350:2013 which are available in the UK from the BSI, 389 Chiswick High Road, London W4 4AL.

In September 1992, the BNF – Fulmer organisation was closed down. BAS purchased their Reference Materials business, including the considerable stock of BNF samples, and is continuing the business as before. Thus, BAS is now the primary source of BNF copper, nickel and lead base Reference Materials. Replacement samples are being produced by BAS in order to maintain continuity of supply of these samples: (see the latest BAS Catalogue for details of such samples already produced by BAS).

In order to assist our customers to obtain complementary Reference Materials from other reputable producers, BAS is now holding a stock, and many of the Reference Materials detailed in this catalogue are immediately available, with delivery of non-stock items usually achieved within two to three weeks.

In this catalogue Reference Materials which are supplied with a Certificate of Analysis giving the information specified in ISO Guide 31 "Contents of Certificates of Reference Materials" are referred to as "Certified Reference Materials" and the remainder as "Reference Materials", in accordance with the definitions given in ISO Guide 30 "Terms and definitions used in connection with Reference Materials". (ISO Guides are available from Case Postale 56, CH-1211 Geneva 20, Switzerland).

The Certificate accompanying each CRM, or Analysis Report/Information Sheet accompanying each RM, should be consulted to obtain the accurate analysis of each sample, since in some cases the figures shown in this catalogue may differ slightly from those given on the Certificate or Analysis Report/Information Sheet. Please note that the disc/block sizes stated in this catalogue are approximate and may vary from sample to sample.

GENERAL INFORMATION

Our website, at www.basrid.co.uk, is continuously being improved and now includes a page of downloadable certificates for all currently available BAS products.

QUALITY ASSURANCE

Bureau of Analysed Samples Ltd, is very pleased to advise customers that in November 1994 its Quality System was formally approved and recognised by the award of a Certificate of Registration to the Quality Standard BS EN ISO 9002:1994 for the production and supply of CRMs, RMs and SUS. This certificate has now been revalidated to the new standard BS EN ISO 9001:2015. Furthermore, BAS was accredited, in June 2006, to the International Guide, ISO Guide 34 (General Requirements for the Competence of Reference Material Producers) and the accreditation has since been updated to the Standard ISO 17034.

Please note that, whilst BAS is accredited to ISO 17034, only two of the Producers detailed in this catalogue (Brammer Standard Company, Inc. and Bundesanstalt für Materialforschung und -prüfung) are so accredited. The CRM/RMs prepared by the other producers in this catalogue will not have been produced under ISO 17034 accreditation.

Australian Coal Industry Reference Samples (ACIRS), Australia

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only

Coal Reference Materials (Finely divided material – unit weights as shown in table)

ACIRS No.	Description	Unit Weight	Ash	Volatile Matter	Total C	H	N	P	C as CO	Cl	F	Hg	Cd	As	Se	Total S	Hardgrove Grindability Index	Gross Calorific Value MJ/kg	Relative Density
S2A-2020	Coal	125g	0.43
S2B-2015	Coal	125g	0.027	0.0037	0.0000057	0.69
G10-2022	Coal	125g	10.46	19.79	0.020	...	0.052	0.0076	0.00000029	0.606	...	32.331	1.379
H9-2022	Coal	4 x 1kg	30, 45, 62 & 87

Coal Fly Ash Reference Material (Units of 75g)

ACIRS No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	TiO ₂	Mn ₃ O ₄	BaO	SrO	SO ₃	ZnO
A2-2024	Coal Fly Ash	58.0	26.0	8.8	2.61	1.03	0.36	0.90	0.55	1.42	0.12	0.05	0.04	0.13	0.01

Values are also given for Ash Fusibility Reducing Temperatures:- Deformation 1310°C; Spherical 1370°C; Hemispherical 1400°C; Flow 1480°C
 Ash Fusibility Oxidising Temperatures:- Deformation 1430°C; Spherical 1460°C; Hemispherical 1480°C; Flow 1520°C

ALPHA RESOURCES Inc. (AR), USA

CHEMICAL COMPOSITION (nominal mass content in %)

Oxygen & Nitrogen in Steel Reference Materials (units as shown)

AR No.	Units	Oxygen	Nitrogen
645	100 x 1g pins	0.0034	0.0069
646	"	0.0028	0.076
658	"	0.0013	0.0771
661	"	0.0008	0.0091
1651	"	0.0036	0.0228
1652	"	0.0031	0.0537
1658	"	0.0009	0.0756

Hydrogen in Steel Reference Materials (units as shown)

AR No.	Units	Hydrogen
555	100 x 1g pins	0.00025

Hydrogen, Oxygen & Nitrogen in Titanium Reference Materials (units as shown)

AR No.	Units	Hydrogen	Oxygen	Nitrogen
648	100 x 0.1g pins	0.0169	0.119	0.0058

Alpha Resources also produce Reference Materials for:
 Carbon, Sulphur & Nitrogen in Steel
 Hydrogen, Nitrogen & Oxygen in Zirconium
 Hydrogen & Carbon in Titanium
 Hydrogen & Carbon in Zirconium
 Oxygen & Sulphur in Copper
 Oxygen & Nitrogen in Iron Powder

**The above figures are target levels and may vary between batches.
 The above only constitutes a selection of Alpha Resource samples. Additional samples are available and information on these will be provided on request.**

ARCELORMITTAL MAIZIÈRES RESEARCH SA (formerly IRSID), France

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steel Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Ni	Al Total	Co	Cu	Pb	Sn
ECRM 012-1	0.082	0.083	0.255
ECRM 021-1	0.243	0.271	1.288	0.0121	0.0087	0.125	0.255	0.167
ECRM 022-1	0.115	...	0.797	0.057	0.296
ECRM 023-1	0.331	0.264	0.667	0.021	0.0156	0.280	...
ECRM 024-1	0.104	0.139	0.726	0.0155	0.235	0.287	...

Alloy Steel Certified Reference Materials (Finely divided material – units of 100g; 190-1 also available as 35mm x 35mm x 30mm blocks)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	V	W
ECRM 106-2	0.153	0.238	0.727	1.030	0.054	1.430	0.078
ECRM 107-1	0.407	0.286	0.611	1.443	0.323	0.191	0.345	...	0.108
ECRM 108-1	0.384	0.340	0.690	0.0176	0.017	2.92	0.538	0.215	0.118
ECRM 112-1	0.348	1.00	0.191	4.78	1.21	0.234	0.115	...	0.604	1.78
ECRM 113-1	0.680	0.249	0.586	<i>0.013</i>	<i>0.006</i>	0.816	0.413	1.744	0.146
*ECRM 188-1	1.094	0.0113	1.538
*ECRM 190-1	0.395	0.278	1.28	0.0112	0.0044	2.18	0.410	0.934	...	0.034	...	0.0096

Alloy Steel Certified Reference Materials (continued)

AMMZ/IRSID No.	Bi	Cd	Ga	Hg	Nb	Pb	Sb	Se	Te	Tl	Zn
*ECRM 188-1	< 0.00002	< 0.00005	0.00251	< <i>0.00001</i>	0.00013	< 0.0001	0.00048	< <i>0.0002</i>	< 0.0002	< <i>0.00002</i>	< <i>0.0003</i>

Highly Alloyed Steel Certified Reference Materials (Finely divided material – units of 100g; ECRM 269-1 also available as 35mm diameter x 25mm discs)

AMMZ/IRSID No.	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	Nb	Sn	Ti	V	W	Ca	Zn
ECRM 201-1	0.291	0.843	0.363	12.33	0.050	0.202	0.099	0.0193	...	<i>0.020</i>	...	0.0018	0.0005
*ECRM 269-1	0.0499	0.441	1.262	0.0313	0.0010	18.150	0.397	8.044	0.0061	0.1116	0.366	0.0460	0.0242	0.0099	0.0006	0.0991	0.0306
*ECRM 279-2	0.0885	0.5160	0.2584	15.642	...	1.603	0.1067
*ECRM 282-1	0.086	0.734	1.64	0.019	0.0042	16.72	2.19	10.86	0.109	0.488	<i>0.031</i>

* Denotes Full EURONORM-Certified Reference Material

ARCELORMITTAL MAIZIÈRES RESEARCH SA (formerly IRSID), France

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	C	Si	Mn	P	S	Cr	Al	N	Ti
ECRM 503-1	Ferro-Manganese	0.700	0.865	80.8	0.069	<i>0.009</i>
ECRM 507-1	Ferro-Chromium	5.43	1.20	0.270	0.018	...	70.27	...	0.050	...
ECRM 509-1	Ferro-Chromium	0.013	0.229	...	0.018	...	72.85	...	0.026	...
ECRM 510-1	Ferro-Titanium	0.058	4.65	...	<i>0.035</i>	<i>4.9</i>	<i>0.014</i>	26.95

Mineral, Concentrate and Ore Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	Co	C(τ)	Zn	Fe (II)	Others
ECRM 601-1	Iron Ore	36.76	8.95	4.05	1.21	2.33	0.114	0.370	0.590	0.065	<i>8.8</i>	...
ECRM 603-1	Iron Ore	53.65	1.28	<i>0.91</i>	<i>0.2</i>	4.20	0.137	0.440	0.084	0.097	<i>0.3</i>	...
ECRM 604-1	Iron Ore	65.69	1.27	0.107	0.049	0.93	0.060	0.092	0.053	0.015	<i>0.5</i>	...
ECRM 606-1	Iron Ore	59.66	1.04	1.04	0.32	0.34	0.019	2.59	0.026	0.033	<i>0.1</i>	...
ECRM 607-1	Iron Ore	30.89	3.07	13.74	0.77	2.48	0.123	0.254	0.529	0.050	<i>5.95</i>	...
ECRM 608-1	Ferriferrous Marl	4.00	28.23	6.22	0.81	5.26	0.428	0.044	0.053	0.455	<i>1.85</i>	...
ECRM 611-1	Iron Ore Sinter	62.22	2.07	2.85	0.32	0.69	0.035	1.97	0.030	<i>0.008</i>	<i>13.84</i>	...
ECRM 612-1	Iron Ore Sinter	42.43	5.94	12.06	1.20	3.00	0.151	0.363	0.885	0.053	<i>9.19</i>	...
*ECRM 677-1	Iron Ore	51.54	11.78	0.038	0.012	0.32	0.013	0.016	0.0170	<i>0.005</i>	0.007	0.008	...	<i>0.002</i>	<i>0.0015</i>	<i>0.0006</i>	...	<i>0.002</i>	...	0.43 H₂O+
*ECRM 691-1	Iron Ore	64.39	0.556	0.999	2.022	0.475	0.966	0.1734	0.0877	0.0632	0.0164	0.0504	0.0603	0.0095	0.0299	<i>(0.0216)</i>	0.307	0.0195	20.71	0.0768 Cu 0.0008 Pb

Refractory Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Cr	Mn	B	N	P	S	C(τ)	H ₂ O	LOI
ECRM 702-1	Dolomite	0.440	1.04	21.48	12.37	0.21	0.013	<i><0.002</i>	0.098	0.024	<i>0.027</i>	<i>12.3</i>	0.5	45.6
*ECRM 778-1	High Carbon Magnesite	0.67	0.489	0.883	48.87	0.297	<i>0.008</i>	0.102	0.011	0.0012	...	<i>0.004</i>	...	14.00	...	15.38
*ECRM 780-1	Silicon Carbide	1.30	63.5	0.84	0.051	1.86	0.029	...	0.32	26.38

Slag and Dust Certified Reference Materials (Finely divided material – units of 100g)

AMMZ/IRSID No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	F	V	Cr	Ni	Zn	Cu	As	Pb	C(τ)	Cl	Others
ECRM 803-1	Blast Furnace Slag	0.613	17.01	30.93	2.44	6.98	0.301	0.552	0.118	0.767
ECRM 804-1	Basic Slag	11.92	2.59	36.88	0.88	0.407	0.152	1.48	7.67	0.127	0.460
ECRM 805-1	Basic Slag	14.87	3.10	34.96	1.12	0.326	0.205	1.59	7.07	0.092	0.514
ECRM 806-1	Basic Slag	17.89	5.48	32.97	1.82	0.477	0.302	4.60	0.982	0.110	0.288
*ECRM 876-1	Electric Furnace Dust	24.85	1.72	3.43	1.31	0.34	0.048	2.84	0.128	0.87	1.98	1.63	0.24	...	0.17	0.034	23.29	0.42	0.023	7.82	0.26	3.63	0.13 Cd 0.094 Sn
*ECRM 880-1	Blast Furnace Dust	31.0	3.34	3.15	0.714	1.28	0.081	0.218	0.038	0.425	0.041	0.108	0.034	...	0.027	0.014	0.064	0.005	...	0.017	<i>37.77</i>	0.086	...

* Denotes Full EURONORM Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Unalloyed Steel Certified Reference Materials (All finely divided materials - units of 100g, except 026-1, 026-2, 027-1, 028-1, and 029-1 which are 10mm dia. x 90mm rods and 098-1 which is in solid disc form 36-39mm dia. x 26mm: ECRM 035-2 also available as 38mm dia. x 20mm discs and ECRM 083-2 also available as 39mm dia. x 28mm discs)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Acid Sol.)	Al (Total)	As	Co	Cu	N	Pb	Sn	Ti	V	Others
ECRM 026-1	1969	<i>0.44</i>	0.0053	0.0031 O
ECRM 026-2	1973	0.0042	0.0025 O
ECRM 027-1	1970	<i>0.05</i>	<i>0.003</i>	<i>0.4</i>	<i>0.03</i>	<i>0.03</i>	<i>0.001</i>	0.0157	0.0084 O
ECRM 028-1	1970	<i>0.1</i>	<i>0.002</i>	<i>0.3</i>	<i>0.06</i>	<i>0.03</i>	<i>0.001</i>	0.0029	0.0113 O
ECRM 029-1	1970	<i>0.05</i>	<i>0.003</i>	<i>0.3</i>	<i>0.03</i>	<i>0.03</i>	<i>0.001</i>	0.0083	0.0312 O
ECRM 030-4	1973	0.456	0.318	0.603	0.018	0.021	0.117	...	0.042	...	0.042	0.012	...	0.061	0.0051	...	0.0055
ECRM 031-3	1972	0.055	0.037	0.329	0.014	0.021	0.054	0.013	...	0.020	0.0050
ECRM 032-2	1968	0.271	0.282	0.556	0.0129	0.0254	<i>0.088</i>	...	<i>0.040</i>	0.020	...	0.085	0.0044
*ECRM 035-2	1998	1.277	0.216	0.305	0.0038	0.0111	0.0104	0.0056	0.0190	0.0177	0.0193	0.0017	...	0.0085	0.0230	0.0030
ECRM 036-1	1968	0.858	0.194	0.327	0.0074	0.0095	<i>0.091</i>	...	<i>0.058</i>	...	<i>0.015</i>	0.0233	...	0.065	0.0100	...	<i>0.006</i>	...	<i>0.019</i>	...
ECRM 042-1	1972	0.108	0.037	0.666	0.0057	0.024	0.016	...	0.029	...	0.010	0.041	0.0078	0.0054 Nb
ECRM 049-1	2020	0.701	0.00404	0.00317
*ECRM 077-3	2017	0.1650	0.01623	0.00852
*ECRM 079-2	1989	0.596	0.247	0.743	0.0234	0.192	0.0382	...	0.022	...	0.021	0.004	...	0.046	0.0074	...	0.0037
*ECRM 082-1	1976	0.415	0.235	0.769	0.013	0.030	0.018	...	0.027	...	0.032	<i>0.029</i>	...	0.025	<i>0.0047</i>	0.149	0.030 Te
*ECRM 083-1	2009	0.0262	...	0.289	0.0076	0.0100	<i>0.013</i>	...	0.014	...	<i>0.004</i>	<i>0.004</i>	...	0.016	0.00189
*ECRM 083-2	2017	0.0315	0.00747	0.2160	0.0106	0.00561	0.0219	...	0.0116	...	0.0784	0.00177	0.00236	0.0127	0.00157	<i>(0.0002)</i>	...	<i>(0.0003)</i>	<i>(0.0005)</i>	0.00439 Zn
*ECRM 098-1	1993	0.00051	0.00048	0.00008	<i>0.00006</i>	0.00031	0.00571	0.00085	0.00024

Alloy Steel Certified Reference Materials (Finely divided material - units of 100g; 129-3, 179-2, 187-2, 191-3, 192-1 and 193-1 and also available as 37-40mm dia. x 25-35mm discs)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu	N	Sn	Ti	V	Others	
ECRM 126-1	1963	0.841	<i>0.24</i>	1.817	0.009	0.005	0.317	...	<i>0.038</i>	<i>0.098</i>	0.143	...	
ECRM 128-1	1972	0.085	0.949	0.839	0.007	0.007	0.108	...	0.046	0.286	0.055	<i>0.0024</i>	...	0.890	<i>0.008</i>	...	
*ECRM 129-3	2008	0.3684	0.2087	0.371	0.0110	0.0165	1.702	0.206	1.022	1.016	0.0049	<i>0.00014</i>	0.0148	0.0804	0.0046	0.0067	0.030	<i>0.0045</i>	0.00059 Sb	
ECRM 130-1	1968	0.546	0.313	1.593	0.0209	0.0158	<i>0.032</i>	...	<i>0.031</i>	0.0037	0.0167	0.072	0.0093	<i>0.003</i>	0.0019 Al (Acid Sol.)	
*ECRM 179-2	1990	0.598	0.579	0.539	0.0267	<i>0.0006</i>	1.08	0.070	0.078	<i>0.0153</i>	0.111	0.0068	...	<i>0.0014</i>	0.188	1.87 W, <0.00003 Bi, <0.00003 Cd, 0.00129 Ga, 0.00144 Nb, 0.00013 Pb, 0.00175 Sb, <0.0002 Te, 0.00023 Zn	
*ECRM 180-1	1973	0.197	0.362	1.286	0.0174	0.0249	1.250	...	0.096	...	0.030	0.115	0.0068	
*ECRM 182-1	1993	0.790	0.368	0.389	0.009	0.011	0.591	...	0.152	0.020	0.141	0.0102	0.177	0.0039 Pb, 0.0042 Sb, 0.0015 Zn	
*ECRM 183-1	1973	0.083	0.421	0.354	0.089	0.031	0.670	...	0.073	0.027	0.445	0.0064	
*ECRM 187-1	1986	0.195	0.026	1.354	0.014	0.025	1.186	0.035	0.096	0.046	0.018	0.0004	0.014	0.161	0.014	0.011
*ECRM 187-2	2011	0.2038	0.2111	1.257	0.0066	0.0300	1.132	<i>0.0623</i>	0.1755	0.0223	0.0057	0.00048	0.0112	0.1288	0.0105	0.0237	...	0.0122	<i>0.0018 Sb</i>	
*ECRM 191-2	2006	0.0043	3.267	0.1334	0.0087	0.0029	0.0314	0.0020	0.0224	0.985	0.0018	0.0165	0.00105	0.0050	0.0024	
*ECRM 191-3	2021	0.0027	3.226	0.1539	0.0097	0.0005	0.0242	0.00127	0.0124	0.815	0.00144	0.00024	...	0.0097	0.00105	0.00131	0.0020	0.00043	0.0036 Mg	
*ECRM 192-1	1995	0.188	0.219	1.377	0.0029	0.0010	0.072	0.482	0.755	0.0308	<i>0.003</i>	<i>0.0002</i>	0.0055	0.045	0.0118	<i>0.003</i>	<i>0.001</i>	<i>0.003</i>	0.029 Al (Acid Sol.)	
*ECRM 193-1	1990	0.139	0.404	0.972	0.0063	0.0086	0.182	0.347	1.178	0.0257	0.0062	<i>0.0002</i>	0.0073	0.598	0.0108	...	<i>0.0013</i>	<i>0.0019</i>	0.0232 Nb	
*ECRM 194-1	2015	0.1532	0.431	1.188	0.0097	0.00059	0.733	0.2857	0.3417	0.0837	0.0042	0.0020	...	0.0751	0.0115	0.0243	0.0026 Ca	
*ECRM 194-2	2015	0.1694	0.2974	1.282	0.0137	0.00049	0.760	0.402	0.3316	0.0669	0.00208	0.00155	0.00328	0.0313	0.00319	<i>0.0004</i>	0.00322	0.00161	0.0290 Nb, 0.0003 Sb	

* Denotes Full EURONORM-Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Highly Alloyed Steel Certified Reference Materials

(Finely divided material[^] – units of 100g; 284-3, 289-1, 290-1 and 291-1 also available as 36-40mm dia. x 25-35mm discs; 271-1 as a 37mm dia. x 25mm disc, 294-1 as a 40mm dia. x 20mm disc and 297-1 as a 36mm dia. x 25mm disc)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Sn	Ti	V	W	Others
ECRM 227-1	1994	0.950	0.272	0.236	0.016	0.022	4.25	2.64	0.114	0.124	0.040	0.0251	...	2.44	3.03	0.0035 Sb
*ECRM 231-2	2002	0.0140	0.368	1.263	0.0179	0.0250	18.07	0.301	10.105	0.0032	0.0048	0.0020	0.0402	0.0941	0.0444	0.0043	0.0007	0.0708	0.0141	0.00074 Ca 0.0011 Sb
ECRM 235-1	1972	0.912	0.094	12.73	0.045	0.0072	0.354	0.032	0.073	0.020
ECRM 237-1	1973	0.068	0.482	1.443	0.032	0.012	17.24	0.306	10.32	0.221	0.123	0.035	0.057	...	0.660 Nb
[^] ECRM 267-1	2021	0.0266	0.00096 O
*ECRM 271-1	2007	0.3698	0.923	0.437	0.0120	0.00045	5.002	1.247	0.1552	0.0234	0.0057	...	0.0139	0.1371	0.0137	0.0084	0.0020	0.850	0.0054	0.0009 Ca 0.0020 O
*ECRM 278-1	1973	0.903	0.336	0.405	0.0154	0.0052	18.11	1.040	0.236	0.077	0.077
*ECRM 283-1	1985	1.219	0.345	0.217	0.022	0.029	4.15	3.41	...	0.010	...	0.0003	10.27	...	0.033	3.28	9.66	...
*ECRM 284-2	2000	0.0201	0.537	1.745	0.0258	0.0237	16.811	2.111	10.72	0.0027	0.0063	0.0026	0.0525	0.1831	0.0151	0.0047	0.191	0.0425	...	0.0099 O
*ECRM 284-3	2016	0.0025	0.0442	0.0615	0.0049	0.0066	17.37	2.236	12.09	0.002	0.00131	0.00020	0.0366	0.0105	0.0418	0.00074	0.0050	0.005	0.0039	...
ECRM 286-2	2023	0.0640	0.3935	1.9187	0.0306	0.3055	17.651	0.4132	8.436	0.1490	0.3703	0.0350	0.0097	0.00048	0.0951	...	0.0031 Zn 70.33 Fe
*ECRM 288-1	1986	2.08	0.260	0.292	0.024	0.0012	12.00	0.103	0.298	0.012	0.006	...	0.018	0.060	0.0151	0.0043	0.020	0.055	0.68	...
*ECRM 289-1	1990	0.0489	0.531	1.016	0.0114	0.0027	14.63	1.102	24.68	0.199	0.006	0.0044	0.065	0.111	2.01	0.260
*ECRM 290-1	1990	0.911	0.072	0.244	0.0160	0.0160	4.18	4.83	0.329	5.12	0.081	0.0325	1.91	6.27	...
*ECRM 291-1	1990	0.903	0.907	0.808	0.0168	0.0087	17.10	2.10	0.563	0.0030	0.0233	0.0711	0.1142	0.388
*ECRM 294-1	2005	0.0657	0.283	18.68	0.0271	0.00031	17.98	0.0861	0.429	0.001	0.0037	<0.0005	0.0288	0.0242	0.566	0.001	<0.002	0.0694	<0.004	...
*ECRM 297-1	2005	0.0223	0.344	0.897	0.0135	0.0101	18.37	0.290	12.33	0.0195	0.0040	1.146	0.0413	0.204	0.0152	...	0.0072	0.535	0.006	...
*ECRM 299-1	2009	0.0154	0.299	0.2678	0.0152	0.00022	22.32	0.0186	0.172	5.33	0.0054	0.0002	0.0187	0.0382	0.0198	0.008	0.1289	0.0329	0.0002	0.1775 Zr

Also available: **BAM Steel-H2**, highly alloyed steel, with a certified hydrogen content of 1.26 mg/kg (100 x 1g pins) [^]ECRM 267-1 is supplied as 100 x 1g pins

Special Alloy Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	N	Nb	V	W	Zr	Ta	Fe
ECRM 326-1	1972	0.092	1.46	0.406	0.0093	0.0028	16.37	0.025	61.16	0.79	0.223	0.027	0.036	...	0.024	...	0.129
ECRM 327-2	1972	0.152	2.052	1.289	0.0228	0.0046	24.35	0.174	19.72	0.070	0.159	0.060	0.059	...	0.044
ECRM 328-1	1973	0.390	0.629	1.395	0.005	0.003	20.54	4.41	20.38	0.070	41.65	0.013	0.027	3.61	...	4.16	...	0.18	2.40

Cast Iron Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Ti	V	Mg
*ECRM 428-2	1998	2.747	1.752	0.750	0.0691	0.1105	0.0366	0.0014	0.0358	...	0.0156	0.0996	...	0.0311	0.0120	...
*ECRM 476-3	1996	3.390	1.813	0.987	0.0908	0.0493	0.0648	...	0.0549	...	0.0145	0.2445	0.0038	0.0222	0.0115	...
*ECRM 478-2	1996	4.003	2.411	0.321	0.202	0.0460	0.251	...	0.151	...	0.0018	0.1276	0.0023	0.0328	0.0113	...
*ECRM 480-1	1988	3.03	2.41	0.151	0.0021	0.0086	0.483	0.016	0.017

* Denotes Full EURONORM Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND -PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	As	Al	B	Cu	Sn	Pb	N	Ti	V	Ca	Mg	Fe	Zn	Co	Sb	Zr
*ECRM 502-2	2004	6.94	0.10	77.87	0.148	0.002	0.0265	...	0.0384	0.0003	0.0370	...	0.0179	0.02	0.0034	14.6
ECRM 529-1	1975	0.10	91.11	0.04	0.013	0.86	0.09	...	0.46	0.04	6.15
ECRM 578-2	2024	0.0200	0.0221	0.0311	...	72.19	0.0299	0.3497	0.00305	0.0069	0.0018
ECRM 589-2	2024	0.179	...	0.247	...	0.0101	...	0.549	0.191	...	3.172	...	0.0697	0.166	68.94	0.0149	...	0.260	...
*ECRM 591-2	2022	0.0206	0.246	0.0207	0.0050	0.0037	0.0086	0.0045	...	0.00046	0.0036	0.0017	84.28	13.86	0.0181
*ECRM 593-1	2022	0.555	4.73	0.861	0.116	0.198	0.621	0.422	0.451	0.0028	...	0.0052	0.166	0.0048	0.0147	67.05	0.0088

* Denotes Full EURONORM-Certified Reference Materials

Ore Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	Description	Fe	SiO ₂	Al ₂ O ₃	TiO ₂	CaO	MgO	Mn	P	S	Na ₂ O	K ₂ O	As	Ba	CO ₂	H ₂ O
ECRM 630-1	1969	Bomi-Hill Concentrate	65.63	5.88	0.88	0.066	0.10	0.47	0.060	0.043	0.032
ECRM 631-1	1969	Venezuela Iron Ore	61.09	3.20	1.06	0.109	0.75	0.54	0.044	0.114	0.033	0.04	0.04
ECRM 633-1	1967	Manganese Ore	1.64	10.39	1.64	0.079	2.02	0.58	47.85	0.170	0.227	0.0040	1.13	3.48	7.11

Iron Ore Certified Reference Materials (Finely divided material – units of 100g; 686-1 supplied as 2 x 50g)

BAM No.	Cert. Date	Description	Fe	Si	Al	Ti	Ca	Mg	Mn	P	S	Na	K	Zn	Cl	Co	Cr	Cu	Ni	Others
*ECRM 680-1	1977	Purple Ore	59.98	4.20	0.66	0.045	0.45	0.14	0.025	0.018	0.544	0.128	0.078	0.165	...	0.013	0.005	0.063	0.007	0.317 Pb, 0.057 As
*ECRM 686-1	2002	Iron Oxide	69.44	0.0083	0.0407	0.0014	0.0097	0.0027	0.231	0.0078	...	0.0058	0.0024	0.0004	0.095	0.0019	0.0182	0.0003	0.0004	0.0007 Mo, 0.0002 Sn
*ECRM 687-1	2009	Iron Oxide	69.66	0.0157	0.0356	0.0303	0.0113	0.0018	0.1658	0.0120	...	0.0030	0.0011	0.0051	0.0173	(0.002)	0.0227	0.0030	0.0122	0.0020 Mo, 0.0006 Sn

Ceramic Certified Reference Materials (Finely divided material – units of 100g; 777-1 supplied as 2 x 50g)

BAM No.	Cert. Date	Description	Si	Ca	Mg	Al	Ti	Mn	P	Fe	Na	K	B	Cr
*ECRM 777-1	1984	Silica Brick	44.44	2.02	0.043	0.42	0.27	0.23	0.02	0.13
*ECRM 779-1	1991	Magnesite	0.182	1.691	54.6	0.105	0.0081	0.503	0.0267	3.73	0.006	0.002	0.0116	0.003

Molybdenum Oxide Certified Reference Material (Finely divided material – units of 100g)

BAM No.	Cert. Date	Ca	Mg	Ti	P	Bi	Cu	Fe	Pb	K	Al	As	Mo	Si	S	Na	C	W	Ba	V
*ECRM 784-1	2018	0.888	0.0883	0.0223	0.0113	0.00326	0.390	1.870	0.0215	0.164	0.468	0.0126	57.85	2.651	0.0083	0.0396	0.0103	0.0145	(0.006)	(0.127)

Slag Certified Reference Materials (Finely divided material – units of 100g)

BAM No.	Cert. Date	Description	SiO ₂	CaO	P ₂ O ₅ (Citric Acid Sol.)	P ₂ O ₅ (Total)	Cr	Al	V	K	Na	Mo	Ni	B	Cu	Pb	F
ECRM 826-1	1994	Phosphate Slag	8.96	46.48	10.73	14.65	0.182	0.696	0.503	0.0278	0.375	0.001	0.002	0.003	0.002	0.005	0.37
ECRM 827-1	1991	Thomas Phosphate	6.21	47.38	18.79	20.70

* Denotes Full EURONORM-Certified Reference Materials

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets are for information only.

Copper and Copper Alloy Certified Reference Materials (223-229 finely divided material – units of 100g; all others are 40mm dia. x 30mm discs)

Mass fraction in %

BAM No.	Cu	Sn	Zn	Pb	Fe	Ni	Al	Mn	Bi	As	Sb	Si	P	S	Cd	Ag	Mg	Others
223	58.74	0.089	38.82	2.13	0.091	0.0214	<0.002	<0.001	0.0018	0.0084	0.0040	<0.003	0.0003	0.0011	<0.0001 Se
224	57.40	0.066	39.40	1.13	0.136	0.038	0.0012	1.70	0.0006	0.0025	0.0026	(0.002)	0.0112	0.0004
227	85.57	6.01	3.46	4.12	0.129	0.284	<0.0001	...	0.0088	0.081	0.160	<0.01	0.0002	0.122	0.0028 Se, 0.0012 Te
228	85.34	9.76	3.32	1.24	0.036	0.109	0.0001	<0.001	0.0086	0.024	0.078	...	0.019	0.036	0.0012 Se
229	63.334	0.00485	36.63	0.0192	0.01061	0.01114	0.00217	0.00072	...	0.0011	0.0034 Se
368	77.05	0.0147	Bal.	0.0131	0.0193	0.0258	1.972	0.0203	...	0.0246	...	0.013	0.0090	0.0019	0.0062	0.00129 Ti
369	0.0022	0.00097	0.00036	0.001042 Co, 0.000921 Cr
370	...	0.00168	...	0.00158	0.00126	0.00156	0.00187	0.00117
371	0.00183	0.00121	0.00016	0.00144 Te
372	0.00117	...	0.00114	...	0.00103	0.00090	...	0.00084 Se
ERM-EB374	92.22	7.60	0.00404	0.00083	0.0040	0.00327	<0.0001	0.00043	0.00022	0.00043	0.00063	<0.001	0.1697	0.0013	<0.0001	0.00121	<0.0001	<0.0002 Se, <0.0001 Te
M376a	Bal.	0.0247	0.0217	0.0236	0.0235	0.0209	0.0182	0.0206	0.0200	0.0200	0.0202	...	0.0203	0.0133	0.0186	0.0163	0.0124	0.0210 Se, 0.0215 Te 0.00422 Zr
ERM-EB377	94.04	5.92	0.01006	0.00449	0.01042	0.01074	0.00451	0.00921	0.00422	<0.001	0.0013	<0.0134	<0.001	0.00068	<0.0001	0.00644	<0.0001	0.0055 Se, <0.0001 Te
ERM-EB378	94.13	5.74	0.00073	0.00042	0.00182	0.00183	<0.0001	0.000074	<0.0001	0.00995	0.00861	<0.0010	0.0602	0.00091	0.01007	0.00266	0.00287	<0.0002 Se, 0.00850 Te 0.0089 Co, 0.0311 Cr
ERM-EB387	75.18	0.00301	19.57	0.00108	0.0617	5.020	...	0.0796
ERM-EB388	89.27	0.857	4.81	0.000969	0.0303	0.00736	4.972	0.0512
ERM-EB389	74.3	0.0262	0.1125	0.0098	0.107	24.7	0.0123	0.415	0.0044	...	0.0046	0.0349	0.0093	0.0308	0.0016	...	0.067	0.0770 Co, 0.0153 Cr 0.0660 Ti, 0.098 Zr
ERM-EB393a	75.8	0.0039	(20.8)	0.0104	0.0143	0.00297	0.00021	0.00185	0.000019	0.000134	0.000093	3.35	0.0454	...	0.000061	0.000047 Se, 0.0000156 Cr
M394	57.70	0.232	...	1.93	0.1191	0.0399	0.00010	0.00141	0.00081	0.01001	0.00238	0.00053	0.00157	...	0.00070	<0.0002 Cr
M394a	57.64	0.174	...	1.92	0.1323	0.0386	0.00079	0.00125	0.00083	0.00959	0.00241	0.00058	0.00172	...	0.00073	0.00013 Cr
M396	65.49	0.0367	...	0.592	0.0235	0.0143	0.223	0.00445	0.00032	0.0590	0.00061	0.187	0.00089	...	0.00022	0.00012 Co, 0.00079 Cr
M397	...	3.99	1.96	0.229	...	0.336	0.00029	0.097	0.459	<0.0001 Se, <0.0001 Te
M397a	...	3.98	1.87	0.227	...	0.337	0.00020	0.097	0.45	<0.0001 Se, <0.0001 Te

Pure Copper Certified Reference Materials (M365a finely divided material – units of 100g; all others are 40mm dia. x 30mm discs, except M383d, M384c- M385a which are 38mm dia. x 30mm discs)

Mass fraction in µg/g, except where marked

BAM No.	Cu	Sn	Zn	Pb	Fe	Ni	Al	Mn	Bi	As	Sb	Si	P	S	Cd	Co	Cr	Ag	Se	Te	Mg	Ti	Zr
M365a*	99.73%	(29)	30	141	6.1	235	30.0	40.4	12.1	2.13	...	159	179	1.27
M381	Bal.	3.86	5.3	0.59	3.3	0.7	<1	0.22	<0.3	<0.5	<1	<3	...	3.2	<0.4	<0.3	<0.4	<1	<1	<0.3	<0.6	<0.3	<6
M382a	Bal.	4.7	7.6	2.2	10.3	2.7	<2	2.5	0.75	0.73	0.87	6.7	0.50	0.92	0.24	2.9	0.77	0.72	1.9	0.57	...
M383d	Bal.	3.8	1.08	7.8	22.4	4.7	<1	0.97	0.82	1.20	1.8	...	<1	3.5	0.62	1.30	0.77	10.2	...	0.47	1.7	1.2	<1
M384c	Bal.	0.6	1.0	7.2	33.0	5.7	<2	5.7	3.8	2.9	9.8	...	<1	4.0	5.0	4.0	...	14.8	2.9	6.1	1.8	<0.2	<0.3
M386a	Bal.	21.6	36.7	19.8	59.3	21.1	26.9	11.1	9.5	20.6	25.2	12	6.5	15.3	5.4	4.9	11.5	44.2	9.7	31.1	76.7	34.7	...
M390	Bal.	<0.1	0.79	1.3
M391	Bal.	<0.1	0.90	3.3
M392	Bal.	<0.1	0.80	7.0

*O=(1712) µg/g

Also available: 379/1, 379/2 and 379/3 which are certified for oxygen at 38 µg/g, 212 µg/g and 378 µg/g respectively (40mm dia. x 30mm discs).

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate.

Aluminium Alloy Certified Reference Materials (201-301 & M319 finely divided material – units of 100g; ERM-EB307a, EB312a, EB315a, M313a, M318, M320, M321 - M324 – approx. 65mm dia. x 30mm discs; M308a – approx. 60mm dia. x 30mm discs; 310 – approx. 60mm dia. x 25mm disc; ERM-EB316, M316a, EB317 & M325 – approx. 50mm dia. x 30mm discs)

BAM No.	Si	Mn	Fe	Cu	Ti	Zn	Mg	Pb	Al	Cr	Ni	V	Be	Bi	Ca	Cd	Li	Na	Sn	Zr	Ga	Sc
201	13.20	0.38	0.18	0.009	0.011	0.038	0.0024	...	Bal.
300	0.14	0.018	0.203	0.046	0.011	0.128	2.67	0.016	Bal.	0.23	<i><0.0005</i>
301	0.061	0.001	0.054	0.0016	0.005	0.033	0.0008	...	Bal.	0.0018	<i><0.0005</i>
ERM-EB307a	0.152	0.811	0.345	0.0939	0.0595	0.0690	4.80	0.0084	Bal.	0.1536	0.0097	0.0119	0.000537	...	0.00192	0.00326	0.00081	<i>0.00084</i>	0.0075	0.00319	0.0124	...
M308a	0.072	0.0343	0.164	1.36	0.0257	5.61	2.28	0.00436	Bal.	0.192	0.0147	...	0.00018	...	<i>0.00108</i>	0.00158	...	0.00873
310	0.080	0.003	0.070	0.0017	0.003	0.009	0.994	0.0035	Bal.	0.0009	0.002	0.0044	0.00013	...	0.00073	0.0024	0.00037	<i>0.0003</i>	0.0024	0.0014	0.0115	...
ERM-EB312a	0.403	0.0488	0.198	0.0509	0.0291	0.0297	0.379	0.00497	Bal.	0.0320	0.00407	0.00673	...	0.00180	<i>0.00169</i>	0.00167	0.00060	<i>0.00040</i>	...	0.00085	0.0129	...
M313a	0.346	0.486	0.388	0.0932	0.099	0.1481	3.35	0.00380	Bal.	0.117	0.0296	0.0308	0.00054	0.0092	0.00104	0.00047	0.00113	0.0025	0.0193	0.0355	0.01067	...
ERM-EB315a	9.88	0.311	0.621	2.46	0.142	0.801	0.446	0.077	Bal.	0.0274	0.0955	0.00470	0.000433	0.0036	...	0.00079	0.0764	0.00310	0.0089	...
ERM-EB316	11.98	0.204	0.1054	0.2970	0.0790	0.0611	0.045	0.0087	Bal.	0.00593	0.0235	0.0098	0.000295	0.0140	<i>0.00113</i>	0.00208	<i>0.0106</i>	0.00328	0.0105	...
M316a	11.87	0.0240	0.986	0.0290	0.0791	0.0593	0.0473	0.0089	...	0.00626	0.0251	0.00984	0.00046	0.0151	0.00179	0.00195	0.01005	0.00291	0.00954	...
ERM-EB317	0.0271	0.0912	0.112	1.77	0.0952	6.93	2.39	0.00481	Bal.	0.141	0.0359	0.0105	0.00101	0.0041	<i>0.00060</i>	0.0237	0.130	0.0183	...
M318	1.210	0.0908	0.246	0.0986	0.0238	0.0486	0.356	0.0056	Bal.	0.0208	0.00500	0.0104	0.00047	...	0.00091	0.00096	0.00060	0.00037	0.00206	0.00329	0.0189	...
M319	0.1043	0.371	0.291	0.0015	0.0030	0.0073	4.96	<i><0.001</i>	...	<i>0.060</i>	<i>0.037</i>	<i>0.0093</i>	...	<i><0.001</i>	...	<i><0.0002</i>	<i><0.001</i>	0.324	<i>0.015</i>	0.847
M320	0.197	0.699	0.206	0.147	0.102	0.252	3.98	0.00448	...	0.1044	0.00209	0.00759	0.00224	...	0.00119	0.00152	0.00091	0.0064	0.00456	0.102	0.0208	0.282
M321	0.0496	0.812	0.0495	4.38	0.0436	0.147	1.51	0.0099	...	0.0558	0.0504	0.0105	0.00049	0.0323	0.00052	0.0030	0.00058	0.00029	0.0286	0.1554	0.00880	0.0502
M323	0.696	1.310	0.475	0.200	0.0279	0.1053	0.226	0.0092	Bal.	0.1185	0.0293	0.0114	0.00072	0.00765	0.00199	0.00101	0.00181	0.00157	0.00927	0.0098	0.00577	...
M324	0.348	1.072	0.501	0.198	0.0370	0.176	1.201	0.00468	...	0.0258	0.00888	0.00915	0.00087	0.0009	0.00137	0.00454	0.00101	<i>0.0009</i>	0.00873	0.00195	0.0306	...
M325	6.83	0.0112	0.143	0.0197	0.117	0.0555	0.504	0.0104	...	0.00634	0.00478	0.00957	0.0026	0.0022	0.00083	<i>0.00135</i>	0.0183	0.00569	0.0191	...

ERM-EB307a also certified for Co: **0.00051%** and Sb: **0.0046%**, M308a for Ag: **0.00065%**, ERM-EB312a for Sr: **0.00111%**, ERM-EB315a for Sb: **0.0051%**, ERM-EB316 for Sr: **0.0260%**, M316a for Ag: **0.0184%**, Sb: **0.0047%** and Sr: **0.0298%**, ERM-EB317 for Ag: **0.0073%** and In: **0.0162%**, M324 for B: **0.00098%**, Co: **0.00489%**, Hg: **0.00072%**, Sb: **0.0042%** and Sr: **0.00173%**, M325 for Sb: **0.0037%** and Sr: **0.0301%**.

Lead Alloy Certified Reference Materials (Disc samples – dimensions as below)

BAM No.	Description	Disc Dimensions	Ca	Sb	As	Sn	Se	Bi	Ag	Al	Cu	Tl	Ni	Cd	Hg	Pt	S	Te	Zn
ERM-EB102a	PbCaSn	40mm dia. x 40mm	0.0635	<i>0.0004</i>	<i><0.0002</i>	1.01	...	0.00737	0.0170	0.0124	0.00013	0.00302	<i>(<0.0003)</i>	<i><0.00011</i>	<i><0.00005</i>
ERM-EB104	PbCaSn	40mm dia. x 40mm	0.0530	1.27	...	<i>0.0126</i>	<i>0.00293</i>
ERM-EB105	PbCaSn	40mm dia. x 40mm	0.0595	1.43	...	0.0133	0.00321
ERM-EB106	PbCaSn	40mm dia. x 40mm	0.0782	1.72	...	<i>(0.0135)</i>	<i>(0.00323)</i>
ERM-EB107	Pure Lead	40mm dia. x 40mm	0.00261	0.00113
ERM-EB108	Pure Lead	40mm dia. x 40mm	0.00260	0.00083
M109	Refined Lead	40mm dia. x 28mm	...	0.0098	0.0113	0.115	...	0.0193	0.00451	<i><0.00021</i>	0.00196	0.00030	0.00035	0.00353	0.00306	0.00318
M110	PbSb3	40mm dia. x 28mm	<i><0.0002</i>	3.08	0.107	0.131	0.0106	0.0126	0.00226	...	0.00064	<i><0.0001</i>	0.00038	<i><0.0001</i>
M112	Pure Lead	38mm dia. x 38mm	0.00052	0.00082	...	0.00053	0.00054	...	0.00053	...

Gold Alloy Certified Reference Materials (15.8mm dia. x 0.25mm discs)

BAM No.	Description	Au	Ag	Cu	Ni	Zn
ERM-EB506	Rose Gold	58.56	3.90	35.65	...	1.891
ERM-EB507	White Gold	75.10	3.02	14.69	4.99	2.107
ERM-EB508	Yellow Gold	75.12	24.90

Iron in Float Glass Certified Reference Materials (100mm x 50mm x 3.5mm plates)

BAM No.	Fe (total)	Fe(II)	Fe(II)	Fe(III)
S050	0.0084	0.0026	0.0037	0.0058
S051	0.0481	0.0155	0.0326	0.0326
S052	0.597	0.160	0.229	0.437

BUNDESANSTALT FÜR MATERIALFORSCHUNG UND - PRÜFUNG (BAM), Germany

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate.

High Purity Substances Certified Reference Materials (Finely divided material - units of 100g) Mass fraction in µg/g

BAM No.	Description	Cert. Date	CO ₂	H ₂ O	Ag	Al	As	B	Ba	Be	Bi	C	Ca	Cd	Ce	Cl
RS 1	SiO ₂ (>99.99%)	1991	8.7	<0.1	0.42	<0.05
RS 2	Al ₂ O ₃ (99.76%)	1994	...	2280	<i><0.5</i>	<i><5</i>	<i><0.5</i>	<i><0.2</i>	3.1	<i><0.2</i>	<i><0.1</i>	<i><10</i>
RS 3	CaCO ₃ (99.79%)	1994	43970	1320	...	<i><5</i>	...	<i><1</i>	45.3	<i><0.5</i>
RS 4	Ni (99.995%)	1996	<1	<1	<0.5	<i><2</i>	<i><2</i>	9.4	<1	<0.2
RS 5	NiO (Ni: 79.3%)	1996	...	150	<1	6	<0.2	...	<1	...	<i><1</i>	14	2.2	<0.2
RS 6A	MgO (Mg: 60.19%)	1997	...	110	...	46	<i><10</i>	<i><50</i>	994
RS 6B	MgO (Mg: 60.17%)	1997	...	283	...	49	<i><20</i>	<i><210</i>	956

BAM No.	Co	Cr	Cu	Fe	Ga	Ge	Hg	In	K	La	Li	Mg	Mn	Mo	N	Na
RS 1 (continued)	...	0.062	<0.1	0.62	...	<1	<0.05	...	0.48	...	0.25	<0.5	<0.2	<2
RS 2 (continued)	<1	<1.5	<2.5	3.3	<i><2</i>	<i><0.5</i>	<i><5</i>	<i><0.3</i>	<i><1</i>	<3	<1.5	<i><1</i>	...	<15
RS 3 (continued)	<i><1</i>	<1	<1	<5	<i><1.5</i>	<i><20</i>	<i><0.5</i>	...	183	3.0	47.5
RS 4 (continued)	<1	<0.5	<2	4.2	<0.2	...	<i><1</i>	<i><0.2</i>	<0.8	<0.5	<i><0.2</i>	2.5	<i><1</i>
RS 5 (continued)	<2	10	1.53	27	<0.5	<i><1</i>	<2	...	<i><2</i>	<1	<1	<5	...	<2
RS 6A (continued)	<i><5</i>	9.2	<i><6</i>	82	601900	5.4	<i><10</i>
RS 6B (continued)	<i><5</i>	8.1	<i><6</i>	80	601700	5.2	<i><10</i>

BAM No.	Ni	O	Pb	S	Sb	Se	Si	Sn	Sr	Te	Ti	Tl	V	W	Zn	Zr
RS 1 (continued)	<0.2	...	<0.15	1.3	<1.3	<0.1
RS 2 (continued)	<10	<20	<i><1</i>	<2	...	<i><1</i>	...	<2	3.2
RS 3 (continued)	<i><3</i>	...	<i><0.1</i>	<i><20</i>	<i><1</i>	173	...	<i><0.5</i>	<2	<i><0.2</i>
RS 4 (continued)	999950	29	<1	<2	<0.2	<1	<2	0.3	...	<i><0.2</i>	...	<0.2	<0.2	<0.1	<4	...
RS 5 (continued)	793000	207000	<2	<4	<i><0.1</i>	<1	<i><5</i>	<i><1</i>	<i><1</i>	<i><0.2</i>	<i><2</i>	<0.5	<1	<i><1</i>	3.4	<i><1</i>
RS 6A (continued)	3.9	...	<i><5</i>	2.0	...	1.3	...	8.4	...	<i><6</i>	<i><20</i>
RS 6B (continued)	3.3	...	<i><5</i>	2.1	...	1.2	...	7.8	...	<i><6</i>	<i><160</i>

Platinum Group Elements in Used Automobile Catalyst Certified Reference Material (Finely divided material - units of 200g) Mass fraction in µg/g

BAM No.	Pt	Pd	Rh
ERM-EB504b	1159	1128	314.2

Electronic Scrap Certified Reference Material (Finely divided material - units of 200g) Mass fraction in µg/g

BAM No.	Cu	Ni	Ag	Pb	Cr	Sn	Au	Pd	Pt	As	Be	Cd	In	Hg
M505a	167600	6940	633	11300	9800	4680	52.4	48.0	5.7	372	6.8	16.4	<i>43</i>	<i><5</i>

Tungsten Metal Powder Certified Reference Material (Finely divided material - units of 100g) Mass fraction in µg/g

BAM No.	Al	Ca	Co	Cr	Cu	Fe	K	Mg	Mn	Mo	Na	Ni	P	Si	Sn
S002	29.4	46	45	47.0	28.4	53	40.0	38.8	16.7	59	41	29	<i>7.2</i>	106	42

Glass Certified Reference Materials (Approx. 38mm dia. x 4mm discs) Mass fraction in %

BAM No.	Description	SiO ₂	Na ₂ O	CaO	MnO	Al ₂ O ₃	BaO	MgO	ZnO	SO ₃	K ₂ O	Cr ₂ O ₃	Fe ₂ O ₃	CuO	As ₂ O ₃	CdO	Co	NiO	P	PbO	Sb	Ti	Cr Total
S005c	Multielement	70.8	13.92	10.39	...	1.109	0.0114	2.28	0.0196	...	0.717	0.00158	0.0422	0.0107	0.00108
S006	Multielement	33.10	8.79	7.660	0.213	1.081	0.0456	1.163	<i>0.0061</i>	0.0201	0.577	0.382	0.468	<i>0.0026</i>	0.0009	0.000021	0.0172	0.00193	0.0085	0.0103	0.00108	0.0391	...

BNF - FULMER (BNF), UK

CHEMICAL COMPOSITION (nominal mass content in %)

Following the closure of the BNF-Fulmer organization in October 1992, BAS purchased their entire stock of non-ferrous spectroscopic reference materials and will continue to supply these until exhausted. Replacement samples are being produced by BAS in order to maintain continuity of these samples (see BAS Catalogue for details of such samples which are designated as CURMs).

Copper Base Reference Materials (Approx. 50mm dia x 10mm discs)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	Mg	S
C11.01-1	Copper Tin Binary Bronze	Bal.	3.4	0.01	<0.005	0.006	0.009	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.02	"	Bal.	5.5	0.02	<0.005	0.006	0.02	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.03	"	Bal.	7.4	0.01	<0.005	<0.005	0.04	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C11.04	"	Bal.	9.6	0.01	<0.005	<0.005	0.05	<0.005	<0.005	<0.005	<0.005	<0.005	<0.0005	<0.005	<0.001	<0.001
C30.01-2	Main Elements in Brass	51.48	<0.01	<0.01	Bal.	<0.005	...	<0.005	<0.005	<0.005	<0.005	<0.005	0.005	<0.002
C30.02-1	"	55.6	<0.01	<0.01	Bal.	<0.005	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002
C30.03-2	"	60.6	<0.01	<0.01	39.3	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002
C30.06-1	"	74.8	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002
C30.07-1	"	82.0	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002
C30.10-2	"	93.8	<0.01	<0.01	6.1	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002
C30.12-2	"	60.85	<0.01	<0.01	Bal.	0.52	...	<0.005	<0.005	0.90	<0.005	<0.005	<0.002	<0.005
C30.13-1	"	60.6	<0.01	<0.01	Bal.	<0.01	...	<0.005	<0.005	1.9	<0.005	<0.005	<0.002	<0.002
C30.14-2	"	60.5	<0.005	<0.01	Bal.	1.0	...	<0.01	<0.005	2.4	<0.005	<0.005	<0.005	<0.005
C30.15-1	"	60.6	<0.01	<0.01	Bal.	<0.01	...	0.55	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002
C30.16-1	"	61.2	<0.01	<0.01	Bal.	<0.01	...	0.90	<0.005	<0.005	<0.005	<0.005	<0.002	<0.002
C30.17-2	"	61.6	<0.01	0.01	Bal.	0.01	...	1.4	<0.005	<0.005	<0.005	<0.005	<0.005	<0.005
C30.18-1	"	64.36	0.65	<0.01	Bal.	<0.005	...	<0.005	0.10	<0.005	<0.005	<0.005	<0.003	2.91
C30.19-1	"	69.9	1.07	<0.01	Bal.	<0.01	...	<0.005	<0.005	<0.005	<0.005	<0.01	<0.002	4.65
C30.21-1	"	56.0	1.96	<0.005	Bal.	<0.005	...	<0.005	0.18	<0.005	<0.005	<0.01	...	1.44
C30.22-2	"	58.28	0.009	1.05	Bal.	<0.01	...	0.006	<0.005	<0.005	0.011	<0.012	<0.005	<0.003
C38.01-1	Impurities in Brass	61	0.20	0.20	Bal.	0.01	...	0.01	<0.0005	0.009	0.03	0.02	<0.0005	0.003
C38.02-1	"	61	0.10	0.10	Bal.	0.03	...	0.09	0.01	0.14	0.06	0.06	0.005	0.004
C38.03-1	"	61	0.05	0.06	Bal.	0.13	...	0.05	0.07	0.07	0.08	0.08	0.008	0.07
C38.04-1	"	61	0.02	0.03	Bal.	0.06	...	0.04	0.12	0.22	0.04	0.12	0.008	0.02
C38.05-1	"	61	0.01	0.02	Bal.	0.19	...	0.008	0.14	0.02	0.01	0.01	0.01	0.12
C38.06-1	"	61	<0.005	0.002	Bal.	<0.005	...	<0.005	<0.0005	<0.001	<0.001	<0.002	<0.0005	<0.001

BNF – FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Copper Base Reference Materials (Approx. 50mm dia x 10mm discs)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	P	Fe	Si	Mn	As	Sb	Bi	Al	Mg	Co	S	Cr	Ag	Cd
C42.21-1	Admiralty and Naval Brass	66.1	0.54	0.23	Bal.	0.096	0.081	0.06	0.081	<0.005	<0.005	0.19	0.012	0.005	0.007
C42.25	"	58.5	2.2	<0.01	Bal.	<0.005	0.06	<0.005	<0.002	0.13	0.10	<0.005	<0.002	0.02	0.001
C43.03-1	Aluminium Brass	80.0	<0.01	0.11	Bal.	<0.003	...	0.044	<0.005	<0.002	<0.005	<0.01	<0.005	1.41
C48.03-1	Cartridge Brass	70.45	0.047	0.054	Bal.	0.030	<0.001	<0.001	<0.002	0.040	0.079	0.097	0.029	0.007	0.001	...	0.004	0.0005	...	0.013
C48.06	"	71.6	0.03	0.02	Bal.	0.11	0.002	0.02	0.006	0.006	0.008	0.006	0.004	0.002	0.001	...	0.006	0.0006	...	0.008
C51.12-2	Aluminium Bronze	Bal.	0.18	0.25	0.42	0.11	<0.005	2.90	<0.01	1.25	0.11	6.06
C51.13-2	"	Bal.	0.19	0.12	0.30	0.053	0.021	2.05	0.16	0.77	0.21	6.93
C52.51-3	Aluminium Bronze	Bal.	<0.01	<0.01	0.02	5.1	...	4.3	<0.01	<0.01	10.0	<0.01	<0.01
C52.56-3	"	Bal.	0.11	0.17	0.28	5.6	...	4.6	0.15	0.74	8.9	0.09	0.14
C54.01-3	Phosphor Bronze	Bal.	3.2	0.29	0.31	0.26	0.05	0.01	0.006	0.13	0.04	0.08	...	0.009	<0.001	...	0.03
C62.11-2	Cupro-Nickel	Bal.	0.04	<0.005	0.097	29.8	...	0.60	0.36	0.52	0.03	<0.005	<0.005
C62.14-2	"	Bal.	0.12	0.01	0.12	20.2	...	1.49	0.022	0.24	0.002	0.03	0.083
C62.15-2	"	Bal.	0.03	0.016	0.04	25.9	...	2.36	0.014	0.23	0.004	0.042	0.023
C65.27-1	Nickel Silver	57.0	0.01	0.04	28.7	13.9	0.02	0.26	<0.002	0.13	<0.01	...	0.03
C65.28-1	"	56.9	0.15	0.06	26.7	15.3	0.07	0.13	0.01	0.57	0.01	...	0.03

BNF - FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Nickel Base Alloy Reference Materials (Approx. 28.6mm dia. x 25mm discs)

BNF No.	Description	C	Si	Cu	Fe	Mn	Cr	Ti	Al	Co	Mo	Mg	Ni
B6998	MONEL Alloy 400	0.09	0.04	31.3	2.30	0.29	0.02	0.11	0.008	0.025	...	0.079	Bal.
B7000	"	0.05	0.11	31.5	0.64	0.87	0.035	0.03	0.028	0.50	...	0.026	Bal.
B7001	"	0.01	0.28	31.4	0.32	1.66	0.05	0.025	0.040	0.25	...	0.010	Bal.
B7002	"	0.015	0.15	31.7	0.13	2.65	0.10	0.015	0.060	0.10	...	0.007	Bal.
E3918	NIMONIC Alloy 75	0.05	1.14	0.005	1.57	0.85	19.4	0.72	0.25	0.22	0.49	0.058	Bal.
E3919	"	0.07	0.89	0.055	2.62	0.47	19.6	0.40	0.15	1.00	0.25	0.040	Bal.
E3920	"	0.07	0.57	0.11	3.02	0.28	19.2	0.35	0.13	2.02	0.095	0.020	Bal.
E3921	"	0.11	0.34	0.27	3.50	0.14	19.4	0.20	0.045	0.53	0.05	...	Bal.
E3922	"	0.14	0.16	0.50	3.98	0.10	19.2	0.08	0.035	0.115	0.03	0.014	Bal.
B7004	NIMONIC Alloy 80A	0.01	0.17	0.14	0.97	0.08	19.6	2.63	1.64	0.06	0.06	0.002	Bal.
B7005	"	0.035	0.23	0.045	0.32	0.16	19.6	2.52	1.55	1.04	0.10	0.005	Bal.
B7006	"	0.08	1.03	0.075	0.61	0.25	19.6	2.14	1.19	0.35	0.20	0.008	Bal.
B7007	"	0.14	0.66	0.22	0.22	0.53	19.4	2.31	1.36	0.15	0.39	0.019	Bal.
B7008	"	0.21	0.36	0.025	0.19	0.02	19.3	2.33	1.46	2.00	<0.01	0.030	Bal.
B7011	NIMONIC Alloy 90	0.095	1.02	0.065	0.34	0.16	19.7	2.05	1.20	17.0	0.20	0.010	Bal.
B7012	"	0.16	0.39	0.11	0.25	0.53	19.6	2.28	1.25	17.0	0.39	0.018	Bal.
B7013	"	0.22	0.65	0.20	0.22	0.06	19.6	2.39	1.46	17.0	<0.01	0.030	Bal.

BNF - FULMER (BNF), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Nickel Base Alloy Reference Materials (Approx. 28.6mm dia. x 25mm discs)

BNF No.	Description	C	Si	Cu	Fe	Mn	Cr	Ti	Al	Co	Mg	Mo	Nb	Ni
E3923	INCOLOY Alloy 800	0.01	0.17	0.54	Bal.	1.00	20.6	0.29	0.57	0.06	...	0.51	...	32.0*
E3924	"	0.03	0.30	0.29	Bal.	0.85	20.6	0.30	0.28	0.13	...	0.26	...	32.3*
E3925	"	0.08	0.41	0.14	Bal.	0.68	20.8	0.28	0.24	0.28	...	0.10	...	32.2*
E3926	"	0.06	0.60	0.085	Bal.	0.50	20.2	0.39	0.08	0.54	...	0.05	...	32.0*
E3927	"	0.08	0.75	0.055	Bal.	0.40	20.4	0.58	0.10	1.02	...	0.025	...	32.1*
E3928	INCOLOY Alloy DS	0.10	1.77	0.05	Bal.	1.44	18.2	0.24	0.115	1.01	...	0.025	...	36.5*
E3929	"	0.085	1.80	0.085	Bal.	1.30	17.9	0.14	0.07	0.52	...	0.055	...	36.3*
E3930	"	0.08	2.09	0.135	Bal.	1.18	18.6	0.065	0.03	0.26	...	0.105	...	36.2*
E3931	"	0.05	2.32	0.28	Bal.	1.06	18.5	0.035	0.015	0.12	...	0.25	...	36.4*
E3932	"	0.04	2.50	0.55	Bal.	0.93	18.5	0.025	0.01	0.07	...	0.49	...	36.4*
B5789	INCONEL Alloy 600	...	0.61	0.24	6.10	0.39	16.5	0.52	0.09	0.60	0.017	Bal.
B5871	"	...	0.88	0.02	6.34	0.57	16.0	0.27	0.18	1.09	0.013	Bal.
B5967	"	...	0.45	0.41	7.18	0.23	16.0	0.28	0.09	0.31	0.038	Bal.
B5968	"	...	0.22	0.80	8.05	0.12	16.0	0.11	0.03	0.18	0.059	Bal.
B7047	INCONEL Alloy X-750	0.035	0.17	0.49	5.51	1.29	15.0	2.71	0.49	0.58	1.36†	Bal.
B7048	"	0.075	0.23	0.30	6.09	1.00	15.1	2.52	0.71	0.30	1.18†	Bal.
B7049	"	0.09	0.33	0.155	7.08	0.81	15.0	2.30	0.91	0.20	0.97†	Bal.
B7050	"	0.125	0.44	0.075	8.09	0.61	15.0	2.27	1.01	0.10	0.77†	Bal.

(MONEL, NIMONIC, INCOLOY and INCONEL are all trade marks of Special Metals Corporation)

† Samples contain less than 0.01% Ta

Lead Base Alloy Reference Material (Approx. 50mm square x 20mm blocks)

BNF No.	Description	Cu	Sn	Pb	Zn	Ni	Cd	Sb	Bi	Ca	Ag
L21.02-1	Battery Alloy	0.0013	0.27	Bal.	0.0016	≤0.0002	≤0.0002	0.0003	0.01	0.03	0.008

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

C, S, N, H & O in Steel Reference Materials (CSN 2-1 and CSN 2-2 are 500 x 1g pins; CSN 2C and CSN A are 100g of finely divided material)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	H	V	O	Ca	Sn	Ti	Co	N
BS CSN 2-1	0.476	(0.03)	(0.4)	(0.004)	0.034	(16.8)	(0.5)	(0.2)	0.064
BS CSN 2-2	0.548	(0.03)	(0.4)	(0.004)	0.028	(16.8)	(0.5)	(0.2)	0.076
BS CSN 2C	0.469	0.17	0.60	0.012	0.0305	0.072	(0.006)	0.071	0.046	0.073	...	0.004	...	0.0033	(0.006)	0.002	(0.006)	0.0173
BS CSN A	0.068	(0.05)	(1.0)	(0.14)	0.305	(0.06)	...	(0.05)	...	(0.06)	0.0081

Calcium Treated Carbon Steel Reference Materials (38-41mm dia. x 19-30mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Ni	Mo	Al	As	B	Ca	Co	Cu
BS 1018	0.195	0.237	0.79	0.012	0.024	0.177	0.104	0.044	0.029	0.0041	(0.0002)	(0.0004)	0.0058	0.130
BS 9325B	0.254	0.38	0.504	0.032	0.0067	1.22	3.13	0.203	0.027	0.0033	(0.0003)	(0.004)	0.0073	0.166
BS HiCal-1	0.271	1.29	1.00	(0.007)	0.0007	1.55	3.28	0.379	0.070	0.0022	(0.0001)	0.0140	0.0024	0.152

BRAMMER No.	Fe	Mg	Nb	N	O	Pb	Sb	Sn	Ta	Ti	V	W	Zr
BS 1018 (continued)	98.2	(0.0003)	(0.0006)	0.0079	0.0014	(0.0006)	(0.001)	0.0099	...	0.0009	0.0009	0.0014	(0.001)
BS 9325B (continued)	94.0	(0.005)	(0.002)	0.0112	0.011	0.0019	(0.05)	(0.002)	(0.003)	0.0020	0.0080	0.0036	0.0010
BS HiCal-1 (continued)	91.9	(0.0003)	(0.002)	(0.0005)	...	(0.0002)	...	0.0037	0.0027	(0.0009)	(0.0008)

Calculated by difference

High Manganese Steel Reference Materials (32mm dia. x 17mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Nb	Sn	Ti	V
BS 17A	0.588	0.22	19.38	0.043	0.005	1.37	0.52	0.060	0.052	(0.0001)	0.013	0.135	0.038	0.06	0.012	(0.002)	0.016
BS 19A	1.57	1.46	8.76	0.092	0.009	3.75	1.97	1.48	0.057	(0.0005)	0.014	0.51	0.039	0.040	0.037	(0.007)	0.10

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Stainless and High Temperature Steel Reference Materials (37-44mm dia. x 10-19mm discs)

BRAMMER No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Ca	Co	Cu	N	O	Nb	Sn	Ti	V	W	Others
BS 17-4PHC	0.033	0.399	0.81	0.022	0.027	15.40	0.45	4.24	0.0023	0.0026	0.0007	0.077	3.23	0.027	0.010	0.258	0.0100	(0.001)	0.090	0.121	0.0043 As 74.8 Fe (0.0001) Pb (0.002) Zr
BS 82E	0.062	0.58	1.61	0.027	0.001	22.38	0.31	12.49	0.006	0.0024	0.0014	0.12	0.26	0.072	...	0.062	0.006	0.003	0.064	0.041	...
BS 83G	0.073	0.56	1.66	0.024	0.004	24.50	0.085	19.15	(0.004)	(0.0001)	...	0.153	0.114	0.026	0.0064	0.061	0.003	(0.003)	0.077	0.007	...
BS 85D	0.048	0.54	1.69	0.024	0.024	17.09	0.59	9.98	0.13	(0.001)	0.0004	0.97	0.45	(0.02)	(0.002)	0.062	0.0062	0.48	0.132	(0.07)	(0.01) As (0.001) Sb
BS 86F	0.054	1.22	1.30	0.021	0.0011	18.74	0.24	34.99	(0.007)	0.0026	(0.001)	0.098	0.23	0.035	...	0.19	0.004	(0.006)	0.061	(0.03)	(0.003) As (0.001) Pb
BS 87F	0.055	0.67	1.64	0.024	0.025	17.30	0.29	10.12	0.004	(0.0006)	0.0007	0.17	0.28	0.037	0.005	0.57	0.004	0.004	0.13	0.050	0.005 As
BS 90F	0.085	0.58	0.53	0.023	0.328	13.01	0.14	0.30	(0.006)	0.021	0.12	0.037	0.011	0.011	0.005	(0.002)	0.076	0.032	...
BS 94C	0.057	0.62	0.45	0.024	0.002	25.90	0.20	0.43	0.004	(0.0005)	0.0008	0.042	0.056	0.065	0.0061	0.032	0.006	...	0.12	(0.03)	...
BS 180B	0.022	0.46	4.65	0.017	0.0008	21.5	2.20	11.9	(0.007)	0.0011	0.0009	0.111	0.201	0.315	0.0043	0.131	0.0040	(0.005)	0.149	0.050	58.5 Fe
BS 181B	0.070	3.94	8.07	0.021	0.0009	16.17	0.173	8.18	0.0119	(0.0008)	(0.001)	0.044	0.206	0.158	0.0010	0.026	(0.004)	0.0051	0.044	0.016	62.8 Fe
BS 183A	0.172	0.37	0.35	0.016	0.0040	12.14	0.12	1.85	0.002	(<0.0005)	0.0020	0.036	0.093	0.0256	0.0065	0.006	0.003	0.002	0.090	2.60	(0.002) As
BS 184A	0.035	0.080	0.06	0.007	0.001	12.66	2.20	8.34	1.00	(0.0004)	(0.0003)	0.036	0.041	0.0045	(0.0003)	(0.006)	(0.002)	0.051	0.014	0.032	(0.002) Ta
BS 185A	0.033	0.38	0.49	0.022	0.002	14.46	0.30	4.43	0.002	0.0017	(0.0002)	0.026	3.41	0.027	(0.0021)	0.32	0.007	(0.001)	0.048	(0.014)	(0.002) Ta
BS 187B	0.013	0.63	0.77	0.021	0.0021	19.8	2.07	33.8	0.0033	0.0013	(0.0003)	0.191	3.13	0.0185	0.0019	0.335	0.0042	0.0028	0.086	0.047	0.0005 Pb 0.0008 Ta
BS 188B	0.046	0.266	0.247	0.016	(0.0007)	14.32	1.30	24.81	0.168	0.0047	(0.00003)	0.274	0.120	0.0021	0.0006	0.099	0.0051	2.20	0.264	0.043	0.0045 As 55.8 Fe
BS 189A	0.0147	0.30	0.639	0.019	(0.001)	20.4	6.04	23.8	0.0129	(0.0002)	(0.0004)	0.100	0.184	0.198	0.0024	0.13	0.0035	0.0065	0.054	0.037	0.0039 As (0.001) Zr
BS 316F	0.015	0.55	1.46	0.029	0.026	16.79	2.10	10.09	(0.002)	0.0019	0.0018	0.126	0.437	0.061	0.0055	0.011	0.0092	0.011	0.062	0.045	0.0067 As 68.1 Fe
BS 430	0.061	0.37	0.71	0.024	0.002	16.5	0.052	0.22	<0.05	<0.005	<0.005	<0.5	0.12	0.06	(0.006)	0.01	0.009	<0.05	0.057	<0.05	0.0045 As 81.7 Fe
BS 9841	0.067	0.54	1.69	0.024	0.024	24.30	0.57	19.55	(<0.006)	0.0026	(0.0002)	0.116	0.356	0.064	(0.011)	0.070	0.006	(0.002)	0.070	0.06	(0.006) Sb
BS 9842	0.059	0.99	1.50	0.025	0.0016	24.19	0.111	20.02	0.014	0.0025	0.0010	0.237	0.147	0.037	(0.0044)	0.026	0.005	0.003	0.075	0.011	(0.002) As
BS 9941	0.021	0.33	1.78	0.027	0.024	18.48	3.24	13.68	0.004	0.0025	(0.0003)	0.178	0.424	0.036	(0.0058)	0.015	0.007	(0.002)	0.062	0.068	(0.010) As
BS 9942	0.021	0.49	1.84	0.025	0.006	18.21	3.30	13.55	0.004	0.0014	0.0014	0.086	0.305	0.071	(0.0023)	0.005	0.006	(0.002)	0.072	0.032	(0.004) As

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Nickel Base Alloy Reference Materials (Disc samples – dimensions as below)

Brammer No.	Description	Disc Dimensions mm	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Pb	Sn	Ti	V	W	Fe	Mg	Others
BS 200-1	Nickel 200	38 dia. x 15	0.0413	0.037	0.111	0.0009	0.0011	0.0011	0.0004	99.60	0.0048	0.0033	0.089	0.0077	0.0004	0.0010	(0.0001)	0.0209	0.0008	0.00016	0.046	0.0307	0.0015 O
BS 200-2	"	"	0.050	0.060	0.244	0.0020	0.0068	0.0094	0.0005	99.31	0.0041	0.0031	0.104	0.053	0.0009	0.0006	(0.0002)	0.0197	0.0014	(0.0003)	0.115	0.0368	0.0025 O
BS 200-3	"	"	0.0145	0.0110	0.157	0.0015	0.0032	0.0091	0.0004	99.4	0.0068	0.0037	0.103	0.108	0.0004	0.0008	0.0003	0.0235	0.0009	(0.0004)	0.138	0.0240	0.0026 O
BS 200-4	"	"	0.107	0.101	0.310	0.0023	0.0076	0.132	0.0013	98.9	0.0057	0.0037	0.0911	0.0482	0.0010	0.00087	0.00020	0.0191	0.0024	0.00095	0.297	0.0312	0.0015 O
BS 600-2	Nickel 600 Alloy	38 dia. x 20	0.071	0.23	0.31	0.006	0.004	16.36	0.007	75.34	0.16	0.0098	0.10	0.089	(0.02)	(<0.002)	(0.002)	0.37	0.028	...	6.80	0.012	0.030 N
BS 600-3	"	"	0.020	0.19	0.28	0.008	0.005	14.77	0.007	75.05	0.09	0.0082	0.10	0.24	(0.02)	(0.001)	(0.002)	0.20	0.020	...	8.88	0.012	0.0081 N
BS 600-4	"	"	0.034	0.22	0.20	0.007	0.004	14.72	(0.002)	75.88	0.06	0.0060	0.09	0.08	(0.015)	(<0.001)	(0.002)	0.20	0.023	...	8.40	0.020	0.021 N
BS 600-5	"	38 dia. x 19	0.047	0.26	0.21	0.005	<0.002	15.59	0.049	74.83	0.19	0.0018	0.029	0.10	(0.03)	(<0.001)	(<0.003)	0.23	0.054	...	8.36	0.004	0.011 N
BS 600-6	"	"	0.083	0.31	0.21	0.007	0.001	14.86	0.12	76.00	0.278	0.0028	0.066	0.24	0.14	(<0.001)	(<0.003)	0.24	0.030	...	7.33	0.022	0.0078 N 0.0012 O
BS 800A	Cr/Fe Nickel Alloy	38 dia. x 19	0.075	0.361	0.883	0.013	(0.0007)	21.09	0.117	33.3	0.362	0.0018	0.069	0.244	0.021	(0.001)	0.0041	0.526	0.058	(0.030)	42.7	0.0022	0.0126 N 0.0014 O
BS 197A	Ra 333 Alloy	38 dia. x 19	0.050	0.96	1.56	0.021	(<0.001)	25.11	2.99	44.44	0.185	0.0019	3.06	0.119	0.20	(0.0002)	...	0.017	0.051	2.80	18.07	(0.0030)	(0.052) N
BS 718D	In 718 Alloy	"	0.037	0.072	0.100	0.0083	0.0004	18.32	3.00	52.5	0.631	0.0041	0.368	0.071	5.16	(0.00006)	0.0020	0.93	0.038	0.049	18.51	0.0038	0.0011 As 0.0084 N 0.0015 O
BS 825F	Nickel Alloy 825	"	0.012	0.59	0.521	0.018	(0.005)	23.2	3.19	38.9	0.081	0.0023	0.064	1.78	(0.02)	(0.0008)	0.0036	0.91	0.086	0.015	30.7	0.0013	0.0085 N 0.0009 O
BS 400D	Monel Alloy	"	0.130	0.146	0.993	(0.0010)	0.0006	0.0057	0.0024	63.4	0.0231	0.0009	0.032	33.0	(0.0001)	0.0004	0.00012	0.064	(0.0002)	0.0004	2.00	0.0217	0.00017 N 0.0008 O 0.0003 Zr
BS 400-1	"	38 dia. x ~18	0.109	0.16	1.07	0.022	0.008	0.033	0.001	66.0	0.004	(0.0005)	0.37	30.97	0.0003	0.0020	0.0010	0.007	(0.001)	...	1.27	0.048	0.004 As
BS 400-2	"	"	0.170	0.17	1.17	0.027	0.008	0.091	0.0012	65.9	0.006	(0.0006)	0.46	30.75	0.0004	(0.001)	0.0012	0.011	(0.003)	...	1.42	0.033	0.004 As
BS 400-3	"	"	0.153	0.063	0.85	0.026	0.006	0.21	0.003	65.4	0.001	(0.0002)	0.46	31.25	(0.0004)	(0.0015)	0.0014	0.004	0.003	...	1.60	0.012	0.004 As
BS 500E	"	38 dia. x 19	0.134	0.148	0.605	0.0022	0.0006	0.0174	0.0044	64.7	2.94	0.0017	0.017	29.9	(0.002)	(0.0008)	(0.0008)	0.607	(0.001)	(0.002)	0.722	0.0058	0.0005 O 0.0133 Zr
BS H1C	Hastelloy (B-2)	"	0.0022	(0.01)	0.51	0.0049	(0.0004)	0.70	27.2	69.8	0.15	(0.001)	(0.01)	(0.002)	(0.009)	(0.00002)	(0.002)	(0.008)	(0.02)	(0.009)	1.29	(0.0012)	(0.001) As (0.009) Ta
BS H2E	" (C-276)	32 dia. x 19	0.0030	0.030	0.55	0.005	0.00045	15.85	15.98	58.3	0.35	0.0028	0.032	0.0070	(0.009)	(0.002)	(0.001)	0.007	0.15	3.28	5.41	0.0019	0.0119 N 0.0005 O
BS H3C	" (x)	38 dia. x 19	0.087	0.36	0.492	0.0150	(0.0003)	21.50	8.82	46.6	0.149	0.0020	1.37	0.106	0.095	...	0.0019	(0.0064)	0.047	0.623	19.54	0.0020	0.0266 N 0.0013 O
BS H6B	" (C-22)	"	(0.008)	(0.035)	0.226	0.0054	0.0005	22.3	14.05	55.9	0.23	0.0016	0.079	0.035	(0.1)	...	(0.0007)	0.050	0.0063	3.20	3.45	0.0010	0.0118 N 0.0007 O

BS 200-1 to 200-4 also certified for As and Ca, plus some for N, Sb and Ta

BRAMMER STANDARD COMPANY, Inc. (BS), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Copper Base Alloy Reference Materials (38-41mm dia. x 12-19mm discs)

BRAMMER No.	Cu	Pb	Sn	Zn	Mn	Al	Fe	Ni	P	As	Si	Sb	C	S	Others
BS 464A (Wrought)	60.6	0.056	0.62	38.73	0.0002	(0.001)	0.013	0.004	0.012	<0.002	<0.01	(0.001)	(0.0006)	(0.001)	...
BS 482A (Wrought)	60.0	0.50	0.65	38.8	<0.002	(0.003)	0.020	(0.007)	<0.003	<0.002	(0.002)	0.0012	(0.0015)	<0.002	...
BS 510B (Wrought)	95.0	0.0112	4.6	0.251	0.0004	(0.006)	0.009	0.0211	0.074	0.0010	(0.003)	(0.002)	0.0010	0.007	(0.0001) N, 0.0009 O
BS 544B (Wrought)	88.2	3.9	4.06	3.51	(0.0009)	(0.0009)	0.087	0.068	0.0258	0.0043	0.0042	0.0244	0.0031	0.0249	0.0173 Ag, 0.0005 O
BS 623A (Wrought)	88.13	0.001	0.002	0.008	0.273	9.12	2.19	0.146	<0.002	(0.006)	0.014	<0.002	(0.002)	(<0.0005)	...
BS 630C (Wrought)	80.7	0.0093	0.0152	0.234	0.325	9.90	3.82	4.82	0.0043	0.0007	0.064	0.0003	0.0060	(<0.0005)	0.0019 Co, 0.0030 Cr 0.0011 Mg
BS 655A (Wrought)	95.74	0.008	0.07	0.02	0.91	(0.002)	0.075	0.008	(0.004)	<0.002	3.14	<0.002	(0.0006)	(0.0003)	...
BS 675A (Wrought)	58.5	0.074	0.80	39.1	0.32	<0.002	1.12	0.019	0.010	0.003	(0.005)	0.0011	(0.0007)	(0.0005)	...
BS 706B (Wrought)	87.00	0.006	0.006	0.054	0.61	<0.003	1.56	10.9	0.009	<0.0005	<0.002	<0.002	(0.004)	0.009	0.005 Co
BS 715A (Wrought)	68.0	(0.007)	0.008	0.10	0.82	(0.01)	0.61	30.22	0.006	(0.0014)	0.10	(0.003)	0.03	0.001	...
BS 903E (Cast)	87.0	0.100	8.63	4.11	...	(0.001)	0.0072	0.293	0.056	(0.002)	(0.0018)	0.010	(0.002)	0.0092	(0.007) O
BS 905A-1 (Cast)	87.3	0.030	10.25	2.27	(<0.0003)	(<0.003)	0.015	0.018	0.055	(0.001)	(<0.004)	0.004	(0.002) Ag
BS 938-1 (Cast)	77.1	14.8	7.16	0.26	(0.001)	(<0.002)	(0.015)	0.49	(0.059)	(0.004)	(<0.004)	0.033	...	0.009	0.0048 Ag
BS 954B (Cast)	83.9	0.047	0.07	0.10	0.27	10.20	3.90	1.38	0.012	(0.005)	0.07	(0.001)	(0.005)	(<0.0005)	0.003 Ag
BS 955C (Cast)	80.6	0.003	0.003	0.15	0.06	10.68	4.04	4.31	0.012	(<0.002)	0.025	(<0.002)	0.014 Ag

Cobalt Base Reference Materials (38mm dia. X 19mm discs)

BRAMMER No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	N	Nb	Ti	V	W	Fe	O	La
BS 171C	Stellite 25	0.119	(0.1)	1.47	(0.008)	(0.0008)	20.3	(0.08)	10.1	(0.04)	(0.004)	51.2	(0.02)	0.0045	(0.006)	(0.07)	(0.009)	15.3	1.07	(0.002)	(0.030)
BS 171D	Stellite 25	0.120	(0.1)	1.47	(0.01)	(0.0009)	20.2	(0.08)	10.1	(0.05)	(0.004)	51.2	(0.02)	0.0046	(0.006)	(0.05)	(0.01)	15.3	1.07	(0.0008)	(0.02)
BS 172B	Stellite 188	0.055	0.33	0.97	(0.008)	(0.0009)	22.8	0.28	22.5	0.21	(0.004)	34.8	(0.02)	0.033	0.042	0.079	0.0081	15.2	2.46	0.0011	0.059

CANADA CENTRE FOR MINERAL AND ENERGY TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Base Metal Ore Certified Reference Materials (Finely divided material – units of 200g)

CANMET No.	Description	Si	Al	S	Fe	K	Na	Ca	As	Mg	C	Cd	Pb	Cu	Ti	W
BH-1	Tungsten Ore	38.0	3.5	0.8	3.2	0.7	0.1	0.5	...	0.4	0.1	0.4	0.422
CD-1	Antimony Ore	32.9	5.5	3.1	2.8	1.8	0.1	1.4	0.66	0.6	0.21	...	0.02	<0.01
CT-1	Tungsten Ore	17.2	2.9	8.2	17.5	0.7	0.2	12.2	...	2.0	1.7	0.2	1.04
HV-2a	Copper-Molybdenum Ore	31.34	7.96	0.344	2.044	2.31	2.335	1.891	0.00121	0.329	(0.4)	(0.2)	0.00069	0.3808	0.0000128	0.000789
MP-1b	Zinc-Tin-Copper-Lead Ore	16.79	3.46	13.79	8.19	(0.2)	...	2.47	2.30	0.024	(0.028)	0.0527	2.091	3.069	0.075	(0.11)
MP-2a	Tungsten-Molybdenum Ore	31.2	5.99	0.716	5.00	1.226	(0.03)	3.22	0.558	0.0923	...	0.00145	0.277	0.0459	0.0268	0.338
OKA-1	Niobium Ore	2.4	0.9	0.6	2.8	0.3	0.2	31.3	...	1.3
TAN-1	Tantalum Ore	33.42	8.2	...	0.2	1.5	4.6	0.5	...	0.02
TLG-1	Tungsten Ore	21.5	3.0	...	8.6	0.4	0.2	16.6	...	2.7	1.4	0.1	0.083

(Continued from above)

CANMET No.	Bi	Cr	Mn	Mo	P	Zn	Zr	Sr	In	Nb	Ta	Sn	Sb	Ag	H ₂ O (105°C)	LOI
BH-1 (continued)	0.2	0.02
CD-1 (continued)	3.57	...	0.2	4.0
CT-1 (continued)	0.7	0.03
HV-2a (continued)	0.000158	0.0100	0.0545	0.01254	0.0427	0.00565	0.00658	0.00123	...	(0.0002)	(0.00002)	(0.00012)	0.000689	0.0001448	(0.3)	3.01
MP-1b (continued)	0.0954	...	(0.048)	0.0285	(0.02)	16.67	0.056	1.61	0.0054	0.00470
MP-2a (continued)	0.0989	0.0150	0.1018	0.1586	...	0.566	0.0134	0.00123	0.001209	0.0097	0.0016	0.0537	0.00078	0.000482	...	(4)
OKA-1 (continued)	1.1	...	1.1	0.05	...	1.0	...	0.37	31.9
TAN-1 (continued)	0.02	0.02	0.236	0.01
TLG-1 (continued)	1.3	<0.01	1.6	...

HV-2a also certified for Ba: **869** µg/g, Ce: **19.1** µg/g, Co: **3.40** µg/g, Cs: **2.70** µg/g, Dy: **1.126** µg/g, Er: **0.646** µg/g, Gd: **1.40** µg/g, La: **9.1** µg/g, Nd: **8.77** µg/g, Ni: **6.47** µg/g, Rb: **48.3** µg/g, Sm: **1.69** µg/g, Th: **1.28** µg/g and U: **1.08** µg/g.

MP-2a also certified for Ba: **12.3** µg/g, Ce: **357** µg/g, Co: **5.50** µg/g, Cs: **5.78** µg/g, Dy: **32.5** µg/g, Gd: **24.8** µg/g, Hf: **9.40** µg/g, La: **157** µg/g, Li: **81** µg/g, Lu: **4.36** µg/g, Nd: **117.9** µg/g, Rb: **229** µg/g, Sc: **4.87** µg/g, Sm: **26.7** µg/g,

Tb: **4.82** µg/g, Th: **61.3** µg/g, Tm: **4.10** µg/g, U: **37** µg/g and Yb: **28.8** µg/g.

Noble Metal Ore, Concentrate and Matte Certified Reference Materials

(Finely divided material – CH-4, MA-1b, MA-3a, PTC-1b and SU-1b in units of 200g, GTS-2a in units of 350g, DS-1, MA-2c, PTA-1 and UMT-1 in units of 400g)

CANMET No.	Description	Si	SiO ₂	Fe	Al	Ca	K	Na	S	Mg	Ni	Cu	Co	Pb	Ag	As	Pd	Pt	Au	Rh	C	Zn	H ₂ O	LOI
CH-4	Gold Ore	...	62.75	5.32	7.73	1.96	1.80	3.18	0.65	1.40	0.0051	0.20	0.0026	(0.0014)	0.00021	0.00082	0.000088	...	0.12	0.020	...	(0.9)
DS-1	Gold Ore	25.68	...	(3.0)	4.48	6.248	1.1	...	2.85	2.76	0.00487	0.00271	0.00095	0.00138	0.000047	0.6960	0.003259	0.0206	...	13
GTS-2a	Gold Ore Mill Tailings	23.65	...	7.56	6.96	4.01	2.021	0.617	0.348	2.412	0.00771	0.00886	0.00221	0.00179	(0.000064)	0.0124	(0.002)	...	0.0000272	...	2.011	0.0208	...	9.87
MA-1b	Gold Ore	24.5	...	4.62	6.11	4.6	4.45	1.49	1.17	2.6	0.0004	0.00170	...	2.44	...	0.1	7.9
MA-2c	Gold Ore	24.40	...	5.39	6.70	4.76	3.20	2.23	0.23	2.91	0.0064	0.0095	0.0029	0.0029	0.000051	0.0009	0.000302	...	1.78	0.0093	...	7.55
MA-3a	Gold Ore	21	...	5	6	5.5	4	1.5	1	3	0.007	0.01	0.003	0.002	0.00024	0.0008	0.000856	...	2.5	0.008	...	10
PTA-1	Platiniferous Black Sand	...	3.6	63.0	2.9	1.2	0.6	0.000305
PTC-1b	Nickel-Copper Sulphide	2.468	...	36.78	0.752	0.571	0.15	(0.17)	29.95	0.441	11.256	7.919	0.3253	0.0795	0.00531	0.0222	0.000946	0.000647	0.000199	(0.00005)	...	0.2083	0.81	13.44
SU-1b	Nickel Copper Cobalt Ore	15.23	...	25.54	4.30	2.21	(0.6)	(1.6)	14.14	1.790	1.953	1.185	0.0672	0.0058	0.00639	0.000249	0.0000791	0.0000491	(0.00002)	...	0.04	0.0235	(0.6)	(8)
UMT-1	Ultramafic Ore Tailings	0.1396	0.0743	0.0077	0.0000106	0.0000129	0.0000048	0.0000001

DS-1 also certified for Ba: **0.0221**%, Hg: **0.0082**%, Mn: **0.0437**%, P: **0.034**% and Tl: **0.0020**%. GTS-2a also certified for Ba: **0.0186**%, Mn: **0.1510**%, P: **0.0892**%, Sr: **98.2** µg/g and Th: **1.244** µg/g. SU-1b is also certified for Mn: **0.0703**% and has provisional constituent values for Bi, Se and V. UMT-1 also has provisional constituent values for Ir and Ru.

CANADA CENTRE FOR MINERAL AND ENERGY TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Ore Concentrate Certified Reference Materials (Finely divided material, CCU-1 and CZN-4 – units of 200g; CPB-3 – units of 100g)

CANMET No.	Description	SiO ₂	Al	Mg	Ca	Cu	Zn	Pb	Ag	Hg	Au	S	Fe	Sb
CCU-1f	Copper Concentrate	2.015	0.1203	0.383	0.140	23.33	4.085	0.2095	0.0157	0.001219	0.001908	34.82	29.5	0.00855
CPB-3	Lead Concentrate	2.62	0.203	0.1062	0.059	0.240	5.96	58.53	0.2790	0.00408	<i>0.0000119</i>	<i>17.03</i>	8.45	0.580
CZN-4	Zinc Concentrate	0.295 Si	0.0715	<i>0.0352</i>	<i>0.0419</i>	0.403	55.24	0.1861	0.00514	0.000454	<i>(0.000004)</i>	33.07	<i>9.086</i>	<i>(0.001)</i>

CANMET No.	As	Bi	C	Cd	Co	Cr	Mn	Mo	Ni	Se	Te	Tl	H ₂ O	LOI
CCU-1f (continued)	0.0821	<i>(0.0000649)</i>	<i>(0.06)</i>	0.01102	0.03042	<i>(0.0007)</i>	0.00829	0.00116	0.00192	0.0211	0.00499	0.000151	<i>0.96</i>	<i>19.15</i>
CPB-3 (continued)	<i>0.0391</i>	...	<i>1.037</i>	0.0652	0.00136	0.0102	<i>0.421</i>	...	0.00168	<i>(0.15)</i>	...
CZN-4 (continued)	0.0356	<i>(0.0010)</i>	<i>(0.09)</i>	0.2604	0.00935	...	<i>(0.009)</i>	0.00867	<i>0.149</i>	...

Sulphide Ore Mill Tailings and Concentrate/Tailings Certified Reference Materials (Finely divided material – RTS-3a and RTS-5 in units of 100g, TPO-1 in units of 25g)

CANMET No.	Description	Al	As	Ca	Co	Cu	Fe	Mg	Ni	Pb	Si	SiO ₂	S (Sulphate)	S (Total)	Zn
RTS-3a	Sulphide Ore Mill Tailings	5.12	0.00182	2.14	0.0143	0.2353	20.49	2.483	0.00613	0.0209	18.28	...	<i>(1.1)</i>	9.59	0.2890
RTS-5	Nickel-Copper-Gold Tailings	6.25	0.1286	3.86	0.00769	0.0647	11.9	3.59	0.1104	0.00663	19.20	...	<i>1.23</i>	1.924	0.0105
TPO-1	Iron Sulphide Conc./Tailings	<i>3.51</i>	...	<i>2.17</i>	0.021	0.118	34.85	<i>1.66</i>	0.617	25.52	...	18.03	<i>0.02</i>

CANMET No.	Ag	Au	Ba	Bi	C	Cd	CO ₂	Cr	H ₂ O	K	Mn
RTS-3a (continued)	0.00111	<i>0.0000561</i>	0.0106	0.00313	<i>(0.04)</i>	0.00092	<i>(0.04)</i>	<i>0.0176</i>	...	0.460	0.1585
RTS-5 (continued)	0.000150	0.0000408	0.0252	<i>0.000205</i>	<i>1.617</i>	0.0261	<i>(1.4)</i>	0.850	0.1092
TPO-1 (continued)	<i>0.03</i>	...	<i>0.56</i>	<i>0.08</i>

CANMET No.	Na	Pd	Pt	P	Se	Sr	S (Elemental)	S (Sulphide)	Ti	Zr	LOI
RTS-3a (continued)	0.684	<i>(0.0000004)</i>	...	<i>0.0446</i>	<i>0.00448</i>	0.00447	<i>(1.2)</i>	<i>(8)</i>	<i>0.351</i>	<i>0.0078</i>	<i>(10.6)</i>
RTS-5 (continued)	1.285	<i>(0.000014)</i>	<i>(0.00002)</i>	0.0369	<i>0.000803</i>	0.01306	<i>(0.3)</i>	...	0.3132	<i>(0.0075)</i>	<i>9.90</i>
TPO-1 (continued)	<i>0.85</i>	<i>0.02</i>	...	<i>0.03</i>	<i>0.35</i>

CANADA CENTRE FOR ENERGY AND MINERAL TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content) - Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Geochemical Soil and Till Reference Materials (Finely divided material – units of 100g)

CANMET No.	Description	Mass content	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P ₂ O ₅	S	LOI (500°C)	LOI (1000°C)
TILL-2	Till	%	<i>60.8</i>	<i>16.0</i>	<i>5.39</i>	<i>1.83</i>	<i>1.27</i>	<i>2.19</i>	<i>3.07</i>	<i>0.10</i>	<i>0.88</i>	<i>0.17</i>	<i><0.05</i>	<i>6.8</i>	<i>8.1</i>
TILL-3	Soil	%	<i>69.1</i>	<i>12.2</i>	<i>3.92</i>	<i>1.71</i>	<i>2.63</i>	<i>2.64</i>	<i>2.42</i>	<i>0.06</i>	<i>0.49</i>	<i>0.11</i>	<i><0.05</i>	<i>3.6</i>	<i>4.6</i>

CANMET No.	Mass content	As	Au	Ba	Be	Bi	Br	Ce	Co	Cr	Cs	Cu	Eu	Er	Hf	La	Li	Lu	Mn	Mo	Nb
TILL-2 (continued)	µg/g	<i>26</i>	<i>0.002</i>	<i>540</i>	<i>4.0</i>	<i><5</i>	<i>12.2</i>	<i>98</i>	<i>15</i>	<i>74</i>	<i>12</i>	<i>150</i>	<i>1.0</i>	<i>3.7</i>	<i>11</i>	<i>44</i>	<i>47</i>	<i>0.6</i>	<i>780</i>	<i>14</i>	<i>20</i>
TILL-3 (continued)	µg/g	<i>87</i>	<i>0.006</i>	<i>489</i>	<i>2.0</i>	<i><5</i>	<i>4.5</i>	<i>42</i>	<i>15</i>	<i>123</i>	<i>1.7</i>	<i>22</i>	<i><1</i>	<i>1.4</i>	<i>8</i>	<i>21</i>	<i>21</i>	<i>0.2</i>	<i>520</i>	<i>2</i>	<i>7</i>

CANMET No.	Mass content	Nd	Ni	P	Pb	Rb	Sb	Sc	Sm	Sr	Ta	Tb	Th	Ti	U	V	W	Y	Yb	Zn	Zr
TILL-2 (continued)	µg/g	<i>36</i>	<i>32</i>	<i>750</i>	<i>31</i>	<i>143</i>	<i>0.8</i>	<i>12</i>	<i>7.4</i>	<i>144</i>	<i>1.9</i>	<i>1.2</i>	<i>18.4</i>	<i>5300</i>	<i>5.7</i>	<i>77</i>	<i>5</i>	<i>40</i>	<i>3.7</i>	<i>130</i>	<i>390</i>
TILL-3 (continued)	µg/g	<i>16</i>	<i>39</i>	<i>490</i>	<i>26</i>	<i>55</i>	<i>0.9</i>	<i>10</i>	<i>3.3</i>	<i>300</i>	<i><0.5</i>	<i><0.5</i>	<i>4.6</i>	<i>2910</i>	<i>2.1</i>	<i>62</i>	<i><1</i>	<i>17</i>	<i>1.5</i>	<i>56</i>	<i>230</i>

Information is also given on the certificate of analysis re several partial extraction elements using HNO₃/HCl.

Rock and Mineral Certified Reference Materials (Finely divided material – units of 400g, except WMG-1a - 350g and WMS-1a - 200g) Nominal mass content in %

CANMET No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	Fe	TiO ₂	CaO	MgO	K ₂ O	Na ₂ O	MnO	P ₂ O ₅	Cu	Cr _(total)	Ni	S	LOI
TDB-1	Diabase Rock	<i>50.2</i>	<i>13.6</i>	<i>14.4</i>	10.4	<i>2.3</i>	<i>9.6</i>	<i>5.9</i>	<i>0.89</i>	<i>2.2</i>	<i>0.20</i>	<i>0.23</i>	0.0323	0.0251	0.0092	<i>0.03</i>	<i>0.3</i>
WGB-1	Gabbro Rock	<i>49.1</i>	<i>11.15</i>	6.71	...	<i>0.84</i>	<i>15.78</i>	9.40	0.94	<i>2.15</i>	<i>0.143</i>	<i>0.099</i>	<i>0.0106</i>	0.0291	<i>0.0076</i>	<i>0.02</i>	<i>4</i>
WMG-1a	Mineralized Gabbro	18.27 Si	4.75 Al	...	12.71	0.419 Ti	10.06 Ca	7.41 Mg	0.1021 K	0.1119 Na	<i>0.1141 Mn</i>	0.0731 P	0.7120	0.0804	0.2480	3.43	<i>4.31</i>
WMS-1a	Massive Sulphide	<i>(4.7) Si</i>	1.350 Al	...	45.4	<i>0.084 Ti</i>	3.09 Ca	<i>0.331 Mg</i>	0.0991 K	0.0329 Na	<i>0.060 Mn</i>	<i>(0.018) P</i>	1.396	<i>0.0068</i>	3.02	28.17	...
WPR-1a	Altered Peridotite	17.62 Si	2.621 Al	...	11.34	0.3527 Ti	2.528 Ca	<i>15.22 Mg</i>	0.156 K	<i>0.050 Na</i>	0.138 Mn	0.0303 P	0.299	<i>0.322</i>	0.439	1.764	<i>8.42</i>

Nominal mass content in ng/g

CANMET No.	As	Au	Pt	Pd	Rh	Ru	Ir	Os	Ba	Ce	Ag	Co	Sb	Th	V	Zn
TDB-1 (continued)	...	6.3	5.8	22.4	<i>0.7</i>	<i>0.3</i>	<i>0.15</i>	...	241000	41000	<i>(500)</i>	<i>47000</i>	<i>1000</i>	2700	<i>471000</i>	155000
WGB-1 (continued)	...	2.9	6.1	13.9	<i>0.32</i>	<i>0.3</i>	<i>0.33</i>	...	<i>851000</i>	<i>(<20000)</i>	<i>(<1000)</i>	<i>29800</i>	<i>2000</i>	<i>(<1600)</i>	<i>222000</i>	<i>31500</i>
WMG-1a (continued)	5990	<i>617</i>	899	484	<i>(15)</i>	<i>(20)</i>	<i>(27)</i>	...	216	<i>17180</i>	3030	191	<i>1550</i>	1070	158000	112
WMS-1a (continued)	30900	300	1910	1450	222	<i>145</i>	<i>322</i>	<i>(150)</i>	<i>(70000)</i>	<i>(7900)</i>	<i>3700</i>	<i>1450000</i>	<i>6920</i>	<i>(1200)</i>	<i>140000</i>	<i>130000</i>
WPR-1a (continued)	9300	<i>50</i>	452	614	<i>20</i>	...	70600	9690	1020	213000	3130	<i>640</i>	135000	160000

WPR-1a also certified for Bi, Cd, Cs, Dy, Er, Eu, Ga, Gd, Hf, Ho, La, Li, Lu, Nd, Pb, Pd, Rb, Sc, Sm, Sr, Tb, Tm, Y and Yb.

CANADA CENTRE FOR ENERGY AND MINERAL TECHNOLOGY (CANMET), Canada

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Rare Earth Elements with Zirconium and Niobium Certified Reference Materials (Finely divided material – units of 100g)

CANMET No.	Description	Al	As	Ba	Be	Ca	Ce	Co	Cr	Cs	Cu	Dy	Er	Eu	Fe	Gd	Hf
REE-1	Rare Earth Elements	3.59	0.0124	0.01001	<i>0.0590</i>	2.30	0.3960	0.000158	0.0277	0.000107	0.00797	0.0847	0.0701	0.00235	<i>4.16</i>	0.0433	0.0479
REE-2	Rare Earth Elements	0.761	...	5.02	<i>0.00331</i>	13.68	0.9610	0.000771	<i>0.00327</i>	<i>(0.000009)</i>	0.000555	0.00692	0.00140	0.00966	12.14	<i>0.0219</i>	<i>0.000095</i>
REE-3	Rare Earth Elements	4.372	...	0.00691	0.00823	1.644	0.4540	<i>0.000092</i>	0.0082	0.0001118	0.00163	0.03303	0.01872	0.002085	8.28	0.0346	0.0448

CANMET No.	Ho	K	La	La (Total)	Li	Lu	Mg (Total)	Mn (Total)	Mo	Na	Nb	Nd	Ni	P	Pb	Pr	Rb	S(Total)
REE-1 (continued)	0.0208	3.09	0.1661	...	<i>0.0205</i>	<i>0.00924</i>	<i>0.895</i>	<i>0.155</i>	0.00366	1.445	0.4050	0.1456	0.00247	0.0261	0.1137	0.0435	0.1047	<i>(0.03)</i>
REE-2 (continued)	0.000787	<i>0.0172</i>	<i>(0.46)</i>	0.5130	0.000961	<i>0.000092</i>	6.26	1.316	<i>0.0154</i>	<i>0.120</i>	<i>0.1060</i>	0.3660	<i>0.000899</i>	0.461	<i>0.00408</i>	0.1075	0.000122	1.745
REE-3 (continued)	0.00650	3.76	0.2121	...	<i>(0.0060)</i>	0.2153	0.0594	<i>0.313</i>	0.00597	<i>2.328</i>	0.1073	0.2083	0.001083	0.0201	0.0534	0.0550	0.0887	<i>(0.04)</i>

CANMET No.	Sc	Si	Si (Total)	Sm	Sn	Sr	Ta	Tb	Th	Ti	Tm	U	W	Y	Yb	Zn	Zr	L.O.I
REE-1 (continued)	<i>(0.0008)</i>	31.36	...	0.0381	0.0498	0.0129	<i>0.0231</i>	0.01062	0.0719	<i>0.384</i>	0.01060	0.0137	<i>(0.001)</i>	0.548	0.0678	<i>0.187</i>	1.91	<i>(2)</i>
REE-2 (continued)	0.00575	...	1.377	0.0410	0.00241	0.2300	0.000117	0.00203	0.0737	0.1969	0.0001383	0.000373	0.00099	0.0176	<i>0.00072</i>	<i>0.042</i>	<i>0.00322</i>	31.38
REE-3 (continued)	<i>(0.0003)</i>	29.66	...	0.0398	0.01211	0.01337	0.00607	0.00552	0.01355	0.3202	0.002580	<i>0.00299</i>	<i>(0.0001)</i>	0.1725	0.01594	0.1499	1.866	0.346

Copper Anode Certified Reference Material (finely divided material – units of 425g)

CANMET No.	Description	Ag	As	Au	Bi	Cu	Fe	Ni	Pb	Sb	Se	Sn	Te	Zn
CUAR-1	Copper Anode	0.0294	0.0145	0.00023	<i>0.0083</i>	<i>(98.6)</i>	0.0076	<i>0.4109</i>	0.0864	<i>0.0798</i>	<i>0.0026</i>	0.0113	0.0033	<i>(0.0032)</i>

Zinc-Aluminium Foundry Alloy Certified Reference Materials (50mm dia. x 12mm discs; also as finely divided material – units of 80g)

CANMET No.	Description	Al	Cu	Mg	Fe	Sn	Pb	Cd
NZA-1	Zinc-Aluminium Foundry Alloy	28.70	1.51	0.020	0.046	0.0069	0.0030	0.00098
NZA-2	Zinc-Aluminium Foundry Alloy	23.81	3.00	0.029	0.021	0.0045	0.0076	0.0047
NZA-3	Zinc-Aluminium Foundry Alloy	25.99	2.00	0.0049	0.066	0.0034	0.0045	0.0064
NZA-4	Zinc-Aluminium Foundry Alloy	26.65	2.45	0.0106	0.027	0.0087	0.0101	0.0029
NZA-5	Zinc-Aluminium Foundry Alloy	10.85	1.04	0.021	0.016	0.0017	0.0012	0.0095
NZA-6	Zinc-Aluminium Foundry Alloy	7.54	3.17	0.00037	0.0105	0.0051	0.0809	0.0147
NZA-7	Zinc-Aluminium Foundry Alloy	13.17	0.212	0.052	0.016	0.0116	0.0136	0.00020

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Highly Alloyed Steel Certified Reference Material (Finely divided material units of 100g or a 40mm dia x 20mm disc)

CTIF No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	As	Co	Cu	N	Nb	Sn	V	Al _{Sol.}	Al _{Tot.}	Ga
*ECRM 273-1	Highly Alloyed Steel	0.0336	0.378	0.785	0.0131	0.00037	14.747	0.246	4.852	0.0030	0.0391	3.047	0.0444	0.221	0.0021	0.0512	<i>0.0032</i>	<i>0.0062</i>	<i>0.0023</i>

Special Alloy Certified Reference Materials (40mm dia. x 20mm discs: ECRM 378-1 is also available in the finely divided form in units of 100g.)

CTIF No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Cu	Nb	Ti	W	Fe
*ECRM 377-1	Nickel Alloy IN 625	0.0202	0.077	0.0225	0.0036	0.0006	21.72	8.94	61.45	0.216	<i>0.0006</i>	0.0348	0.0110	3.50	0.255	...	3.77
*ECRM 377-2	Nickel Alloy IN 625	0.0202	0.077	0.0225	0.0036	0.0006	21.72	8.94	61.45	0.232	<i>0.0006</i>	0.0348	0.0104	3.50	0.264	...	3.77
*ECRM 378-1	Cobalt Alloy, Stellite grade 6	1.181	1.172	0.0579	<i>0.0023</i>	0.0055	28.22	0.0503	0.617	63.52	4.43	0.606

Cast Iron Certified Reference Materials (Finely divided material units of 100g)

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Co	Cu	N	Sn	Te	Ti	V	Zn
*ECRM 485-3	3.514	0.1488	0.0081
*ECRM 487-2	3.573	0.0899	0.0491	0.0066	0.0031	0.0249	0.0034	0.0219	0.079	0.0064	0.0151	0.0136	0.0044	0.0045	0.0064	0.0021	0.0117	0.0012
*ECRM 488-2	3.956	0.374	0.201	0.0111	0.1173	0.303	<i>0.0008</i>	0.1247	0.0256	0.0052	0.0013	<i>0.0089</i>	0.0636	0.0545	<i>0.0006</i>
*ECRM 490-1	4.813	<i>0.03</i>	10.83	0.0267	0.0040	0.0183	...	<i>0.02</i>	0.0088	0.0030	0.0035	0.0152	...
*ECRM 491-1	3.616	0.0866
*ECRM 492-1	3.258	0.0854	0.0048

* Denotes Full EURONORM Certified Reference Materials

Low Alloy Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material.

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Co	Cu	Sn	Ti	V	Others
FL 1-1	<i>2.1</i>	<i>3.2</i>	<i>0.80</i>	<i>0.118</i>	<i>0.0765</i>	<i>0.06</i>	<i>0.038</i>	<i>0.245</i>	...	<i>0.0195</i>	<i>0.305</i>	<i>0.020</i>	<i>0.015</i>	...
FL 3-1	<i>2.3</i>	<i>2.1</i>	<i>0.27</i>	<i>0.729</i>	<i>(0.013)</i>	<i>0.107</i>	<i>0.106</i>	<i>0.553</i>	<i>(0.022)</i>	<i>0.102</i>	<i>0.111</i>	<i>0.054</i>	<i>0.049</i>	<i>0.008 N</i>
FL 7-1	<i>3.1</i>	<i>2.55</i>	<i>0.1</i>	<i>1.34</i>	<i>0.048</i>	<i>0.043</i>	<i>0.335</i>	<i>0.232</i>	...	<i>0.351</i>	<i>0.0291</i>	<i>0.05</i>	<i>0.0796</i>	<i>0.0266 As, 0.004 N</i>
FO 5-4	<i>3.2</i>	<i>0.7</i>	<i>0.2</i>	<i>1.30</i>	<i>0.027</i>	<i>0.23</i>	<i>0.41</i>	<i>0.172</i>	<i>(0.019)</i>	<i>0.12</i>	<i>0.109</i>	<i>0.04</i>	<i>0.14</i>	<i>(0.003) As</i>
FO 6-4	<i>3.5</i>	<i>0.55</i>	<i>0.7</i>	<i>0.87</i>	<i>0.106</i>	<i>0.45</i>	<i>0.202</i>	<i>0.128</i>	...	<i>0.12</i>	<i>0.039</i>	<i>0.09</i>	<i>0.11</i>	...
FO 7-2	<i>2.45</i>	<i>0.675</i>	<i>0.70</i>	<i>0.84</i>	<i>0.085</i>	<i>0.455</i>	<i>0.26</i>	<i>0.15</i>	...	<i>0.125</i>	...	<i>0.065</i>	<i>0.13</i>	<i>0.0113 N</i>
FO 8-2	<i>3.6</i>	<i>1.04</i>	<i>0.37</i>	<i>0.107</i>	<i>0.019</i>	<i>0.30</i>	<i>0.0086</i>	<i>0.30</i>	...	<i>0.215</i>	<i>0.051</i>	<i>0.05</i>	<i>0.010</i>	<i>0.0095 As, 0.0067 N</i>
FO 9-2	<i>2.7</i>	<i>1.5</i>	<i>0.7</i>	<i>0.02</i>	<i>0.015</i>	<i>0.18</i>	<i>0.13</i>	<i>0.355</i>	...	<i>0.31</i>	<i>0.144</i>	<i>0.017</i>	<i>0.022</i>	...
FO 10-3	<i>3.5</i>	<i>0.65</i>	<i>1.05</i>	<i>0.196</i>	<i>0.101</i>	<i>0.379</i>	<i>0.202</i>	<i>0.117</i>	<i>0.0275</i>	<i>0.116</i>	<i>(0.002)</i>	<i>0.1</i>	<i>0.085</i>	<i>0.0012 As</i>
FO 12-1	<i>3.7</i>	<i>1.86</i>	<i>0.44</i>	<i>0.038</i>	<i>0.004</i>	<i>0.77</i>	<i>0.011</i>
FO 17-1	<i>3.0</i>	<i>2.48</i>	<i>0.47</i>	<i>0.470</i>	<i>0.168</i>	<i>(0.016)</i>	...	<i>0.021</i>	<i>0.032</i>	<i>(0.006)</i>	<i>0.024</i>	<i>0.032</i>	<i>0.018</i>	...
FO 18-2	<i>3.4</i>	<i>1.2</i>	<i>0.60</i>	<i>1.34</i>	<i>0.136</i>	<i>0.170</i>	<i>0.179</i>	<i>0.140</i>	...	<i>0.049</i>	<i>0.046</i>	<i>0.055</i>	<i>0.102</i>	<i>0.004 N</i>
FO 19-2	<i>4.04</i>	<i>1.05</i>	<i>1.05</i>	<i>0.030</i>	<i>0.057</i>	<i>0.0420</i>	...	<i>(0.075)</i>	<i>0.0392</i>	<i>0.0298</i>	<i>0.0012</i>	<i>0.029</i>	<i>0.0419</i>	<i>0.0005 Te, 0.0070 N</i>
FPA-1-3	<i>3.10</i>	<i>0.029</i>	<i>0.105</i>	<i>0.002</i>	<i>0.0009</i>	<i>0.073</i>	<i>0.0109</i>	<i>0.045</i>	<i>0.0097</i>	<i>0.062</i>	...	<i>0.0010</i>	<i>0.0010</i>	<i>0.0109 As, 0.012 N</i>
FT 1-3	<i>2.9</i>	<i>2.25</i>	<i>0.7</i>	<i>0.118</i>	<i>(0.006)</i>	<i>0.07</i>	...	<i>0.134</i>	...	<i>0.018</i>	...	<i>0.04</i>	<i>0.7</i>	...
FT 2-1	<i>3.4</i>	<i>1.4</i>	<i>0.78</i>	<i>0.045</i>	<i>0.095</i>	<i>0.03</i>	...	<i>0.07</i>	...	<i>0.01</i>	...	<i>0.10</i>	<i>0.405</i>	...
FT 3-1	<i>3.2</i>	<i>1.55</i>	<i>0.345</i>	<i>0.063</i>	<i>0.051</i>	<i>0.685</i>	...	<i>0.092</i>	...	<i>0.015</i>	...	<i>0.2</i>	<i>0.016</i>	...

CENTRE TECHNIQUE DES INDUSTRIES DE LA FONDERIE (CTIF), France

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Cu, Ni, Cr, Mo Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu
NH 1-2	3.00	1.35	0.90	0.060	0.105	0.83	1.45	1.38	1.99
NH 2-3	2.45	1.80	1.05	0.043	0.065	1.26	1.00	1.82	1.00
NH 3-2	3.45	0.85	0.175	0.36	0.024	1.76	0.73	2.53	0.031
NH 4-2	2.85	0.49	0.28	0.12	0.022	2.46	0.30	3.60	0.09
NH 5-2	2.30	0.31	0.24	0.115	0.04	2.85	0.017	4.90	0.035
NH 6-1	2.70	2.28	0.355	0.066	0.036	6.60	0.11	7.06	0.115
NH 7-1	3.43	0.95	0.63	0.035	0.022	9.02	...	5.53	0.105
NH 7-2	3.20	1.20	0.91	0.034	0.0120	8.87	...	5.53	0.108
NH 8-1	3.00	0.80	0.57	0.052	0.076	5.03	0.125	8.16	0.065
NH 9-1	3.15	1.24	0.65	0.087	0.029	11.70	0.059	4.11	0.203

Austenitic (Ni-resist) Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Ni	Cu	N	Nb	Mg
NR CU 1-1B	3.1	1.0	1.465	0.172	0.09	0.994	18.02	4.95
NR CU 2	2.52	2.07	1.07	0.115	0.049	2.05	15.9	6.50
NR CU 3	1.94	3.12	0.597	0.047	0.017	3.49	13.30	8.07	(0.008)
NR 1-2L	2.50	2.99	1.34	0.125	0.10	1.74	25.87	0.49
NR 3-2L	2.99	3.04	0.72	0.088	0.052	2.97	21.58	0.26
NR 5-2L	1.77	2.99	1.207	0.037	0.083	0.27	33.89	0.48
NR 6-2L	1.76	2.07	0.70	0.031	0.063	3.49	30.37	0.020
NR 8-2L	2.89	1.74	5.19	0.054	0.025	0.165	13.33	0.075
NR 1-2S	2.58	3.02	1.54	0.19	...	2.00	20.60	0.11
NR 2-2S	2.32	1.43	0.53	0.062	...	0.51	36.3	0.21
NR 3-2S	2.92	2.91	0.77	0.024	...	3.05	24.63	0.33
NR 4-2S	2.47	4.87	1.71	0.145	...	1.50	18.30	0.63
NR 6-2S	1.815	2.44	0.99	0.019	...	1.06	30.75	0.03
NR 8-2S	3.05	1.41	4.39	0.124	...	0.191	14.20	0.071
NR 2-1G	2.2	1.5	0.4	0.05	<0.01	0.40	36.3	0.23	...	0.25	...
NR 4-1G	2.3	5.6	1.72	0.11	...	1.40	21.30	0.64

Chromium Iron Reference Materials (43mm dia. x 5mm chill cast discs) Supplied as a pair of discs of the same material

CTIF No.	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	N
FCR 1-3	2.46	0.48	0.63	0.019	0.007	18.71	1.41	1.30	0.031	...
FCR 2-4	2.8	1.07	0.74	0.137	0.055	11.8	3.88	1.87	0.135	...
FCR 3-1	2.03	0.255	0.99	0.034	0.035	14.85	0.91	0.652	0.0490	...
FCR 4-1	2.45	1.40	2.05	0.097	0.066	24.2	2.16	0.57	1.32	...
FCR 5-1	3.43	0.30	0.55	0.052	0.0175	28.5	3.27	2.69	1.02	...
FCR 6-1	1.3	0.75	1.4	0.201	0.086	30.84	0.455	0.188	0.480	...
FCR 7-1	3.3	1.07	0.365	0.099	0.0427	33.65	2.62	0.947	0.704	...
FCR NI 1	1.27	1.63	0.71	0.41	0.06	26.20	...	16.50	0.02	...
FCR NI 2	2.0	1.51	0.60	0.185	0.024	29.07	...	13.11	...	0.1
FCR NI 3	2.74	0.67	0.46	0.036	0.011	31.65	...	11.05

DEGERFORS LABORATORIUM AB (D-LAB), Sweden

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in small italic type only approximate.

Ferro-Alloy Certified Reference Materials from Degerfors Laboratorium AB (D-LAB), Sweden (Finely divided material – units of 50g)

D-LAB No.	Description	C	Si	P	S	Cr	N	O	H
DFS 1	Ferro-chromium - Low Carbon	0.0549	<i>0.87</i>	<i>0.027</i>	<i>0.0017</i>	69.8	0.0973	<i>0.56</i>	<i>0.0024</i>
DFS 2	Ferro-chromium - High Carbon	9.03	<i>0.2</i>	<i>0.021</i>	<i>0.0174</i>	69.6	<i>0.0178</i>	<i>0.2</i>	...
DFS 3	Ferro-chromium - High Nitrogen	<i>0.068</i>	<i>0.54</i>	<i>0.023</i>	<i>0.016</i>	64.2	9.71	<i>3</i>	...

Nordisk Industrilaboratorium AB (NILAB), Sweden

CHEMICAL COMPOSITION (nominal mass content in %)

Alloy Steel Certified Reference Materials (500 HA and 501 HA available in finely divided form and all available in disc form – see table)

NILAB No.	Description	Unit sizes	C	Si	Mn	P	S	Cr	Mo	Ni
100 LA	Bearing Steel	34mm dia. x 20mm disc	1.002	0.283	0.333	0.012	0.018	1.517	0.012	0.027
500 HA	Stainless Steel	150g powder 38mm dia. x 20mm disc	0.041	0.720	1.541	0.024	0.012	16.93	2.73	11.00
501 HA	Highly Alloyed Steel	150g powder 38mm dia. x 20mm disc	0.014	0.676	0.858	0.020	0.003	19.79	6.14	17.69

Alloy Steel Certified Reference Materials (continued)

NILAB No.	Al	As	Co	Cu	N	Nb	Ti	V
100 LA (cont.)	0.005	0.004	0.007	0.019	0.0046	...	0.0007	0.004
500 HA (cont.)	0.139	0.182	0.1154	0.023	...	0.074
501 HA (cont.)	0.003	...	0.159	0.761	0.223	0.007	...	0.044

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Ferro-Alloy, Silico-Chromium, Silico-Manganese and Electrolytic Manganese Reference Materials (Finely divided material - units of 50g)

Dillinger No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	N
DL SL12-07	Ferro – Manganese	1.630	1.113	88.00	0.081	...	0.060	...	0.022	0.039	...
DL SL17-05	Ferro – Boron	0.62	1.011	0.416	0.061	...	0.925	0.023	0.097	0.085	20.23	0.025	...
DL SL20-10	Ferro – Molybdenum	0.026	0.161	0.010	0.015	0.092	0.035	78.09	0.112	0.008	...	0.020	...
DL SL23-10	Ferro – Silicon	0.11	75.94	0.139	0.021	...	0.019	...	0.006	2.041
DL SL25-10	Ferro – Vanadium	0.120	0.894	1.154	0.051	0.016	0.201	0.029	0.009	0.783	...	0.008	...
DL SL28-15	Ferro – Niobium	0.043	1.580	0.842	0.065	0.056	0.028	0.020	0.019	4.82
DL SL29-02	Fe-Si-Ti	0.284	59.25	1.64	0.010	0.005	0.059	0.126	0.043	0.613
DL SL30-01	Fe-Si-Zr	0.338	51.14	0.210	0.033	0.002	0.004	...	0.013	0.852	0.027
DL SL54-03	Silico – Chromium	0.034	40.46	0.41	0.022	...	36.93	...	0.190	0.579
DL SL77-01	Electrolytic Manganese	0.120	1.09	95.85	0.056	0.016	0.411	...	0.0068	0.0015	...	0.0012	...

Dillinger No.	Cu	Nb	Pb	Ti	V	W	Zr	Ba	Ca	Mg	Ta	Zn	Fe
DL SL01-07 (cont.)	0.012	0.122	0.015	2.64
DL SL12-07 (cont.)	0.016	0.026	0.009	8.78
DL SL17-05 (cont.)	0.072	0.025	0.006	0.127	75.71
DL SL20-10 (cont.)	0.464	20.66
DL SL23-10 (cont.)	0.011	0.093	0.042	1.019	0.029	19.42
DL SL25-10 (cont.)	0.038	0.013	...	0.071	80.85	0.025	0.010	14.25
DL SL28-15 (cont.)	0.209	60.15	0.140	0.185	0.013	...	0.105	0.856	...	28.77
DL SL29-02 (cont.)	0.022	11.21	0.154	...	0.046	...	0.220	0.234	24.80
DL SL30-01 (cont.)	0.073	36.06	...	0.157	8.87
DL SL54-03 (cont.)	0.020	0.124	0.074	20.93
DL SL77-01 (cont.)	0.007	0.0011	2.07

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Dust and Slag Reference Material (Finely divided material - units of 100g, except SX62 – units of 20g)

Dillinger No.	Description	CaO	SiO ₂	Fe	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	SO ₃	CuO	Al ₂ O ₃	MgO	NiO	Cr ₂ O ₃
DL SX62-06	Cupola Dust	0.090	0.430	...	0.572	0.061	0.191	0.305	0.220	0.020	...	0.048
DL SX66-04	Tundish Slag	1.609	24.75	...	4.62	0.098	0.084	...	0.026	...	1.884	64.65	0.165	0.255
DL SX74-03	Manganese Slag	15.95	43.23	0.088	0.818	19.84	12.34	...	0.007

Dillinger No.	SnO ₂	V ₂ O ₅	MoO ₃	TiO ₂	PbO	SnO ₂	ZnO	Cl	F	Na ₂ O	K ₂ O	CO ₂	C(tot)	H ₂ O (900°C)
DL SX62-06 (cont.)	0.014	...	0.047	91.1	...	0.071	0.085	0.086	...	2.57	1.17
DL SX66-04 (cont.)	0.141	0.516	0.089	0.35	0.471	1.02
DL SX74-03 (cont.)	0.100	0.433	1.30	0.032	...	0.062

Refractory, Magnesite and Uncover Compound Reference Materials (Finely divided material - units of 100g)

Dillinger No.	Description	CaO	SiO ₂	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	SO ₃	Al ₂ O ₃	MgO
DL SX26-12	Refractory	1.80	40.80	3.10	0.135	0.279	36.45	13.13
DL SX42-08	Magnesite	2.06	5.09	1.49	0.070	0.077	...	0.018	41.66	47.83
DL SX59-06	Uncover Compound	33.29	30.78	0.598	0.052	0.037	0.061	...	14.43	19.38

Dillinger No.	NiO	TiO ₂	Cr ₂ O ₃	V ₂ O ₅	ZrO ₂	Na ₂ O	SrO	K ₂ O	C (tot)	CO ₂	H ₂ O (900°C)
DL SX26-12 (cont.)	0.032	1.25	0.385	0.027	0.163	0.242	...	0.759	0.437	0.54	0.75
DL SX42-08 (cont.)	...	0.066	<0.080	...	0.091	0.037	0.353	0.58	0.89
DL SX59-06 (cont.)	...	0.037	0.32	0.015	0.210

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Fluorspar, Limestone and Gravel Reference Materials (Finely divided material - all units of 100g)

Dillinger No.	Description	CaO	SiO ₂	Fe	Fe ₂ O ₃	MnO	Mn ₃ O ₄	P ₂ O ₅
DL SX35-13	Limestone	55.06	0.289	...	0.082	0.017	...	0.007
DL SX36-09	Gravel	0.047	96.35	0.706	0.706	...	0.20	0.019

Dillinger No.	SO ₃	Al ₂ O ₃	MgO	TiO ₂	Na ₂ O	K ₂ O	V ₂ O ₅	Cr ₂ O ₃	Co ₃ O ₄
DL SX35-13 (cont.)	0.012	0.097	0.466	0.006	0.003	0.029
DL SX36-09 (cont.)	...	1.46	0.104	0.086	0.045	0.334	<0.006	0.029	0.005

Dillinger No.	SrO	CO ₂	H ₂ O (900°C)
DL SX35-13 (cont.)	0.019	43.80	0.099
DL SX36-09 (cont.)	...	<0.025	0.043

Cover Powder and Rutile Reference Materials (Finely divided material - DL SX57-04 - units of 20g)

Dillinger No.	Description	CaO	SiO ₂	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	Al ₂ O ₃	MgO
DL SX57-04	Cover Powder	0.302	92.49	0.090	0.067	0.273	0.071	0.198	0.362

Dillinger No.	Cr ₂ O ₃	TiO ₂	Na ₂ O	K ₂ O	V ₂ O ₅	Nb ₂ O ₅	ZrO ₂	C	CO ₂	H ₂ O (900°C)
DL SX57-04 (cont.)	0.070	0.97	3.60	0.008	1.38

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

DILLINGER LABORATORY (DL), Germany
CHEMICAL COMPOSITION (nominal mass content in %)

Iron Ore and Sinter Reference Materials (Finely divided material – units of 100g)

Dillinger No.	CaO	SiO ₂	Fe	FeO	Mn	P ₂ O ₅	S	Al ₂ O ₃	MgO	TiO ₂	Na ₂ O	K ₂ O	V ₂ O ₅	Cr ₂ O ₃	ZnO	C(tot)	CO ₂	H ₂ O (900°C)
DL SX11-14	0.421	7.47	65.55	27.20	0.029	0.028	0.019	0.271	0.565	0.060	0.078	0.061	0.002	0.006	...	0.125
DL SX11-15	0.494	5.79	63.17	...	0.074	0.101	...	2.68	0.244	0.128	0.020	0.008	0.010	0.005
DL SX11-16*	1.149	4.67	64.69	...	0.198	0.058	...	0.722	0.400	0.078	0.016	0.023	0.009	0.038	0.0010	0.016	0.026	0.059
DL SX11-18	0.052	1.56	64.72	...	0.713	0.141	0.009	1.785	0.057	0.075	0.014	0.020	0.017	...	0.005	0.085	0.033	2.51
DL SX11-23	0.034	2.67	64.80	0.133	0.049	0.123	0.011	1.619	0.037	0.047	0.006	0.008	0.005	...	0.0009	0.058
DL SX11-35	0.011	0.696	64.69	0.06	1.520	0.140	0.006	1.49	0.033	0.052	...	0.016	0.069	0.007	2.31
DL SX11-36	0.370	3.35	65.74	...	1.21	0.017	0.002	0.345	0.083	0.023	0.025	0.033	0.006	0.025	...	0.016	0.030	0.057
DL SX11-37	1.930	2.365	66.15	0.32	0.038	0.113	0.003	0.442	0.164	0.032	0.020	0.011	...	0.017	...	0.101	0.089	0.080
DL SX56-32	10.79	5.55	55.03	4.06	0.208	0.104	0.061	1.281	2.070	0.068	0.048	0.174	0.026
DL SX56-35	6.11	4.81	59.22	5.27	0.368	0.120	0.013	1.392	0.882	0.224	0.047	0.066	...	0.031	0.010	1.27

* DL SX11-16 has the following additional constituent value: NiO 0.011%.

Cement Reference Materials (Finely divided material – units of 100g)

Dillinger No.	Ca	CaO	SiO ₂	Fe ₂ O ₃	Mn ₃ O ₄	P ₂ O ₅	S	Al ₂ O ₃	MgO	TiO ₂	SrO	K ₂ O	Na ₂ O	BaO	V ₂ O ₅
DL SX02-09	48.78	...	21.95	0.204	0.025	0.043	1.19	4.63	0.717	0.095	0.051	1.01	0.078	0.028	...
DL SX02-10	33.39	46.72	30.30	1.66	0.327	0.066	1.77	9.99	4.96	0.421	0.077	0.541	0.236	0.071	0.011
DL SX02-11	40.63	...	25.04	2.98	0.172	0.137	1.48	6.86	2.79	0.319	0.083	0.524	0.156	0.041	0.014
DL SX02-12	46.48	...	21.16	3.94	0.062	0.191	1.18	4.41	0.945	0.242	0.086	0.495	0.084

The above represents a selection of samples prepared by Dillinger Laboratory in which the reference values have been obtained after a preliminary multi-element analysis by a complete reconstitution of the test sample using pure and ultrapure compounds as primary references. Sets of Dillinger samples are available to provide ranges of values for most categories of materials stated, and details can be provided on request.

The Dillinger certified values are based on the SI unit's kg and mole and are obtained by means of absolute calibration.

FLUXANA GMBH & CO. KG REFERENCE MATERIALS (FLX), GERMANY

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Cement Reference Materials (Finely divided material – unit weights as shown)

FLX No.	Unit Weight	Al ₂ O ₃	CaO	Cl	Cr ₂ O ₃	Fe ₂ O ₃	K ₂ O	MgO	Mn ₂ O ₃	Na ₂ O	P ₂ O ₅	S	SiO ₂	SO ₃	SO ₄ as SO ₃	SrO	TiO ₂	ZnO	LOI
FLX-CRM 103	50g	7.75	54.9	...	0.007	1.78	0.77	4.44	0.17	0.33	0.09	...	26.95	2.73	...	0.07	0.372	0.014	...
FLX-CRM 105	30g	4.27	65.24	0.049	0.008	2.5	1.24	1.57	0.04	0.21	0.0053	...	20.84	3.37	...	0.146	0.179	0.054	(2.61)
FLX-CRM 106	30g	5.7	66.05	0.055	0.008	1.98	0.86	0.96	0.161	0.12	0.111	...	20.29	3.01	...	0.206	0.271	0.012	(2.06)
FLX-CRM 107	30g	4.23	67.19	0.043	0.006	1.29	0.7	0.7	0.04	0.18	0.16	...	21.81	3.13	...	0.151	0.194	0.013	(6.59)
FLX-CRM 108	30g	4.66	65.15	0.042	0.007	2.97	0.74	2.15	0.219	0.09	0.169	...	20.06	3.31	...	0.083	0.186	0.036	(2.68)
FLX-CRM 109	30g	4.25	66.45	0.049	0.008	2.32	1.06	1.59	0.051	0.18	0.052	...	20.39	3.11	...	0.144	0.0203	0.042	(5.96)
FLX-CRM 110	30g	4.7	68.13	0.008	0.004	0.18	0.94	0.65	0.029	0.05	0.037	...	22.01	2.88	...	0.041	0.17	0.003	(3.46)
FLX-CRM 130	30g	11.62	56.6	...	0.021	2.88	0.682	1.84	0.062	0.277	0.067	...	14.35	10.91	(10.18)	0.052	0.563	0.018	(5.12)
FLX-CRM 131	30g	23.1	42.89	...	0.038	3.24	0.287	1.62	0.029	0.466	0.06	...	8.73	18.19	(17.85)	0.067	1.15	0.006	(2.03)
FLX-CRM 137	30g	4.99	64.77	...	(0.007)	3.07	0.769	1.64	0.266	(0.107)	0.171	...	20.78	3.17	...	0.076	0.221	0.029	(2.66)
FLX-CRM 138	30g	4.39	68.6	...	(0.005)	1.78	0.77	1.09	0.095	0.15	0.114	...	19.0	3.44	...	0.189	0.220	0.017	(9.5)

Glass Reference Materials (Discs - dimensions as shown)

FLX No.	Description	Dimensions	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	CaO	MgO	Na ₂ O	K ₂ O	SO ₃	BaO	Cr ₂ O ₃	PbO	ZnO	ZrO ₂
FLX-DGG1	Soda-lime Glass	40mm dia. x 10mm	71.72	1.23	0.137	0.191	...	6.73	4.18	14.95	0.338	0.436
FLX-Q0	Quartz Glass	40mm dia. x ~5mm	...	<0.1	0.0103	0.0103	<0.0002	<0.0002	<0.1	<0.1	<0.0003	<0.01	<0.025	<0.0002	<0.0007	<0.0003	<0.02

FLX No.	As ₂ O ₃	CdO	CeO ₂	Co ₃ O ₄	CuO	Gd ₂ O ₃	La ₂ O ₃	NiO	Sb ₂ O ₃	SeO ₂	SnO ₂	SrO	TeO ₂	Y ₂ O ₃
FLX-Q0 (continued)	<0.0016	<0.0009	<0.05	<0.0002	<0.000	<0.3	<0.0005	<0.0003	<0.0014	<0.0004	<0.0013	<0.8	<0.0018	<0.3

XRF Monitor Glass (40mm dia. x approx. ~3mm disc)

FLX No.	Description	SiO ₂	Al ₂ O ₃	TiO ₂	Fe ₂ O ₃	MnO	CaO	MgO	Na ₂ O	K ₂ O	SO ₃	P ₂ O ₅	B ₂ O ₃	SrO	Cl	F
FLX-Z1	XRF Monitor Glass	14.01	0.62	0.09	0.09	0.04	30.22	0.44	5.80	0.09	2.97	0.23	bal.	0.01	0.84	3.23

INSTITUTE OF GEOLOGICAL SCIENCES/BRITISH GEOLOGICAL SURVEY (IGS), U.K.

CHEMICAL COMPOSITION (nominal mass content in %)

Ore and Concentrate Reference Materials (Finely divided material - approximate unit weights as shown)

IGS No.	Description	Unit Weight	Ba	Cu	F	Fe	MnO ₂	Nb	Sr	Ti	W	SiO ₂	Others
27	Molybdenum-Tungsten Ore	65g	...	2.11	...	1.76	0.036	...	0.276 Mo
29	Pyrolusite	40g	0.59	0.185	93.38	2.21	...
32	Rutile	45g	0.26	...	57.19
35	Zircon	50g	0.16	1.20 Hf, 48.96 Zr
39	Fluorite	55g	0.44	...	46.85	0.014

SOCIETY OF GLASS TECHNOLOGY (SGT), U.K.

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Glass Certified Reference Materials (Broken pieces - units of 25g) (G4, G7, G10 and G11 are also available as 40mm dia. glass discs)

SGT No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	BaO	Na ₂ O	K ₂ O	PbO	As ₂ O ₃	B ₂ O ₃	TiO ₂	Cr ₂ O ₃	ZnO	ZrO ₂	Mn ₃ O ₄	F	SO ₃	LOI (550°C)
G4	Fluoride Opal Glass	69.49	3.02	0.099	4.24	<0.05	...	15.45	0.57	0.19	0.041	...	3.28	4.96	<0.05*	0.22
G7	Soda-Lime-Silica Glass	72.64	1.50	0.044*	11.03	0.14	...	13.90	0.43	0.042	0.19*	0.07
G8	Lead Oxide-Potassium Oxide-Silica Glass	56.34	0.05	0.010*	<0.02	<0.02	...	0.23	11.85	30.59	0.32*	0.36	0.02	0.21
G10	Amber Soda-Lime-Silica Container Glass	72.7	1.62	0.325	10.7	1.81	0.02	12.2	0.35	0.097	0.020	...	(0.024)	(0.038)	...	0.05	...
G11	Green Soda-Lime-Silica Container Glass	70.7	1.83	0.342	10.3	2.14	0.03	13.6	0.69	0.068	0.205	...	(0.015)	(0.034)	...	0.06	...

* Total iron as iron (III) oxide Fe₂O₃

* Total arsenic as As₂O₃

* Total sulphur as SO₃

HEALTH AND SAFETY LABORATORY (HSL), UK
CHEMICAL COMPOSITION (nominal mass content in %)

Welding Fume Reference Materials (Finely divided material – units of 1g)

HSL No.	Description	Fe	Mn	Ni	Cr	Zn
MSWF-1	Elements in Mild Steel Welding Fume	42.8	1.48	21.7
SSWF-1	Elements in Stainless Steel Welding Fume	29.8	22.9	3.7	8.4	...

Respirable α -Quartz Reference Material (Finely divided material – units of 5g)

HSL No.	Description	% Crystallinity
A9950	Respirable α -Quartz Powder	89.3

IMI WOLVERHAMPTON METAL (IMI), U.K.
CHEMICAL COMPOSITION (nominal mass content in %)

Aluminium Alloy Reference Materials (Mushroom samples, approx. 58mm dia. x 7mm thick)

IMI Ref No.	Description	Cu	Mg	Si	Fe	Mn	Ni	Zn	Pb	Sn	Ti	Cr
IMI 2WM3	BS 1490: LM2	0.41	0.19	8.33	1.19	0.35	0.21	0.70	0.10	0.10	0.11	0.09
IMI 4P1	BS 1490: LM 4	1.80	0.25	5.92	0.25	0.63	0.40	0.01	0.19	0.19	0.21	<0.005
IMI 4P4		3.69	0.045	4.55	0.84	0.30	0.11	0.46	0.05	0.055	0.05	0.15
IMI 4P5		4.25	<0.005	3.94	1.03	0.14	<0.005	0.61	<0.005	<0.005	<0.005	0.19
IMI 24WM6	BS 1490: LM 24	1.85	0.20	6.55	1.02	0.63	0.45	0.56	0.26	0.10	0.23	0.19
IMI 25WM5	BS 1490: LM 25	0.075	0.19	8.36	0.42	0.15	<0.005	0.015	0.07	<0.005	<0.005	0.10
IMI 27WM2	BS 1490: LM 27	1.52	0.12	7.79	0.35	0.57	0.30	0.63	0.14	0.045	0.16	0.12
IMI 27WM5		2.79	0.36	5.60	0.91	0.10	0.005	1.13	<0.005	0.15	0.005	<0.005

Note that all the IMI RMs have a dimple, approx 15mm diameter, in the surface and hence are unsuitable for XRF analysis.

INDUSTRIAL ANALYTICAL (PTY) LTD. (IA), SOUTH AFRICA

CHEMICAL COMPOSITION (nominal mass content) – Figures in brackets are for information only.

Concentrate/Tailing Reference Materials (Finely divided material – unit of 120g) (nominal mass content in %)

IA No.	Description	SiO ₂	Al ₂ O ₃	CaO	MgO	Pb	Cu	Zn	Fe	C	S	Mn	As	Sn	Cd	Ni	Ag
RPZ-PC	Lead Concentrate	1.26	0.22	4.06	2.30	52.13	0.66	7.05	5.03	3.45	16.76	0.39	0.059	0.012	0.015	0.00052	0.0660
RPZ-PF	Lead Feed Stock	14.32	1.66	14.12	8.48	3.85	0.29	12.85	5.16	5.77	1.57	1.35	0.023	0.018	0.026	0.00071	0.0070
RPZ-ZC	Zinc Concentrate	0.53	0.14	1.80	0.89	3.53	0.65	55.26	4.02	0.89	31.75	0.77	0.023	0.012	0.11	0.00032	0.0310

Concentrate/Tailing Reference Materials (Finely divided material – units of 120g) (nominal mass content in µg/g)

IA No.	Description	Co	Cu	Ni	Au	Pt	Pd	Rh	Ru	Ir	Ag
HGC	High Grade Sulphide Concentrate	1600	69500	61500	9.7	81.5	47.5	4.79	4.44	2.42	(14.7)
HGT	High Grade Tail	97	230	78	0.13	0.40	0.32	0.05	0.051	0.016	(0.27)
LGC	Low Grade Sulphide Concentrate	1000	29100	34900	5.39	38.5	27.0	2.89	2.74	1.44	(0.98)
LGT	Low Grade Tail	97	220	700	0.097	0.37	0.28	0.05	0.053	0.023	(0.18)
MGC-A	Medium Grade Sulphide Concentrate A	1030	31900	35700	5.56	40.4	29.1	3.28	3.02	1.55	(1.17)
MIM C2	PGM bearing Pyroxenite Concentrate	1230	33100	42800	4.90	44.5	33.4	4.01	3.76	2.18	(5.5)
MIM T2	PGM bearing Pyroxenite Tailing	70	180	840	0.13	0.358	0.384	0.048	0.055	(<0.5)	(0.15)

Nickel Ore/Concentrate/Tailing Reference Materials (Finely divided material – unit of 130g) (nominal mass content in %)

IA No.	Description	Ni	Co	Cu	Si	Fe	Ca	Mg	Al	S	Ti
TN-O 01	Tati Nickel Ore	0.40	0.014	0.31	22.52	7.07	6.41	5.48	9.32	1.94	...
TN-T 01	Tati Nickel Tailing	0.083	0.0047	0.047	0.22	0.20

Nickel Ore/Concentrate/Tailing RMs (continued) (nominal mass content in µg/g)

IA No.	Au	Pt	Pd	Rh	Ag	Sn	Se	Te	Zn	Pb	Cd	Cr	As	Mn	Bi	V
TN-O 01 (cont.)	0.04	0.15	0.65	(<0.01)	0.60	0.73	11.50	0.82	46.5	10.80	22.10	547	12.0	771	0.75	101
TN-T 01 (cont.)	490	...	860

Ferro-Alloy Slag Reference Materials (Finely divided material – units of 120g) (nominal mass content in %)

IA No.	Description	SiO ₂	Al ₂ O ₃	FeO	Fe ₂ O ₃	MnO	MgO	CaO	B ₂ O ₃	Cr ₂ O ₃
XS-FCS	Ferro-Chrome Slag	24.34	23.72	10.82	15.39	3.91	...	22.45
SAM-SMS1	Silico-Manganese Slag	43.28	8.96	...	0.178	16.81	5.16	19.47	0.26	...

INSTITUTO DE PESQUISAS TECNOLOGICAS (IPT), BRAZIL

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in italic type only approximate.

Cast Iron Certified Reference Materials (Finely divided material – units of 80g)

IPT No.	Description	C (Total)	C (Graphitic)	Si	Mn	P	S	Cr	Mo	Ni	Cu	Ti	V
49	White Iron	2.11	...	0.78	0.272	0.012	0.019	0.020	...	0.021	0.040
75A	Ni-Cr-Mo-Cu Iron	3.4	2.7	1.98	0.722	0.250	0.033	0.487	0.439	0.425	0.433	0.022	0.030

Copper Base Alloy Certified Reference Materials (Finely divided material – unit weights as shown)

IPT No.	Description	Unit Weight	Cu	Sn	Pb	Zn	Ni	P	Fe	As	Sb	Bi	Al	S	Ag	Cd	Se	Te
10B	Bronze	80g	85.2	4.61	4.74	4.73	0.33	0.003	0.211	0.019	0.114	0.068
40	Brass	100g	58.10	0.18	2.45	39.1	0.001	...	0.007	...	0.023	...	0.010	...	0.0015	0.049
64	Pure Copper	50g	99.98	<0.0005	0.00006	0.001	0.00018	...	0.00045	0.0002	0.0002	<0.0001	<0.0006	...	0.0010	...	<0.0002	<0.0001
74	Bronze	60g	80.41	2.84	6.24	9.88	0.15	0.002	0.315	0.002	0.016	0.056	...	0.013

Silicon Metal Certified Reference Materials (Finely divided material – units of 60g)

IPT No.	Fe	Ca	Al	C	S	Mn	Ti	Mg	P	Cu	Cr	Ni	V	Pb
134	0.29	0.102	0.085	0.025	0.002	0.0113	0.0097	0.0048	0.0033	0.0014	0.0011	0.0006	0.0004	0.0002
135	0.125	0.011	0.045	0.018	0.002	0.0070	0.0113	0.0012	0.0027	0.0008	0.0006	0.0005	0.0003	0.0002

Clay, Refractory, Feldspar, Glass Sand, Limestone and Bauxite Certified Reference Materials (Finely divided material – unit weights as shown)

IPT No.	Description	Unit Weight	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	ZrO ₂	SrO	CaO	MgO	MnO	Li ₂ O	Na ₂ O	K ₂ O	P ₂ O ₅	LOI
32	Plastic Clay	50g	51.8	28.5	3.46	1.49	0.17	0.39	0.16	0.80	0.13	12.6
42	Clay	50g	51.9	32.2	1.09	0.96	0.05	0.19	0.02	0.47	0.07	12.9
51	Burnt Refractory	80g	55.0	40.3	1.19	2.19	0.070	...	0.06	0.20	...	0.018	0.09	0.69	0.09	0.16
53	Potash Feldspar	80g	65.8	18.3	0.13	0.013	0.27	0.05	2.5	12.1	0.072	0.51
57	Burnt Refractory	80g	24.3	71.5	1.25	1.19	0.20	0.009	0.05	0.13	...	0.008	0.35	0.83	0.054	0.20
63	Silica Refractory	80g	96.28	0.48	0.52	0.030	0.002	...	2.21	0.18	0.008	0.0005	0.013	0.043	0.013	0.17
72	Soda Feldspar	80g	66.2	20.26	0.09	0.005	0.18	0.022	10.0	1.47	1.03	0.66
122	Dolomitic Limestone	80g	4.3	1.24	0.65	0.06	...	0.018	32.0	17.5	0.042	...	0.019	0.43	0.048	43.3
131	Bauxite	70g	0.78	54.1	11.5	1.77	0.35	0.31	0.022	0.15	30.0

JERNKONTORET / NAREMA (JK), Nordic Countries

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Alloy Steel and Special Alloy Certified Reference Materials (Finely divided material – units of 100g; also available as discs of 38mm dia. x 25mm depth)

JK No.	Description	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	N	Pb
*ECRM 196-2	Silicon Steel	0.0060	1.808	0.364	0.00369	0.00065	0.0282	0.0142	0.0401	0.2167	0.00033	0.00014	0.0138	0.0057	0.00178	...
*ECRM 197-1	Low Alloy Steel	0.219	0.275	0.792	0.0073	0.0232	0.451	0.402	0.148	0.0313	0.0083	...	0.0135	0.152	0.0114	<i>0.0003</i>
*ECRM 268-1	Tool Steel	1.134	0.373	0.293	0.0209	0.0154	4.578	3.208	0.1437	<i>(0.00005)</i>	0.0062	0.0009	0.0290	0.1232	2.030	<i>(0.00016)</i>
*ECRM 270-1	Stainless Steel	0.0742	1.517	0.540	0.0196	0.0007	20.88	0.2099	10.86	<i>0.0023</i>	<i>0.0034</i>	...	0.0685	0.1076	0.1417	...
*ECRM 274-1	Vanadium Steel	1.563	1.057	0.397	0.0148	0.0096	8.036	1.4551	0.077	<i>0.0025</i>	<i>0.0013</i>	<i>0.0005</i>	<i>0.023</i>	0.0281	0.0769	<i>0.000064</i>
*ECRM 298-2	Duplex Stainless Steel	0.0140	0.331	0.786	0.0210	0.0006	24.91	3.781	6.877	0.0148	0.0028	0.0024	0.0482	0.105	0.277	<i><0.0001</i>
*ECRM 379-1	Stainless Steel	0.0121	0.393	1.804	0.0166	0.0006	26.79	3.290	30.83	<i>0.0246</i>	<i>0.0028</i>	0.00190	0.0390	0.984	0.0550	<i>0.000038</i>

Alloy Steel and Special Alloy Certified Reference Materials (continued)

JK No.	Sn	Ti	V	W	Bi	Ca	Ce	Ga	Ir	La	Mg	Nb	Pr	Sb	Zn	Fe	O
*ECRM 196-2 (cont.)	0.00047	0.00253	0.00368	0.00071	0.00075	0.00019
*ECRM 197-1 (cont.)	0.0097	0.0005	<i>0.005</i>	<i>0.002</i>
*ECRM 268-1 (cont.)	0.0078	<i><0.0012</i>	8.478	3.707	<i>(0.00002)</i>	<i>(0.0004)</i>	...	<i>(0.0019)</i>	<i><0.0019</i>	...	0.0017	<i>(0.0010)</i>
*ECRM 270-1 (cont.)	<i>0.0035</i>	<i>0.0019</i>	0.0256	<i>0.0244</i>	0.0487	<i>0.0021</i>	<i>0.0002</i>	0.0154	<i>0.0009</i>	...	<i>0.00295</i>	<i>0.0007</i>	<i>0.00074</i>
*ECRM 274-1 (cont.)	<i>0.001</i>	<i>0.0011</i>	4.010	0.0087	<i>0.0002</i>	<i>0.0026</i>
*ECRM 298-2 (cont.)	0.0029	0.0023	0.0704	0.0094	<i>0.0040</i>	0.0006	<i>0.0006</i>
*ECRM 379-1 (cont.)	0.0021	<i>0.0014</i>	0.0663	<i>0.0091</i>	<i>0.00001</i>	0.0033	<i>0.00001</i>	<i>0.0023</i>	<i>0.00001</i>	...	<i>0.0006</i>	<i>0.0028</i>	<i>0.00002</i>	0.00057	...	<i>35.6</i>	<i>0.0027</i>

* Denotes Full EURONORM-Certified Reference Materials

Alloy Steel and Special Alloy Certified Reference Materials (Finely divided or disc material – as shown in table) (Note: discs of JK 27B are 38mm dia. x 25mm)

JK No.	Description	Unit	C	Si	Mn	P	S	Cr	Mo	Ni	Al _{tot}	Co	Cu	N	Pb	Sn	V	W	Ce
JK 3B	Unalloyed Steel	150g	0.742	0.251	0.803	0.0101	0.0071	0.0529	0.0051	0.0591	0.0036	0.0048	0.0175	0.0054	<i>0.0002</i>	0.0044	<i>0.002</i>
JK 7B	Low Alloy Steel	150g	0.342	0.267	0.697	0.0057	0.0064	1.34	0.182	1.34	0.014	...	0.021	0.0050	0.004
JK 12A	Tool Steel	150g	0.886	0.30	0.312	0.020	0.023	4.04	4.85	0.191	...	0.189	0.062	0.0259	0.0004	0.007	1.94	6.42	...
JK 20A	Tool Steel	150g	1.263	0.0094	0.0027	0.160	...	0.161	1.75	...
JK 21	Low Alloy Steel	150g	0.1741	0.36	1.46	0.0148	0.011	0.024	0.004	0.035	...	0.008	0.045	0.008	<i>0.0010</i>	0.006	0.002	<i>0.0006</i>	...
JK 25	Stainless Steel	150g	<i>1.7</i>	<i>22.3</i>	<i>0.1</i>	<i>11.3</i>	0.096
JK 27B	Austenitic Stainless Steel	150g/disc	0.0089	0.401	1.510	0.0298	0.0207	17.36	2.510	12.56	<i>0.0021</i>	0.142	0.265	0.0630	<i>0.000097</i>	0.0068	0.057	0.031	...

Alloy Steel and Special Alloy Certified Reference Materials (continued)

JK No.	Al Acid Sol.	Al Non-Acid	As	B	Nb	Sb	Ta	Ti	Zr	Ca	O	Mg	Ag	Bi	Zn	Cd
JK 3B (cont.)	<i>0.002</i>	<i>0.0007</i>	...	<i>0.0020</i>	...	<i>0.0005</i>	<i>0.018</i>	<i>0.0001</i>	<i>0.00002</i>	<i>0.0001</i>
JK 21 (cont.)	0.032	0.005	<i>0.0100</i>	...	0.0175	<i>0.0010</i>	<i>0.0010</i>	0.0008	<i>0.0010</i>	<i>0.0007</i>	<i>0.0001</i>
JK 27B (cont.)	<i>(0.006)</i>	0.00072	...	<i>(0.0014)</i>	...	<i>0.0002</i>	...	0.0022	<i>0.008</i>	<i>0.00017</i>	...

JERNKONTORET / NAREMA (JK), Nordic Countries

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

C, S, N & O in Steel Certified Reference Materials (Finely divided, rod or punched disc material – as shown in table)

JK No.	Description	Unit	C	Si	Mn	S	Cr	Ni	Al Tot.	Al Sol.	N	O
JK 31	Alloy Steel	8mm dia. x 500mm rod	<i>1.03</i>	<i>0.32</i>	<i>0.36</i>	<i>0.021</i>	<i>0.020</i>	...	0.0015
JK 32	Alloy Steel	10mm dia. x 500mm rod	<i>1.02</i>	<i>0.32</i>	<i>0.30</i>	...	<i>1.38</i>	...	<i>0.011</i>	<i>0.008</i>	...	0.0028
JK 34	Alloy Steel	8mm dia. x 500mm rod	<i>0.13</i>	<i>0.31</i>	<i>1.40</i>	<i>0.051</i>	<i>0.047</i>	...	0.0068
JK 36	Stainless Steel	150g	0.0125	0.0126	0.0337	...
JK 54	Stainless Steel	100 x 1g punched discs	0.0535	0.0007	0.0229	0.0046

Iron Powder Certified Reference Material (Finely divided material – unit weight of 35g)

JK No.	Description	O	N	C	S
JK 47A	Iron Powder	0.69	0.0062	0.370	<i>0.0090</i>

Ferro-Alloy Certified Reference Material (Finely divided material – unit weight of 50g)

JK No.	Description	C	Si	Mn	P	Cr	Ni	Al	Ca	Co	Cu	Fe	Ti	V
JK 39	Ferro-Silicon	0.105	75.9	0.165	0.018	<i>0.01</i>	<i>0.008</i>	1.45	0.24	<i>0.002</i>	0.013	21.6	0.116	<i>0.007</i>

Iron Ore Certified Reference Material (Finely divided material – ECRMs 688-1 and 689-1 in units of 100g, JK 28 in units of 150g, JK 29A and JK 42A in units of 100g)

JK No.	Description	Fe ₂ O ₃	FeO	Fe	SiO ₂	CaO	MgO	Al ₂ O ₃	TiO ₂	MnO	P ₂ O ₅	P	S
*ECRM 688-1	Iron Ore	61.38	3.383 Si	1.449 Ca	1.061 Mg	0.679 Al	0.408 Ti	0.0457 Mn	...	0.337	<i>0.047</i>
*ECRM 689-1	Iron Ore	57.05	<i>5.4 Si</i>	1.183 Ca	0.980 Mg	1.185 Al	0.3264 Ti	0.1196 Mn	...	0.0706	<i>0.058</i>
JK 29A	Magnetite	71.36	0.33	0.082	0.223	0.232	0.292	0.0632	...	0.0059	0.0059
JK 42A	Magnetite	70.66	0.800	0.199	0.382	0.278	0.385	0.0506	...	0.0247	0.0082

Iron Ore Certified Reference Materials (continued)

JK No.	Na ₂ O	K ₂ O	V ₂ O ₅	Cr	Ni	Co	Cu	Sn	Pb	Zn
*ECRM 688-1 (cont.)	0.333 Na	0.180 K	0.135 V	<i>0.002</i>	0.0136	0.0096	0.0023	<i>0.0003</i>	0.00025	0.0015
*ECRM 689-1 (cont.)	0.638 Na	0.462 K	0.1020 V	<i><0.002</i>	0.0195	0.0103	0.0068	<i><0.0004</i>	<i>(0.0005)</i>	0.0042
JK 29A (cont.)	0.015	0.0087	0.266	0.0057	0.0167	0.0106	0.0007	<i>0.0002</i>	<i><0.001</i>	0.0016
JK 42A (cont.)	0.043	0.0157	0.251	0.0010	0.0129	0.0105	0.0007	<i>0.0003</i>	<i><0.001</i>	0.0015

* Denotes Full EURONORM-Certified Reference Materials

Slag and Fluorspar Reference Materials (Finely divided material – unit weights as shown in table)

JK No.	Description	Unit	SiO ₂	Al ₂ O ₃	TiO ₂	FeO	Fe ₂ O ₃	Ca	CaO	CaF ₂	MgO	MnO	P	S	C	F	P ₂ O ₅	V ₂ O ₅	Cr ₂ O ₃	Pb
JK S10	Electro Slag Refining	100g	7.8	0.54	0.05	0.10	...	50.8	20.3	70.7	0.30	0.03	0.002	...	0.022	34.4	...	<i><0.01</i>
JK S11	AOD Slag	100g	26.8	2.85	0.95	0.2	60.0	...	4.7	0.12	...	0.30	...	7.9	<i><0.005</i>	<i><0.01</i>	0.17	...
JK D	Fluorspar	100g	<i>1.5</i>	0.04	0.20	97.07	0.035	0.004	...	47.24	<i><0.001</i>

JERNKONTORET / NAREMA (JK), Nordic Countries

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Blast Furnace Slag Certified Reference Material (Finely divided material – unit of 100g)

JK No.	Description	Fe	Si	Ca	Mg	Al	Ti	Mn	P	S	Na	K	V	Cr	Ni	Mo	Ba	Sr	Zr
*ECRM 883-1	Blast Furnace Slag	0.9820	16.67	21.32	8.86	6.55	1.3331	0.546	0.0033	1.0885	0.316	0.393	0.122	0.0130	0.00053	≤0.001	0.0436	0.0380	0.0276

Industrial Fly Ash Certified Reference Materials (Finely divided material – unit weights as shown in table)

JK No.	Description	Unit	Fe	Ca	Al	Na	K	Zn	Pb	Cd	Cr	Ni	Cu	V	As	Bi	Sb	Hg	Sn
*ECRM 882-1	Industrial Fly Ash	100g	22.20	10.11	0.375	0.697	0.960	28.49	1.324	0.0183	0.490	0.0263	0.218	0.0090	0.0054	0.0026	0.0116	0.000075	<i>0.021</i>
JK 43	Industrial Fly Ash	15g	<i>20</i>	<i>12</i>	<i>0.2</i>	<i>0.5</i>	<i>0.3</i>	4.96	0.21	0.0023	<i>8</i>	<i>2</i>	<i>0.2</i>	<i>0.02</i>	0.00039	...
JK 44	Industrial Fly Ash	25g	<i>27</i>	<i>5</i>	<i>0.2</i>	<i>1</i>	<i>1.3</i>	27.3	2.74	0.0469	<i>0.2</i>	<i>0.02</i>	<i>0.2</i>	<i>0.02</i>	0.00028	...
JK 45	Industrial Fly Ash	15g	<i>40</i>	<i>7</i>	<i>0.1</i>	<i>7</i>	<i>0.4</i>	1.53	0.11	0.0047	<i>0.3</i>	<i>0.05</i>	<i>0.01</i>	<i>0.1</i>	0.000025	...

* Denotes Full EURONORM-Certified Reference Materials

Zinc Setting-up Samples (Discs – 40mm x 40mm x 10mm) Mass content in µg/g

JK No.	Description	Ag	Al	Bi	Cd	Cr	Cu	Fe	Ga	In	Mn	Ni	Pb	Sb	Sn	Tl
SUS Zn-1	Zinc disc	2	2024	0.2	14	55	14	273	0.4	...	6	43	21	0.1	0.3	8
SUS Zn-2	Zinc disc	2	1394	56	75	63	19	314	0.4	...	7	43	77	34	61	5
SUS Zn-5	Zinc disc	2	1992	136	63	81	15	318	19	29	9	47	108	24	99	3

Ceramic (high oxygen) Setting-up Sample (Disc – 25mm dia. x 8mm)

JK No.	Description	O	Al	C _{total}	Ti	Fe	W
CE 650A	Ceramic (high oxygen)	<i>30</i>	<i>34</i>	<i>6</i>	<i>21</i>	<i>2.1</i>	<i>0.8</i>

Depth Profile Setting-up Sample (Plate – 102mm x 68mm x 0.5mm)

JK No.	Description	P	Pb	Ni	Layer thickness
JK SUS NiP-1	Steel plate with a layer of electroplated nickel (NiP alloy)	<i>5.8 ± 0.02</i>	<i>0.26 ± 0.02</i>	<i>bal.</i>	<i>8.7 ± 0.5 µm</i>

Direct Reduced Iron Reference Material (100g Powder)

JK No.	Description	Fe _{tot}	Fe _M
55	Direct Reduced Iron	<i>92.47</i>	<i>84.15</i>

Blast Furnace Pellets – Powder Certified Reference Material (100g Powder)

JK No.	Description	Fe	Fe (II)	SiO ₂	CaO	MgO	Al ₂ O ₃	TiO ₂	MnO	Na ₂ O	K ₂ O	V ₂ O ₅	Cr	Ni	Zn	Co	Cu
52	Blast Furnace Pellets - Powder	66.76	0.83	2.58	0.464	0.510	0.399	0.284	0.0485	0.0406	0.0321	0.252	0.0137	0.0172	0.0021	0.0095	0.0010

Direct Reduction Pellets – Powder Certified Reference Material (100g Powder)

JK No.	Description	Fe	SiO ₂	CaO	MgO	Al ₂ O ₃	TiO ₂	MnO	P	Na ₂ O	K ₂ O	V ₂ O ₅	Cr	Ni	Zn	Co
53	Direct Reduction Pellets - Powder	67.82	0.795	0.932	0.691	0.165	0.164	0.0609	0.0245	0.0406	0.0315	0.188	0.0039	0.0178	0.0021	0.0074

LUCIDEON (formerly CERAM Research) (LUCIDEON), UK

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in brackets are for information only.

Siliceous, Zircon Bearing and Basic Reference Materials (Finely divided material – units of 100g)

LUCIDEON No.	Description	SiO ₂	TiO ₂	Al ₂ O ₃	Fe ₂ O ₃	CaO	MgO	K ₂ O	Na ₂ O	Li ₂ O	P ₂ O ₅	Cr ₂ O ₃	Mn ₃ O ₄	B ₂ O ₃	BaO	CuO	PbO	ZnO	SrO	ZrO ₂	HfO ₂	LOI	
AN25	Alumina	<0.01	<0.01	99.39	0.03	0.03	<0.01	0.01	0.53	...	<0.01(0.34)
AN26	Alumina	0.12	<0.01	99.76	0.03	0.03	<0.01	<0.01	0.02(0.08)
AN28	Lead Bisilicate Frit	32.76	<0.01	2.46	0.018	0.05	<0.01	0.05	0.05	64.33	0.15
AN35	Magnesite	0.49	0.01	0.44	1.34	0.83	96.4	<0.01	<0.05	...	0.011	0.046	0.11	0.10
AN36	Magnesite	0.48	0.01	0.42	4.66	0.94	93.30	<0.01	<0.05	...	0.008	0.004	0.11	0.09
AN37	Magnesite	1.39	0.03	1.06	1.80	1.46	94.00	<0.01	<0.05	...	0.02	0.005	0.12	0.09
AN46	Zircon Batt	45.46	0.48	30.52	0.85	0.20	5.34	1.03	0.15	0.02	15.41	0.32	...	0.08
AN100	Chrome Ore	11.1	0.21	24.7	12.88	1.16	22.38	0.01	0.04	26.60	0.13	0.02	...	0.04(5.03)
2CAS12	Sillimanite	33.9	1.31	63.8	0.31	0.25	0.12	0.13	0.15	0.13
2CAS14	Steatite	62.7	0.005	0.149	0.314	0.249	31.28	0.002	0.008	5.10
2CAS15	Zircon	33.9	0.20	0.38	0.07	0.28	0.07	0.01	0.02	63.6	1.28	...	0.23

Please note that LUCIDEON (formerly CERAM Research) also provides a series of RMs for physical properties of ceramic materials. These include two thermal expansion RMs, one of alumina and the other of cordierite. Further details of how these RMs are supplied, as special cut bars or pieces, will gladly be provided on request.

LUCIDEON (formerly CERAM Research) also supplies a Dental Frit Particle Size Distribution CRM, with D50% 3.2 µm, Median diameter 3.2 µm, with 90% between 0.6 and 10.0 µm. This is available in units of 75g.

Please ask us for further details of these Alumina and Cordierite Thermal Expansion CRMs and Dental Frit Particle Size Distribution CRM.

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Electrolytic Iron and Low Alloy Steel Certified Reference Materials

(SRMs 361 and 363 finely divided material, units of 150g; SRMs 1264a and 1265a 31mm dia x 19mm discs and 1762b-1765 31-34mm dia. x 19mm discs)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al (Total)	As	B	Co	Cu
SRM 361	AISI 4340	2016	0.383	0.222	0.66	0.014	0.0143	0.694	0.19	2.00	0.021	0.017	0.000478	0.032	0.042
SRM 363	Cr-V (Mod)	2012	0.62	0.74	1.50	0.029	0.0068	1.31	0.028	0.30	0.24	0.010	0.00131	0.048	0.10
SRM 1264a	High Carbon (Mod)	2019	0.87	0.067	0.258	0.010	0.025	0.066	0.49	0.142	<i>0.008</i>	0.052	<i>0.011</i>	0.15	0.250
SRM 1265a	Electrolytic Iron	2019	0.0067	0.0080	0.0057	0.0011	0.0055	0.0072	0.0050	0.041	<i>0.0007</i>	<i>0.0002</i>	0.00013	0.0070	0.0058
SRM 1762b	Low Alloy Steel	2021	0.3582	0.3430	1.997	0.0374	0.0318	0.932	0.348	1.170	0.0697	0.0173	0.00430	0.0612	0.1201
SRM 1763b	Low Alloy Steel	2019	0.201	0.6275	1.605	0.01233	0.0229	0.5039	0.491	0.5075	0.0422	0.0539	0.00535	0.09248	0.4170
SRM 1764a	Low Alloy Steel	2009	0.592	0.0595	1.193	0.0210	0.0118	1.468	0.2007	0.2006	0.0098	0.0100	<i>0.0010</i>	<i>0.012</i>	0.5178
SRM 1765	Low Alloy Steel	1993	0.006	<i>(0.004)</i>	0.144	0.0052	0.0038	0.051	0.005	0.154	<i>(0.006)</i>	0.0010	0.0009	0.0012	0.0013

Electrolytic Iron and Low Alloy Steel CRMs (continued)

NIST No.	N	Nb	Pb	Sn	Ta	Ti	V	W	Zr	Ag	Bi	Ca	Ce
SRM 361	<i>0.0037</i>	0.022	0.000025	0.010	0.020	0.020	0.011	0.017	0.009	0.0004	<i>0.0004</i>	0.00010	0.0040
SRM 363	<i>0.0041</i>	0.049	0.00186	0.104	<i>0.053</i>	0.050	0.31	0.046	0.049	0.0037	<i>0.0008</i>	0.00022	0.0030
SRM 1264a	<i>0.0032</i>	0.157	0.024	<i>0.008</i>	0.11	0.24	0.106	0.102	0.069	<i>0.00002</i>	<i>0.0009</i>	0.00004	0.00022
SRM 1265a	<i>0.0011</i>	...	0.000015	<i>0.0002</i>	<i><0.0005</i>	<i>0.0001</i>	0.0006	<i>0.00004</i>	<i><0.00001</i>	<i>0.000002</i>	<i><0.00001</i>	<i><0.00001</i>	<i><0.000005</i>
SRM 1762b	...	0.0739	...	0.0479	0.0209	0.0967	0.1999	...	0.0298
SRM 1763b	...	0.0998	...	0.01098	0.0119	0.313	0.3075	0.00216	0.0445
SRM 1764a	<i>0.0023</i>	0.0416	...	<i>0.024</i>	0.0297	0.0286	0.1063	<i>(0.0016)</i>	<i>0.0012</i>
SRM 1765	0.0010	0.0004	0.0003	0.002	<i>(0.004)</i>	0.0055	0.0040	...	<i>(0.0002)</i>	0.0002	<i>(<0.0001)</i>

Electrolytic Iron and Low Alloy Steel CRMs (continued)

NIST No.	Fe	Au	Ge	H	Hf	La	Mg	Nd	O	Pr	Sb	Te	Zn
SRM 361	<i>95.6</i>	<i><0.00005</i>	<i>0.006</i>	<i><0.0005</i>	<i>0.0002</i>	<i>0.001</i>	0.00026	0.00029	<i>0.0009</i>	<i>0.0003</i>	0.0042	<i>0.0006</i>	<i>0.0001</i>
SRM 363	<i>94.4</i>	0.0005	<i>0.010</i>	<i><0.0005</i>	<i>0.0005</i>	<i>0.002</i>	0.00062	0.0012	<i>0.00066</i>	<i>0.0004</i>	0.002	<i>0.0009</i>	<i>0.0004</i>
SRM 1264a	<i>96.7</i>	<i>0.0001</i>	<i>0.003</i>	<i><0.0005</i>	<i>0.0013</i>	0.00007	0.00015	0.00007	<i>0.0010</i>	<i>0.00003</i>	0.034	0.00018	<i>0.001</i>
SRM 1265a	<i>99.9</i>	<i><0.000002</i>	<i>0.0014</i>	<i>0.0001</i>	<i><0.00002</i>	<i><0.000005</i>	<i><0.00002</i>	<i><0.000005</i>	<i>0.0063</i>	<i><0.000005</i>	<i><0.00001</i>	<i><0.00001</i>	<i><0.0001</i>
SRM 1763b	<i>(95.0)</i>	<i>0.0110</i>
SRM 1764a	<i>(95.1)</i>

Information on NIST samples not included in this list will be provided on request.

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

High Temperature Alloy and Specialty Steel Certified Reference Materials (Approx. 32-35mm dia x 19mm discs except SRM 126c and SRM 867 which are finely divided material, units of 150g and 100g respectively)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	Cu	N	Nb
SRM 1158 (SRM 126c)	High Nickel Steel (36% Ni)	2017	0.02540	0.1936	0.4684	<i>0.00350</i>	<i>0.0050</i>	<i>0.0625</i>	<i>0.0110</i>	36.054	<i>0.0396</i>
SRM 1230	High Temperature Alloy A286	2016	0.0428	0.411	0.652	0.0239	0.00095	14.65	1.15	24.08	0.249	<i>(<0.005)</i>	0.137	<i>(0.003)</i>	<i>0.067</i>
SRM 1247 (SRM 867)	Ni-Fe-Cr Alloy UNS N08825	2015	0.0212	0.3234	0.3806	0.0203	<i>0.0017</i>	23.375	2.723	43.47	0.0630	0.00257	1.767	<i>0.0170</i>	0.458
SRM C2400	Fe-Cr-Ni Alloy UNS J92180	2016	0.036	0.61	0.71	0.013	0.003	17.06	0.23	4.07	<i>(<0.01)</i>	...	2.63	...	0.15

High Temperature Alloy and Specialty Steel CRMs (continued)

NIST No.	Pb	Sn	Ta	Ti	Tl	V	W	Zr	Ag	B	Bi	Co	Fe	Ga	O
SRM 1158 (SRM 126c)	<i>(0.001)</i>	<i>0.0080</i>
SRM 1230	<i>(<0.0003)</i>	<i>(<0.033)</i>	<i>(<0.001)</i>	2.18	...	0.229	<i>0.0695</i>	<i>(<0.018)</i>	<i>(0.000025)</i>	0.00519	<i>(<0.0001)</i>	0.151	55.6
SRM 1247 (SRM 867)	0.0000340	<i>(0.0030)</i>	<i>(<0.0010)</i>	0.755	0.000000223	0.0478	<i>0.0056</i>	...	<i>0.000025</i>	0.00198	<i>(<0.00005)</i>	0.092	26.564	<i>0.0112</i>	<i>0.0050</i>
SRM C2400	<i>(<0.01)</i>	...	0.092	<i>(0.1)</i>	<i>(<0.01)</i>	...	<i>(0.0004)</i>	...	0.10

Tool Steel Certified Reference Materials (SRM 1772 approx. 34mm dia x 19mm discs, SRMs 50c, 132b and 134a are all finely divided materials, units of 150g)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	As	Cu	N	V	W	Pb	Sn	B	Ca	Co
SRM 50c	W-Cr-V Steel	2011	<i>0.7193</i>	0.3102	0.3417	0.0222	0.006367	4.128	0.0821	0.0686	0.0225	0.0792	0.0117	1.158	18.445	...	0.0183	<i>(0.035)</i>
SRM 132b	Tool Steel (AISI M2)	1995	0.864	0.185	0.341	0.012	0.004	4.38	4.9	0.23	...	0.088	...	1.83	6.28	0.029
SRM 134a	Mo-W-Cr-V Steel	1957	0.808	0.323	0.218	0.018	0.007	3.67	8.35	0.088	...	0.101	...	1.25	2.00
SRM 1772	Tool Steel (S-7)	1995	0.477	0.264	0.61	0.008	0.0031	3.10	1.39	0.105	...	0.083	...	0.236	<i>0.002</i>	<i><0.001</i>	<i>0.008</i>	<i><0.001</i>	<i>0.001</i>	<i>0.007</i>

White Cast and Ductile Iron Certified Reference Materials (Approx. 32mm dia x 19mm discs except SRM 892 which is finely divided material, units of 150g)

NIST No.	Description	Cert. Date	C	Si	Mn	P	S	Cr	Mo	Ni	Cu	Ti	V
SRM 892	White Cast Iron (Ni-Hard Type IV)	1982	3.33	1.83	0.76	0.054	0.015	10.18	0.20	5.53	0.270	<i>(0.02)</i>	0.041
SRM C1145a	White Cast Iron	1988	2.92	0.271	0.187	0.215	0.191	0.63	0.48	0.62	0.46	0.012	0.112
SRM C1290	White Cast Iron (HC-250+V)	1985	3.04	0.971	0.66	0.030	0.013	30.5	<i>(0.041)</i>	0.917	0.065	...	0.442
SRM C1291	White Cast Iron (Ni-Hard Type I)	1985	2.67	1.34	1.14	0.028	0.032	2.78	0.32	4.34	0.26	...	0.031
SRM C1292	White Cast Iron (Ni-Hard Type IV)	1985	3.47	0.59	0.55	0.049	0.016	11.4	0.25	5.04	0.36	...	0.041
SRM C2424	Ductile Iron	1985	2.68	3.37	0.268	0.041	0.024	0.13	0.019	0.061	...	0.050	0.083

White Cast and Ductile Iron CRMs (continued)

NIST No.	Mg	Pb	Sb	Sn	Zr	Al	As	B	Bi	Ce	Co	La	Fe
SRM 892	<i>(0.0012)</i>	<i>(0.02)</i>	<i>(<0.001)</i>	<i>(0.009)</i>	<i>(0.006)</i>	<i>(0.0020)</i>	0.31	...	<i>(77.4)</i>
SRM C1145a	...	0.0012	<i>(0.04)</i>	<i>(0.10)</i>	<i>(0.002)</i>	<i>(0.04)</i>	<i>(0.03)</i>	<i>(0.02)</i>	<i>(<0.01)</i>	...	0.058
SRM C2424	0.006	<i>(<0.01)</i>	...	<i>(0.002)</i>	...	0.0046	<i>(0.05)</i>	0.0011	...

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified, figures in italic type only approximate and figures in brackets are for information only.

Ore and Concentrate Certified Reference Materials (Finely divided material – unit weights as shown in table)

NIST No.	Description	Cert. Date	Unit Weight	Fe ₂ O ₃	SiO ₂	Al ₂ O ₃	TiO ₂	CaO	MgO	MnO	P ₂ O ₅	SO ₃	K ₂ O
SRM 25d	Manganese Ore	2010	60g	<i>3.91</i>	2.54	<i>5.33</i>	<i>0.136</i>	<i>(0.052)</i>	...	51.78 Mn	0.251	...	<i>0.928</i>
SRM 69b	Bauxite, Arkansas	1991	60g	7.14	13.43	48.8	1.90	0.13	0.085	0.110	0.118	0.63	0.068
SRM 277	Tungsten Concentrate	2013	100g	<i>7.47 Fe</i>	<i>0.842 Si</i>	...	<i>2.20 Ti</i>	<i>0.38 Ca</i>	...	<i>10.2 Mn</i>	<i>0.034 P</i>	<i>0.267 S</i>	...
SRM 423	Molybdenum Oxide Conc.	2019	50g	<i>1.708 Fe</i>
SRM 600	Bauxite, Australian	1991	90g	17.0	20.3	40.0	1.31	0.22	0.05	0.013	0.039	0.19	0.23
SRM 670	Rutile Ore	1993	90g	0.86	0.51	...	96.16	<i>(0.10) Ca</i>
SRM 690	Iron Ore, Canada	2021	100g	66.87 Fe	3.7	0.175	0.0217	0.2004	0.1778	0.2306	0.0098 P	...	0.00303
SRM 691	Iron Oxide, Reduced	2021	100g	90.55 Fe	3.66	1.215	0.275	0.640	0.517	0.0428	0.0052 P	...	0.0656 K
SRM 692	Iron Ore, Labrador	2021	100g	59.61 Fe	10.177	1.428	0.0449	0.0224	0.0361	0.4580	0.0387 P	...	0.0399
SRM 693	Iron Ore, Nimba	2021	100g	65.08 Fe	3.860	1.043	0.0345	0.0158	0.0143	0.0900	0.0563 P	...	0.00283
SRM 694	Phosphate Rock (Western)	1993	90g	0.79	11.2	1.8	<i>(0.11)</i>	43.6	0.33	0.0116	30.2	...	0.51
SRM 696	Bauxite, Surinam	1991	60g	8.70	3.79	54.5	2.64	0.018	0.012	0.004	0.050	0.21	0.009
SRM 697	Bauxite, Dominican	1991	60g	20.0	6.81	45.8	2.52	0.71	0.18	0.41	0.97	0.0769	0.062
SRM 698	Bauxite, Jamaican	1991	60g	19.6	0.69	48.2	2.38	0.62	0.058	0.38	0.37	0.22	0.010
SRM 1835	Borate Ore	1987	60g	1.141	18.408	3.47	0.133	21.622	3.411	0.0333	...	1.477	1.261
SRM 2430	Scheelite Ore	2016	100g	<i>1.13 Fe</i>	1.74 Si	<i>(0.4) Al</i>	...	19.44	<i>(0.5) Mg</i>	0.1178 Mn	<i>(0.02) P</i>	<i>0.25 S</i>	0.179 K

Ore and Concentrate CRMs (continued)

NIST No.	Na ₂ O	Cr ₂ O ₃	V ₂ O ₅	WO ₃	ZnO	ZrO ₂	As	Bi	Cu	Cr	F	Mo	Ni	Pb	Others	LOI
SRM 25d (continued)	<i>(1) H₂O</i>	...
SRM 69b (continued)	<i>0.025</i>	0.011	0.028	...	0.0035	0.29	25.72
SRM 277 (continued)	67.50	...	<i>(<0.8) Zr</i>	...	<i>(<0.01)</i>	<i>(0.014)</i>	<i>0.060</i>	...	<i>0.068</i>	<i>(22.0) O₂</i>	...
SRM 423 (continued)	<i>(0.006)</i>	0.0640	58.61	...	<i>0.0433</i>	7.69 Acid-Insoluble Residue	...
SRM 600 (continued)	0.022	0.024	0.060	...	0.003	0.060
SRM 670 (continued)	...	0.23	0.66	0.84
SRM 690 (continued)	0.00274
SRM 691 (continued)	0.1775	0.0309	0.0256	0.031 Co	...
SRM 692 (continued)	0.0077
SRM 693 (continued)	0.0023	<i>0.0012</i>	<i>0.0048</i>	<i>0.0009</i>	...	<i>0.0043 V, 0.0009 Zr</i>	...
SRM 694 (continued)	0.86	<i>(0.10)</i>	0.31	...	<i>(0.19)</i>	3.2	0.0141 U	...
SRM 696 (continued)	<i>0.007</i>	0.047	0.072	...	0.0014	0.14	29.9
SRM 697 (continued)	<i>0.036</i>	0.100	0.063	...	0.037	0.065	<i>0.0013 Co</i>	22.1
SRM 698 (continued)	<i>0.015</i>	0.080	0.064	...	0.029	0.061	27.3
SRM 1835 (continued)	3.484	0.348
SRM 2430 (continued)	<i>0.018 Na</i>	70.30	<i>0.080</i>	<i>0.0086</i>	...	<i>(1.3)</i>	<i>0.22</i>	<i>0.0022 As</i>	...

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in italic type only approximate.

Rock, Mineral and Refractory Certified Reference Materials (Finely divided material – unit weights as shown in table)

NIST No.	Description	Cert. Date	Unit Weight	SiO ₂	Al ₂ O ₃	TiO ₂	FeO	Fe ₂ O ₃	Cr ₂ O ₃	MnO	CaO	MgO	BaO	Na ₂ O	K ₂ O	Li ₂ O	P ₂ O ₅	SrO	ZrO ₂	LOI
SRM 1d	Limestone, Argillaceous	2005	70g	4.080	0.526	0.07	...	0.3191	<i>0.0012</i>	...	52.85	0.301	<i>0.0033</i>	0.0109	0.1358	...	0.0413	0.0303	...	39.9
SRM 76a	Burnt Refractory (Al ₂ O ₃ -40%)	1992	75g	54.9	38.7	2.03	...	1.60	0.22	0.52	...	0.07	1.33	0.042	0.120	0.037	...	<i>0.34</i>
SRM 77a	Burnt Refractory (Al ₂ O ₃ -60%)	1992	75g	35.0	60.2	2.66	...	1.00	0.05	0.38	...	0.037	0.090	0.025	0.092	0.009	...	<i>0.22</i>
SRM 78a	Burnt Refractory (Al ₂ O ₃ -70%)	1992	75g	19.4	71.7	3.22	...	1.2	0.11	0.70	...	0.078	1.22	0.12	1.3	0.25	...	<i>0.42</i>
SRM 81a	Glass Sand	1978	75g	...	0.66	0.12	...	0.082	0.0046	0.034	...
SRM 165a	Glass Sand (low iron)	1992	75g	...	0.059	0.011	...	0.012	0.00011	0.006	...
SRM 198	Silica Brick	1960	45g	...	0.16	0.02	...	0.66	...	0.008	2.71	0.07	...	0.012	0.017	0.001	0.022	...	<0.01	0.21
SRM 199	Silica Brick	1991	45g	...	0.48	0.06	...	0.74	...	0.007	2.41	0.13	...	0.015	0.094	0.002	0.015	...	0.01	0.17
SRM 278	Obsidian Rock	1992	35g	73.05	14.15	0.245	...	2.04	...	0.052	0.983	4.84	4.16	...	0.036
SRM 688	Basalt Rock	1981	60g	48.4	17.36	1.17	7.64	10.35	...	0.167	2.15	0.187	...	0.134
SRM 1413	Glass Sand (high alumina)	1985	75g	82.77	9.90	0.11	...	0.24	ZnO	Mn₂O₃	0.74	0.06	0.12	1.75	3.94

Cement Certified Reference Materials (Finely divided material – units of 4 x 5g sealed vials, except SRM 634a units of 100g, SRM 1884b units of 5 x 4.5g sealed vials, SRM 1885b, 1886b and 1889b units of 5 x 5g vials and SRM 1887b units of 5 x 4g vials)

NIST No.	Cert. Date	CaO	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	MgO	SO ₃	Na ₂ O	K ₂ O	TiO ₂	SrO	Mn ₂ O ₃	P ₂ O ₅	Cl	F	ZnO	Cr ₂ O ₃	LOI
SRM 634a	2015	65.07	20.493	5.015	3.362	1.0057	2.780	<i>0.0842</i>	0.3572	0.2463	<i>0.0735</i>	<i>0.0229</i>	0.1767	<i>0.0222</i>	<i>0.0114</i>	<i>1.683</i>
SRM 1882a	2014	39.29	4.01	39.14	14.67	0.51	...	0.021	0.051	1.786	<i>0.024</i>	<i>0.060</i>	<i>0.070</i>	<i>0.004</i>	<i>0.113</i>	<i>0.20</i>
SRM 1883a	2019	29.52	0.24	70.04	0.078	0.19	...	0.30	0.014	<i>0.020</i>	<i>0.019</i>	<i>0.003</i>	<i>0.003</i>	<i>0.006</i>	<i>0.59</i>
SRM 1884b	2009	61.31	19.30	4.851	2.937	4.74	4.034	0.278	0.957	0.2651	0.0258	0.0750	0.0965	<i>0.0065</i>	<i>0.0394</i>	<i>0.0042</i>	0.00791	<i>0.597</i>
SRM 1885b	2013	61.87	20.05	4.70	3.044	3.86	2.832	0.293	0.497	0.2361	0.0795	0.1282	0.0737	<i>0.0021</i>	<i>0.0524</i>	0.0354	0.02709	<i>2.310</i>
SRM 1886b	2016	67.05	22.08	3.903	0.297	1.526	2.757	0.01682	0.0164	0.2054	0.0886	0.02639	0.0413	0.00399	<i>0.0118</i>	<i>0.00058</i>	0.00404	<i>3.344</i>
SRM 1887b	2013	61.15	19.59	4.911	2.471	3.624	4.599	0.288	0.961	0.2034	0.2625	0.0957	0.1540	0.01001	<i>0.101</i>	0.01560	0.01551	<i>2.121</i>
SRM 1888b	2010	63.13	20.42	4.277	3.062	3.562	2.634	0.1364	0.658	0.2316	0.1009	0.0652	0.07307	0.0143	<i>0.048</i>	<i>0.01253</i>	<i>0.01021</i>	<i>2.039</i>
SRM 1889b	2019	60.11	18.39	5.79	2.891	2.82	4.3721	0.365	1.115	0.260	0.284	0.0840	0.297	0.0101	<i>0.10</i>	0.0770	0.0083	<i>3.117</i>

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Biological Certified Reference Materials (Finely divided material – unit weights as shown in table) nominal mass content in %

NIST No.	Description	Cert. Date	Unit Weight	Ca	Cl	Mg	N	P	K	Na	S
SRM 1515	Apple Leaves	2019	50g	1.525	0.0582	0.271	2.299	0.1593	1.608	0.00244	<i>(0.18)</i>
SRM 1547	Peach Leaves	2019	50g	1.559	0.0361	0.432	2.965	0.1371	2.433	0.00238	<i>(0.20)</i>
SRM 1566b	Oyster Tissue	2019	25g	0.0838	0.514	0.1085	<i>7.6</i>	...	0.652	0.3297	0.687
SRM 1570a	Spinach Leaves	2014	60g	1.526	...	<i>(0.9)</i>	<i>6.06</i>	0.5187	2.900	1.821	<i>(0.5)</i>
SRM 1573a	Tomato Leaves	2018	50g	5.045	<i>0.66</i>	<i>(1.2)</i>	3.02	0.2161	2.676	0.01361	<i>(0.96)</i>
SRM 1575a	Pine Needles	2017	50g	0.25	0.0421	<i>0.106</i>	...	0.107	0.417	<i>0.0063</i>	...

Biological CRMs (continued) nominal mass content in µg/g

NIST No.	Al	As	B	Ba	Cr	Cu	Fe	Mn	Rb	Sr	Zn
SRM 1515 (continued)	284.5	...	27.6	48.8	<i>(0.3)</i>	5.69	82.7	54.1	10.2	25.1	12.45
SRM 1547 (continued)	248.9	0.062	28.73	123.7	<i>(1)</i>	3.75	219.8	97.8	19.65	53.0	17.97
SRM 1566b (continued)	197.2	7.65	<i>4.5</i>	<i>8.6</i>	...	71.6	205.8	18.5	3.26	<i>6.8</i>	1424
SRM 1570a (continued)	310	0.068	37.7	12.22	...	76.0	<i>12.7</i>	55.54	82.3
SRM 1573a (continued)	5984	0.1126	33.13	<i>(63)</i>	1.988	4.70	367.2	246.3	14.83	<i>(85)</i>	30.94
SRM 1575a (continued)	580	<i>0.039</i>	<i>9.6</i>	6.0	<i><0.5</i>	2.8	46	<i>488</i>	16.5	...	38

Biological CRMs (continued) nominal mass content in ng/g

NIST No.	Cd	Co	I	Pb	Hg	Mo	Ni	Se	Ag	Th	U	V
SRM 1515 (continued)	13.2	<i>(90)</i>	<i>(300)</i>	470	43.2	95	936	<i>(30)</i>	<i>(6)</i>	254
SRM 1547 (continued)	26.1	<i>(70)</i>	<i>(300)</i>	869	31.7	60.3	689	120	...	<i>(50)</i>	<i>(15)</i>	367
SRM 1566b (continued)	2480	371	...	308	37.1	...	1040	2060	666	36.7	<i>255.0</i>	577
SRM 1570a (continued)	2876	393	...	<i>(200)</i>	29.7	...	2142	115.2	...	48.0	<i>155</i>	568
SRM 1573a (continued)	1517	577.3	<i>(850)</i>	...	34.1	<i>(460)</i>	1582	54.3	...	<i>(120)</i>	<i>(35)</i>	835
SRM 1575a (continued)	233	<i>61</i>	...	<i>167</i>	39.9	...	<i>1470</i>	<i>99</i>

NATIONAL INSTITUTE OF STANDARDS AND TECHNOLOGY (NIST), USA

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Environmental Certified Reference Materials (Finely divided materials – unit weights as shown in table) nominal mass content in %

NIST No.	Description	Cert. Date	Unit Weight	Al	Ca	Cl	C	Fe	H	K	Mg	Na	P	Pb	S	Si	Ti	Ash content	Calorific Value (Btu/lb)
SRM 1635a	Trace Elements in Coal (Subbituminous)	2017	50g	<i>0.5437</i>	<i>1.087</i>	...	<i>(77.90)</i>	0.2472	<i>3.92</i>	...	<i>0.2303</i>	0.1031	<i>0.01874</i>	0.000285	0.2909	...	<i>0.0524</i>	<i>(6.29)</i>	<i>(11664)</i>
SRM 1646a	Estuarine Sediment	2004	70g	2.297	0.519	2.008	...	0.864	0.388	0.741	0.027	0.00117	0.352	40.00	0.456
SRM 1648a	Urban Particulate	2020	2g	3.43	5.84	0.4543	<i>(12.7)</i>	3.92	...	1.056	0.813	0.4240	...	0.655	5.51	<i>12.8</i>	0.4021
SRM 2689	Fly Ash, Low Lime	2015	Set (3)	12.94	2.18	9.32	...	2.20	0.61	0.25	0.10	<i>(0.0052)</i>	...	24.06	0.75	<i>(12)</i>	<i>(12000)</i>
SRM 2690	Fly Ash, Medium Lime	2015	Set (3)	12.35	5.71	3.57	...	1.04	1.53	0.24	0.52	<i>(0.0039)</i>	0.15	25.85	0.52	<i>(5.3)</i>	<i>(9700)</i>
SRM 2691	Fly Ash, High Lime	2015	Set (3)	9.81	18.45	4.42	...	0.34	3.12	1.09	0.51	<i>(0.0029)</i>	0.83	16.83	0.90	<i>(4.8)</i>	<i>(8800)</i>

SRM 1648a also certified for PAH and PCB Congeners;

Environmental CRMs (continued) nominal mass content in µg/g

NIST No.	Ag	As	Ba	Br	Cd	Ce	Co	Cr	Cu	Hg	Mn	Ni	Rb	Sb	Se	Sr	Th	Tl	U	V	Zn
SRM 1635a (continued)	...	0.860	3578	...	<i>0.282</i>	...	2.004	3.56	11.42	0.0836	6.69	5.37	1.226	0.251	0.662	160	1.299	...	0.4792	13.34	<i>7.3</i>
SRM 1646a (continued)	<i><0.3</i>	6.23	<i>210</i>	...	0.148	<i>(64)</i>	<i>5</i>	40.9	10.01	<i>0.04</i>	234.5	22.5	<i>38</i>	<i>0.3</i>	0.193	<i>68</i>	<i>5.8</i>	...	<i>2.0</i>	44.84	48.9
SRM 1648a (continued)	<i>6.0</i>	115.5	...	502	73.7	54.6	17.93	402	610	1.323	790	81.1	51.0	45.4	<i>28.4</i>	215	127	4800
SRM 2689 (continued)	...	<i>(200)</i>	<i>(800)</i>	<i>(48)</i>	<i>(170)</i>	...	<i>(0.018)</i>	<i>(300)</i>	<i>(122)</i>	...	<i>(9)</i>	<i>(7)</i>	<i>(700)</i>	<i>(25)</i>	<i>(240)</i>
SRM 2690 (continued)	...	<i>(26)</i>	<i>(5800)</i>	<i>(19)</i>	<i>(67)</i>	...	<i>(0.0005)</i>	<i>(300)</i>	<i>(46)</i>	...	<i>(6)</i>	<i>(0.8)</i>	<i>(2000)</i>	<i>(25)</i>	<i>(120)</i>
SRM 2691 (continued)	...	<i>(30)</i>	<i>(5900)</i>	<i>(26)</i>	<i>(68)</i>	...	0.0578	<i>(200)</i>	<i>(53)</i>	...	<i>(3)</i>	<i>(17)</i>	<i>(2700)</i>	<i>(26)</i>	<i>(120)</i>

Please note that other categories of NIST SRMs (Standard Reference Materials) are available from BAS if required.

SOUTH AFRICAN BUREAU OF STANDARDS (SABS), South Africa

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in small italic type only approximate.

Igneous Rock Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	SiO ₂	Al ₂ O ₃	Total Fe as Fe ₂ O ₃	Fe ₂ O ₃	FeO	MgO	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P ₂ O ₅	BaO	H ₂ O ⁺	CO ₂
SARM 6	NIM-D Dunite	38.96	<i>0.3</i>	17.00	0.71	14.63	43.51	0.28	<i>0.04</i>	<i>0.01</i>	0.22	...	0.26	0.42	0.30	0.40

Values are also given for the following minor and trace elements:- Ba, Ce, Co, Cr, Cu, Dy, Eu, F, Ga, Gd, La, Li, Lu, Mn, Nb, Ni, P, Pb, Rb, S, Sm, Sr, Tb, Th, Ti, Tm, U, V, Y, Yb, Zn, and Zr.

Chromium Ore Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	CaO	Cr ₂ O ₃	FeO	Fe ₂ O ₃	MgO	MnO	SiO ₂	TiO ₂	V ₂ O ₅
SARM 131	Chromium Ore	14.60	<i>0.24</i>	41.83	...	30.7	9.15	0.243	3.13	0.944	0.414
SARM 146	Chromium Ore	14.54	0.10	46.91	25.58	...	10.62	0.22	0.616	0.57	0.32

Magnetite Iron Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	Al	K	Si	As	Ca	Cd	Co	Cr	Cu	Mg	Mn	Na	Ni	P	Pb	S	Ti	Zn	V
SARM 12	Magnetite Iron Ore	66.63	0.41	0.0108	0.16	<i>0.0002</i>	0.78	<i>0.0005</i>	0.0223	0.0021	0.0502	1.69	0.17	0.0091	0.0281	0.0477	0.0025	0.0695	0.43	0.0142	0.0520

Magnetite Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	SiO ₂	Al ₂ O ₃	CaO	CuO	K ₂ O	MgO	MnO	NiO	P ₂ O ₅	TiO ₂	V ₂ O ₅	S	C	LOI
SARM 147	Magnetite Ore	52.67	3.35	0.96	7.05	<i>0.13</i>	<i>0.21</i>	5.28	0.23	<i>0.04</i>	1.17	1.72	0.104	0.13	1.36	3.37

Hematite Iron Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	SiO ₂	Al ₂ O ₃	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P
SARM 132	Hematite Iron Ore	62.2	7.82	1.84	<i>0.09</i>	<i>0.03</i>	0.22	<i>0.020</i>	<i>0.09</i>	0.054

Hematite Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Fe	SiO ₂	Al ₂ O ₃	BaO	CaO	K ₂ O	MgO	MnO	Na ₂ O	P ₂ O ₅	S	TiO ₂	LOI
SARM 145	Hematite Ore	66.42	3.56	0.58	<i>0.046</i>	0.15	0.09	0.02	0.02	0.02	0.12	<i>0.014</i>	0.03	0.36

Zirconium Concentrate Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	ZrO ₂	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	P ₂ O ₅	HfO ₂	CaO	MgO	Cr
SARM 13	Zirconium Concentrate	64.01	32.45	0.61	0.187	0.295	0.23	1.29	<i>0.14</i>	<i>0.044</i>	<i>0.0023</i>

Rutile Ore Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	CaO	Cr ₂ O ₃	Fe	K ₂ O	MgO	MnO	Nb ₂ O ₅	P ₂ O ₅	SiO ₂	Th	TiO ₂	U	V ₂ O ₅	ZrO ₂	LOI
SARM 166	Rutile Ore	0.45	0.11	0.122	0.60	<i>0.061</i>	0.022	0.016	0.31	0.024	1.90	0.00432	93.9	<i>0.00442</i>	0.46	1.08	<i>0.35</i>

SOUTH AFRICAN BUREAU OF STANDARDS (SABS), South Africa

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified and figures in small italic type only approximate.

Fluorspar Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	CaF ₂	CaCO ₃	MgCO ₃	P ₂ O ₅	Mn	SiO ₂	Fe ₂ O ₃
SARM 14	Acid Grade, Buffalo	97.32	<i>0.3</i>	<i>0.03</i>	<i>0.18</i>	...	<i>0.57</i>	<i>0.06</i>
SARM 15	Acid Grade, Zeerust	97.84	0.95	0.55	0.017	0.0213	<i>0.26</i>	<i>0.23</i>

Manganese Ore Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Mn	Fe	SiO ₂	CaO	MgO	Al ₂ O ₃	P	Na ₂ O	K ₂ O	BaO	S	CO ₂	Zn
SARM 16	Manganese Ore (Wessels)	49.17	11.48	5.04	4.70	0.76	<i>0.3</i>	0.033	<i>0.03</i>	0.02	0.60	0.17	<i>1.3</i>	0.0364
SARM 17	Manganese Ore (Mamatwan)	38.81	4.27	4.69	<i>14.4</i>	3.03	0.24	0.018	0.09	0.09	<i>0.08</i>	<i>0.01</i>	15.40	0.0043
SARM 149	Manganese Ore (Kalahari)	38.0	5.39	5.89	14.2	2.08	0.221	0.021	0.147	0.132	0.050

The mineral content of SARM 149 is Braunite: 57.4%, Calcite: 24.6% and Ankerite: 18.0% (Quartz, Hematite and Iron Sulphate were also observed).

Coal Certified Reference Materials (Finely divided material – units of 120g)

SABS No.	Description	SiO ₂	Al ₂ O ₃	Fe ₂ O ₃	TiO ₂	CaO	MgO	Na ₂ O	K ₂ O	P ₂ O ₅	S	LOI
SARM 18	Witbank Coal	6.20	2.57	0.29	0.114	0.18	0.11	...	0.145	...	0.56	90.11
SARM 19	OFS Coal	15.00	8.01	1.75	0.341	1.39	0.20	0.29	0.24	...	1.49	71.28

Values are also given for the following minor and trace elements:- As, Ba, Be, Ce, Co, Cr, Cs, Cu, Ga, Ge, Hf, Hg, La, Mn, Ni, P, Pb, Rb, Sc, Se, Sm, Sr, Ta, Th, U, V, Y, Zn and Zr.

Phosphate Rock Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	P ₂ O ₅	CaO	F	CO ₂	MgO	SrO	Fe ₂ O ₃
SARM 32	Phosphate rock	39.96	54.44	2.49	1.61	0.50	0.52	0.14

Andalusite Certified Reference Material (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	SiO ₂	Fe (as Fe ₂ O ₃)	TiO ₂	K ₂ O	Na ₂ O	MgO	CaO	LOI
SARM 34	Andalusite	59.15	39.04	0.75	0.168	0.238	0.093	0.131	<i>0.13</i>	0.622

Vanadium Pentoxide Certified Material (Finely divided material – units of 100g)

SABS No.	Description	Al ₂ O ₃	CaO	Fe ₂ O ₃	K ₂ O	MgO	Na ₂ O	P ₂ O ₅	SiO ₂	As	S	V (Total)
SARM 38	Vanadium Pentoxide	0.14	<i>0.019</i>	0.119	0.060	0.0037	0.22	<i>0.008</i>	0.11	<i>0.001</i>	<i>0.0045</i>	55.84

SOUTH AFRICAN BUREAU OF STANDARDS (SABS), South Africa

CHEMICAL COMPOSITION (nominal mass content) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets are for information only.

Rock, Mineral and Sediment Certified Reference Materials (Finely divided material – units of 100g)

SABS No.	Description	Mass content	SiO ₂	Al ₂ O ₃	Fe as Fe ₂ O ₃	FeO	MgO	ZrO ₂	CaO	Na ₂ O	K ₂ O	MnO	TiO ₂	P ₂ O ₅	Cr ₂ O ₃	HfO ₂	U ₃ O ₈	ThO ₂	S
SARM 41	Carbonaceous Shale	%	56.67	13.50	4.23	<i>0.3</i>	8.10	...	1.50	0.93	1.39	0.06	0.55	0.05	<i>0.15</i>
SARM 43	Magnesite	%	5.99	<i>0.06</i>	0.26	<i>0.1</i>	44.11	...	0.75	<i>0.05</i>	<i>0.04</i>	<i>0.01</i>	<i>0.01</i>	<i>0.02</i>	<i>0.04</i>
SARM 44	Sillimanite Schist	%	38.84	58.80	2.60	<i>1.0</i>	<i>0.1</i>	...	0.14	<i>0.05</i>	0.18	0.03	1.83	0.10	<i>0.03</i>
SARM 47	Serpentinite	%	36.30	1.09	4.14	<i>0.4</i>	42.09	...	<i>0.10</i>	<i>0.05</i>	<i>0.02</i>	0.06	<i>0.01</i>	<i>0.02</i>	0.29	<i>0.02</i>
SARM 48	Fluorspar Granite	%	67.11	11.24	0.58	<i>0.2</i>	0.18	...	8.90	3.22	4.26	0.02	0.10	<i>0.09</i>
SARM 50	Dolerite	%	51.56	15.28	11.00	8.49	7.57	...	10.80	2.30	0.61	0.17	0.86	0.15	<i>0.03</i>
SARM 52	Stream Sediment	%	57.81	9.38	19.71	<i>4.0</i>	0.60	...	0.37	<i>0.1</i>	0.25	0.27	1.30	0.09	0.19	<i>0.02</i>
SARM 62	Zircon (RBM)	%	32.8	0.88	0.07	...	0.04	64.2	0.11	0.13	0.12	...	1.31	0.0354	0.0158	...

Rock, Mineral and Sediment Certified Reference Materials (continued)

SABS No.	Mass content	Ba	Ce	Co	Cr	Cu	Ga	Mo	Nb	Ni	Pb	Rb	Sr	Th	V	Y	Zn	Zr
SARM 41 (cont.)	µg/g	820	<i>60</i>	<i>15</i>	123	53	<i>20</i>	<i>5</i>	8	122	<i>30</i>	59	54	<i>12</i>	139	17	76	146
SARM 43 (cont.)	µg/g	<i>25</i>	<i>20</i>	4	<i>195</i>	<i>15</i>	252	8	<i>10</i>	...
SARM 44 (cont.)	µg/g	<i>50</i>	<i>220</i>	<i>8</i>	384	<i>10</i>	<i>55</i>	<i>15</i>	96	<i>15</i>	<i>30</i>	13	5	50	395	84	271	405
SARM 47 (cont.)	µg/g	<i>75</i>	<i>20</i>	79	...	<i>5</i>	<i>5</i>	2221	<i>60</i>	...	<i>3</i>	...	<i>16</i>	<i>5</i>	45	...
SARM 48 (cont.)	µg/g	<i>290</i>	<i>850</i>	...	23	<i>10</i>	...	<i>5</i>	202	...	135	291	<i>5</i>	113	<i>8</i>	436	53	300
SARM 50 (cont.)	µg/g	220	<i>30</i>	40	357	84	<i>10</i>	<i>85</i>	<i>25</i>	14	195	<i>6</i>	216	23	81	86
SARM 52 (cont.)	µg/g	<i>410</i>	<i>210</i>	81	...	219	<i>15</i>	...	11	182	1200	20	25	<i>11</i>	346	20	264	250

PGM and Gold Ore Certified Reference Materials (Finely divided material – units of 3kg, except SARM 186 – units of 1kg) nominal mass content in µg/g

SABS No.	Description	Au	Pt	Pd	Rh	Ru	Ir	Fe	Si	Co	Cr	Cu	Ni	S	Al	Ca	Mg	Os	3E PGMs +Au
SARM 75	Sheba Sulphide Zone	0.053	0.32	0.61	2300
SARM 107	PGM Ore	0.046	1.99	0.926	0.320	0.626	<i>0.14</i>
SARM 186	PGM Concentrate	2.58	67.1	28.1	7.63	11.4	3.01	109000	210000	1800	5900	12500	22900	<i>45900</i>	<i>14800</i>	<i>12900</i>	<i>135000</i>	<i>1.48</i>	<i>108</i>

Ferro-Alloy Certified Reference Materials (Finely divided material – units of 100g) nominal mass content in %

SABS No.	Description	C	Si	Mn	P	S	Cr	Ni	Al	Co	Mg	Ti	V	Fe
SARM 33	Ferro-silicon	1.01	15.60	0.75	0.043	...	0.43	0.28	80.2
SARM 144	Ferro-chromium	6.64	5.30	0.32	<i>0.02</i>	<i>0.04</i>	49.02	0.20	<i>0.06</i>	<i>0.06</i>	<i>(0.04)</i>	0.67	0.36	36.87

Ferro-Chrome Slag Certified Reference Material (Finely divided material – units of 100g) nominal mass content in %

SABS No.	Description	Cr ₂ O ₃	SiO ₂	Al ₂ O ₃	Fe _{Total}	CaO	MgO	S
SARM 77	Ferro-Chrome Slag	12.5	26.8	27.5	5.31	3.64	22.99	<i>0.32</i>

SPL-LABMAT (SPL), Czech Republic

CHEMICAL COMPOSITION (nominal mass content in %) - Figures in bold type certified and figures in small italic type only approximate.

Cast Iron Certified Reference Materials (Approx. 40mm dia. x 18mm depth discs)

SPL No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co
CZ20233-3C	3.68	2.15	0.333	0.026	0.007	0.100	0.490	0.040	0.024	0.0044	0.026
CZ20233-4E	4.45	0.090	0.034	0.023	0.006	0.030	0.002	0.049	0.003	...	0.033
CZ20233-5C	2.30	1.40	0.704	0.027	0.091	0.085	0.104	0.188	0.103	0.0078	0.013
CZ20233-6C	3.11	3.25	1.25	0.097	0.019	1.33	0.006	0.021	0.024	0.0024	0.005
CZ20233-7C	3.55	1.73	0.389	0.028	0.026	0.542	0.966	1.26	0.040	0.0008	0.048

SPL No.	Cu	Pb	Sn	Ti	V	W	Bi	Ce	Mg	Sb	Zn
CZ20233-3C (cont.)	0.421	0.005	0.009	0.021	0.016	0.003	0.002	0.013	0.006
CZ20233-4E (cont.)	0.005	0.002	0.001	0.011	0.015	...	0.002
CZ20233-5C (cont.)	0.013	...	0.002	0.008	0.054	...	0.007	0.002	...
CZ20233-6C (cont.)	0.273	0.003	0.131	0.107	0.192	0.007	0.044	...
CZ20233-7C (cont.)	0.016	...	0.004	0.026	0.067	0.037	0.002

Cast Iron Certified Reference Materials (Approx. 40mm dia. x 18mm depth discs)

SPL No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	B	Co	Zr
CZ20034-11B	2.44	3.67	0.382	0.271	0.140	1.178	1.144	0.082	0.067	0.0032	0.007	0.007
CZ20034-12B	2.92	2.96	1.047	0.484	0.077	0.638	0.117	0.174	0.077	0.047	0.002	0.002
CZ20034-13C	3.15	2.23	0.704	0.0261	0.0044	0.124	0.360	1.299	0.022	...	0.02	0.02
CZ20034-14C	3.14	2.49	0.275	0.0162	0.0081	0.045	0.646	0.030	0.007	0.0123	0.013	0.013
CZ20034-15C	3.47	1.68	0.060	0.054	0.0028	0.078	0.002	0.728	0.010	0.0057
CZ20034-16C	3.87	0.95	1.311	0.173	0.0243	0.332	0.195	0.375	0.004	0.020	0.002	0.002
CZ20034-17C	4.08	0.150	0.503	0.104	0.0033	0.178	0.030	2.32	0.002	0.0006

SPL No.	Cu	Pb	Sn	Ti	V	W	Bi	Ce	Mg	Sb	As	Zn
CZ20034-11B (cont.)	0.130	0.007	0.074	0.041	0.182	0.005	0.007	0.011	0.005	...
CZ20034-12B (cont.)	0.223	0.009	0.042	0.071	0.326	0.002	0.006	0.046	0.024	0.004
CZ20034-13C (cont.)	0.089	...	0.014	0.015	0.043	0.003	...	0.011	0.064	0.002	0.002	...
CZ20034-14C (cont.)	0.585	...	0.025	0.018	0.013	0.003	...	0.019	0.017	0.020	0.035	0.010
CZ20034-15C (cont.)	1.123	...	0.006	0.036	0.019	0.004	0.008	0.030	0.040	0.056	0.003	...
CZ20034-16C (cont.)	0.345	0.015	0.125	0.057	0.027	0.015	0.010	0.003	0.017
CZ20034-17C (cont.)	0.037	0.002	0.002	0.015	0.076	0.004	0.002	0.003	0.007	...	0.005	...

Some other SPL samples are available, and information on these will be provided on request.

SUS (SUS), Germany

CHEMICAL COMPOSITION (nominal mass content in %) – figures in small italic type only approximate and and figures in brackets are for information only.

Aluminium and Aluminium Alloy Setting-up Samples (Approx. 55mm dia. x 50mm discs)

SUS No.	Al	Si	Fe	Cu	Mn	Mg	Cr	Ni	Zn	Ti	Ag	B	Be	Bi	Ca	Cd	Co	Ga	Li	P	Pb	Sn	Sr	V	Zr	Na	Sb	In
SUS-RA10	<i>99.99</i>	<i>0.0010</i>	<i>0.0005</i>	<i>0.0002</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0002</i>	<i><0.0003</i>	<i><0.0001</i>	<i><0.0001</i>	<i><0.0002</i>	<i><0.0001</i>	<i><0.0003</i>	<i><0.00001</i>	...	<i><0.0001</i>	<i><0.0001</i>	<i><0.00002</i>	...	<i><0.0003</i>	<i><0.0003</i>	<i><0.00003</i>	<i><0.0002</i>	<i><0.0001</i>	<i><0.00001</i>	<i><0.0003</i>	...
SUS-RA18	<i>75</i>	<i>15</i>	<i>0.2</i>	<i>7.5</i>	<i>0.3</i>	<i>0.2</i>	<i>0.0003</i>	<i>3</i>	<i>0.3</i>	<i>0.001</i>	<i>0.01</i>	<i>0.0035</i>	<i><0.0001</i>	<i>0.001</i>	<i>0.004</i>	<i>0.0005</i>	<i><0.001</i>	<i>0.008</i>	<i><0.001</i>	<i>0.015</i>	<i>0.37</i>	<i>0.37</i>	<i>0.05</i>	<i>0.001</i>	<i>0.005</i>	<i>0.005</i>	<i>0.45</i>	...
SUS-RA19	<i>78</i>	<i>1.7</i>	<i>1.3</i>	<i>0.8</i>	<i>1.3</i>	<i>8</i>	<i>0.2</i>	<i>0.6</i>	<i>7</i>	<i>0.2</i>	<i>0.3</i>	<i>0.001</i>	<i>0.005</i>	<i>0.2</i>	<i>0.008</i>	<i>0.04</i>	<i>0.3</i>	<i>0.06</i>	<i>0.009</i>	<i>0.0009</i>	<i>0.01</i>	<i>0.02</i>	<i>0.009</i>	<i>0.1</i>	<i>0.2</i>	<i>0.001</i>	<i>0.007</i>	<i>0.01</i>

Cobalt and Cobalt Alloy Setting-up Samples (Approx. 40mm dia. x 20mm discs)

SUS No.	Co	C	Si	Mn	P	S	Cr	Cu	Ni	Mo	Nb	Ti	V	W	Zr	Fe	Ta	Al
SUS-RC011	<i>99.9</i>	...	<i>0.01</i>	<i><0.005</i>	<i><0.003</i>	<i>0.0005</i>	<i><0.005</i>	<i><0.01</i>	<i>0.003</i>	<i><0.0005</i>	<i><0.0005</i>	<i><0.3</i>	<i>0.001</i>	<i>0.01</i>	<i><0.003</i>	<i><0.02</i>
SUS-RC014	<i>52</i>	<i>0.2</i>	<i>1</i>	<i>0.5</i>	<i>(0.005)</i>	<i>(0.005)</i>	<i>30</i>	...	<i>10</i>	<i>7</i>	...	<i>(0.7)</i>
SUS-RC015	...	<i>1</i>	<i>0.2</i>	...	<i>0.02</i>	<i>0.02</i>	...	<i>1</i>	...	<i>6</i>	<i>2</i>	<i>0.1</i>	<i>0.1</i>	<i>24</i>	<i>0.5</i>	<i>0.1</i>
SUS-RC016	...	<i>0.2</i>	<i>0.4</i>	<i>3</i>	...	<i>3</i>	<i>2</i>	<i>0.1</i>	<i>1</i>	<i>25</i>	<i>0.2</i>	<i>0.1</i>

Copper and Copper Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Cu	Zn	Pb	Sn	Mn	Fe	Ni	Si	Sb	Al	C	S
SUS-RC11	<i>99.99</i>	<i>0.0002</i>	<i>0.0002</i>	<i>0.0004</i>	<i>0.0001</i>	<i>0.0005</i>	<i>0.0005</i>	<i>0.0001</i>	<i>0.0001</i>	<i>0.0001</i>	...	<i>0.0010</i>
SUS-RC32	<i>60</i>	<i>35</i>	<i>(0.6)</i>	<i>(0.2)</i>	<i>(0.5)</i>	<i>(0.3)</i>	<i>(1.5)</i>	<i>0.5</i>	...	<i>1.5</i>
SUS-RC33	<i>80</i>	<i>(0.02)</i>	<i>(0.01)</i>	...	<i>(0.4)</i>	<i>4.5</i>	<i>4</i>	<i>10</i>
SUS-RC36	<i>80</i>	<i>(0.4)</i>	<i>12</i>	<i>7</i>	...	<i>(0.01)</i>	<i>(1.7)</i>	...	<i>(0.3)</i>
SUS-RC38	<i>65</i>	<i>(0.02)</i>	<i>(0.01)</i>	...	<i>0.75</i>	<i>0.5</i>	<i>30</i>	<i>(0.05)</i>	<i>(0.015)</i>
SUS-RC40	<i>82</i>	<i>(0.01)</i>	<i>(0.02)</i>	...	<i>5</i>	<i>1.5</i>	<i>2</i>	<i>9</i>

Iron and Steel Setting-up Samples (Disc samples – approx. dimensions as below)

SUS No.	Disc Dimensions	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	Nb	Pb	Sn	Ti	V	W
SUS-RE12	40mm dia. x 40mm	<i><0.005</i>	<i>0.003</i>	<i><0.01</i>	<i><0.005</i>	<i><0.002</i>	<i><0.01</i>	<i><0.005</i>	<i><0.01</i>	<i><0.005</i>	<i><0.001</i>	<i><0.0001</i>	<i>0.002</i>	<i><0.01</i>	<i>0.002</i>	<i><0.002</i>	<i>0.001</i>	<i>0.0003</i>	<i><0.001</i>	<i><0.01</i>
SUS-RG13	40mm dia. x 20mm	<i>3</i>	<i>2</i>	<i>1</i>	<i>0.3</i>	<i>0.05</i>	<i>1</i>	<i>0.3</i>	<i>0.6</i>	<i>0.02</i>	<i>0.05</i>	<i>0.2</i>	<i>0.04</i>	<i>0.3</i>	...
SUS-RG14	"	<i>3</i>	<i>2</i>	<i>0.2</i>	<i>0.02</i>	<i>0.005</i>	<i>1</i>	<i>0.02</i>	<i>0.05</i>	<i>0.2</i>	...	<i>0.1</i>	...
SUS-RH12	40mm dia. x 40mm	<i>0.5</i>	<i>0.6</i>	<i>17</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>4</i>
SUS-RH18	"	<i>1.3</i>	<i>(0.04)</i>	<i>(0.3)</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>4</i>	<i>3.5</i>	<i>10</i>	<i>3</i>	<i>10</i>
SUS-RH31	"	<i>0.03</i>	<i>0.3</i>	<i>1.2</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>17</i>	<i>2</i>	<i>20</i>	<i>2</i>	<i>0.3</i>	<i>2</i>
SUS-RN13	40mm dia. x 40mm	<i>1</i>	<i>(0.05)</i>	<i>1.8</i>	<i>(0.005)</i>	<i>(0.005)</i>	<i>(0.05)</i>	<i>(0.01)</i>	<i>3</i>	<i>0.4</i>	<i>(0.002)</i>	<i>(0.0005)</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>(0.005)</i>	<i>(0.001)</i>	<i>0.05</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>(0.01)</i>
SUS-RN14	"	<i>(0.05)</i>	<i>1.8</i>	<i>(0.07)</i>	<i>0.08</i>	<i>0.08</i>	<i>3</i>	<i>0.5</i>	<i>(0.01)</i>	<i>(0.01)</i>	<i>0.05</i>	<i>0.006</i>	<i>0.4</i>	<i>0.4</i>	<i>0.5</i>	<i>0.03</i>	<i>(0.0005)</i>	<i>0.1</i>	<i>0.5</i>	<i>0.4</i>
SUS-RN19	"	<i>1</i>	<i>1</i>	<i>1.5</i>	<i>0.08</i>	<i>0.07</i>	<i>3</i>	<i>1</i>	<i>1</i>	<i>0.5</i>	<i>0.05</i>	<i>0.006</i>	<i>0.8</i>	<i>0.5</i>	<i>0.5</i>	<i>(0.03)</i>	<i>0.1</i>	<i>0.1</i>	<i>0.5</i>	<i>0.5</i>
SUS-CFE3	40mm dia. x 30mm	<i>0.04</i>	<i>0.4</i>	<i>1.7</i>	<i>0.3</i>	<i>0.002</i>	<i>16.7</i>	<i>2.0</i>	<i>11</i>	<i>0.007</i>	...	<i>0.005</i>	<i>0.21</i>	<i>0.09</i>	<i>0.77</i>	<i>0.005</i>	<i>0.07</i>	<i>0.03</i>
SUS-CFE4	"	<i>1.7</i>	<i>0.4</i>	<i>0.4</i>	<i>0.01</i>	<i>0.01</i>	<i>11</i>	<i>0.8</i>	<i>0.3</i>	<i>0.008</i>	<i>0.008</i>	<i>0.002</i>	<i>0.03</i>	<i>0.06</i>	<i>0.04</i>	<i>0.005</i>	<i>0.005</i>	<i>0.003</i>	<i>1</i>	<i>0.03</i>
SUS-CFE5	40mm dia. x 20mm	<i>4</i>	<i>0.3</i>	<i>0.3</i>	<i>0.1</i>	<i>0.03</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	<i>0.1</i>	<i>0.04</i>	...	<i>0.1</i>	...

The above figures are target levels and may vary between batches. Bracketed figures may vary more significantly.

SUS (SUS), Germany

CHEMICAL COMPOSITION (nominal mass content in %) - figures in small italic type only approximate and figures in brackets for information only.

Lead and Lead Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Pb	Zn	Sn	Cd	As	Cu	Bi	Fe	Ti	Ni	Ag	Sb	Te	Se	S	Al	In	Ca	Cr	Co	Ge	Ba	Mn	Pt	Na	Au	Mg	Pd
SUS-RPB11	99.99	0.0005	0.0005	0.0005	0.0005	0.0002	0.0030	0.0002	0.0003	0.0002	0.0006	0.0003
SUS-RPB14	88	<0.003	0.015	0.002	1.2	0.06	0.005	...	0.01	0.001	0.005	10	0.01	0.01	0.01
SUS-RPB15	64	0.1	30	0.01	0.02	1.5	0.1	0.005	0.01	0.003	3	2	0.01	0.01
SUS-RPB16	97	0.001	0.18	0.003	0.02	...	0.3	0.01	0.02	0.01	...	0.0015	...
SUS-RPB17	83	0.001	3.6	...	0.3	1.5	0.1	0.007	0.002	0.001	0.3	9.9	0.003	0.01	0.0009	0.001	0.001	...	0.0002	0.001	...	0.001	...	0.0003
SUS-RPB18	90	...	0.03	0.03	7.6	0.06	0.3	...	0.02	...	0.09	1.2	0.03	0.02	0.01

Magnesium and Magnesium Alloy Setting-up Samples (Approx. 50mm dia. x 50mm discs)

SUS No.	Mg	Si	Fe	Cu	Mn	Ni	Al	Zn	Pb	Sn	Zr	Cd	Na	Ce	La	Y	Nd	Pr
SUS-RMG11	99.9	<0.01	<0.03	<0.002	0.01	<0.001	0.01	0.01	0.001	0.001	0.001
SUS-RMG13	93	0.01	0.001	0.006	0.2	0.001	5.7	0.8	0.001	0.001	0.004	0.0001	0.001	

Nickel and Nickel Alloy Setting-up Samples (Approx. 40mm dia. x 40mm discs)

SUS No.	Ni	C	Si	Mn	P	S	Cr	Fe	Mo	V	Cu	Nb	Co	W	B	Ti	Al	Pb	Zn	Ag
SUS-RNI10	99.99	<0.0008	<0.0010	<0.0002	...	<0.0005	<0.0001	...	<0.0003	<0.0004	0.00008	0.0002	0.00003
SUS-RNI11	99.6	(0.03)	(0.1)	(0.25)	...	(0.25)	...	(0.25)	(0.03)	(0.03)
SUS-RNI12	65	(0.1)	(0.1)	(0.6)	...	(0.6)	...	(0.6)	30	0.5	2.5
SUS-RNI13	57	(0.02)	(0.05)	(0.5)	(0.01)	(0.5)	16	(0.5)	16	(0.2)	(0.1)	...	(1.5)	3.5
SUS-RNI14	50	0.05	(0.2)	(0.2)	...	(0.2)	20	(0.2)	6	...	(0.03)	...	20	...	(0.0005)	2	0.5
SUS-RNI15	51	0.05	(0.1)	(0.1)	(0.005)	(0.1)	18	(0.1)	3	...	(0.03)	5	(0.5)	...	0.005	1	0.6

Zinc and Zinc Alloy Setting-up Samples (Approx. 40mm dia. x 30mm discs)

SUS No.	Zn	Pb	Sn	Cd	Cu	Fe	Al	Mg	Ti	Ni	Mn	Ag	In	Sb	TI
SUS-RZN11	99.99	0.0008	<0.0001	<0.0001	0.0003	0.0005	<0.0001	<0.0001	<0.0001	0.0001	<0.0001
SUS-RZN13	99	0.6	0.3	0.3	0.3	0.02	0.3	<0.001	<0.001	0.05	<0.001	0.05	0.3	0.2	0.03
SUS-RZN14	85.7	0.03	0.02	0.02	4	0.05	10	0.08	0.1	0.004	0.015	0.007	<0.01	<0.01	...

The above figures are target levels and may vary between batches. Bracketed figures may vary more significantly.

VASIPARI KUTATO ES FEJLESZTO VALLALAT (VASKUT), Hungary

CHEMICAL COMPOSITION (nominal mass content in %) – Figures in bold type certified, figures in small italic type only approximate and figures in brackets for information only.

Unalloyed and Low Alloy Steel Certified Reference Materials (32-35mm dia. x 19mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	As	B	Co	Cu	Nb	Sn	Ti	V	Sb
A11/1	0.043	<i>(1.46)</i>	0.21	0.011	0.0137	0.02	1.20	0.04	0.02	0.047	0.16	0.002	0.17	0.46	<i><0.001</i>
A12	0.031	1.19	0.31	0.014	0.082	1.25	0.47	2.43	0.18	0.007	...	0.012	0.18	<i>(0.03)</i>	...	0.05	0.042	0.013

Unalloyed and Low Alloy Steel Certified Reference Materials (All 32-35mm dia. x 19mm discs, except K3-K9 which are 32-35mm dia. x 38mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Co	Cu	Nb	Ti	V	W	Zr
B2/1	0.067	0.34	1.34	0.047	0.046	...	1.09	1.49	0.082	...	0.24	...	0.22	0.91
B3	0.20	0.53	0.14	<i>(0.012)</i>	0.025	5.94	0.25	1.16	1.19	...
B4	0.55	1.72	1.07	0.047	0.043	0.49	0.09
B15	0.98	0.80	0.69	0.030	0.031	3.70	1.20	0.15	0.13	0.21	0.14	...	0.32	0.33
K3	1.03	0.32	0.46	<i>(0.02)</i>	0.010	1.63	...	0.18	0.09
K4	0.52	0.46	0.84	<i>(0.02)</i>	0.025	1.24	...	<i>(0.1)</i>	0.28	0.20
K6	0.51	0.30	0.79	<i>(0.02)</i>	0.026	0.96	0.37	1.72	0.26
K9	0.096	0.59	1.53	<i>(0.01)</i>	0.018	0.64	0.56	0.97	<i>(0.01)</i>	...	0.73	<i>(0.04)</i>	0.11	0.27

Austenitic Stainless Steel Certified Reference Materials (All 32-35mm dia. x 19mm discs, except K7-K10/C which are 32-35mm dia. x 38mm discs)

VASKUT No.	C	Si	Mn	P	S	Cr	Mo	Ni	Al	Cu	Nb	Ti	Fe
K7	0.063	0.89	1.44	0.026	0.012	17.5	...	10.45	...	0.20	...	0.27	...
K8	0.061	1.38	1.10	0.026	0.017	23.5	1.53	<i>(0.18)</i>
K10/C	0.13	0.88	1.77	0.022	0.020	17.5	2.98	11.2	...	0.16	0.98
S19	0.26	2.32	0.32	0.012	0.021	7.00	0.11	12.8	...	0.19	0.81	0.048	<i>(76.1)</i>
S20	0.097	1.80	1.50	0.011	0.025	2.06	3.15	18.2	...	0.44	1.22	<i>(0.01)</i>	<i>(71.5)</i>
S22	0.014	0.61	0.34	0.009	0.008	1.00	0.82	28.2	...	<i>(0.02)</i>	...	0.13	<i>(68.8)</i>
S25	0.067	1.49	1.90	0.045	0.015	15.6	1.77	13.8	...	0.07	0.07	0.46	<i>(64.7)</i>
S26	0.076	0.67	0.99	0.027	0.026	18.9	2.59	3.31	...	0.14	0.07	0.11	<i>(73.1)</i>

PURCHASE PROCEDURE

ORDERING PROCEDURE

Please give the quantity, unit size or weight, reference number, description and producer of the samples required, and ensure we have your full delivery and invoice address.

PRICES

For prices see separate price list. Prices are stated in £ Sterling (GBP) and are subject to revision without notice. They exclude packing, despatch and VAT where applicable.

TERMS

The following terms apply:-

- (i) **United Kingdom.** Net monthly account (subject to approved bank and trade references.) Insurance and freight are charged extra, and Value Added Tax at the standard rate is charged on the net invoice value.
- (ii) **Overseas.** Packing, documentation, insurance and carriage are charged extra at cost. We shall be pleased to forward a quotation detailing these costs upon request. Prepayment is required on all orders.

PAYMENT

To enable us to meet customer requirements with the minimum of delay, new and occasional customers are asked to make payment in advance using one of the following options:-

By BACS or inter-bank transfer to Barclays Bank PLC, Middlesbrough, Sort Code 20-56-74, SWIFT No BUKBGB22

In **Sterling** to Account No 90217506, IBAN No GB16 BUKB 2056 7490 2175 06

In **Euros** to Account No 85465422, IBAN No GB19 BUKB 2056 7485 4654 22

We accept Barclays charges in the UK but not your own bank's charges.

By credit/debit card.

Customers who indicate that they wish to purchase by this method will receive a secure link for Worldpay by email. The link will only be sent at our request and is not available from our web site. For additional security we do not require you to send us any card details to our address.

Please send all orders, enquiries and correspondence to:

**BUREAU OF ANALYSED SAMPLES LTD.,
NEWHAM HALL, NEWBY,
MIDDLESBROUGH, ENGLAND TS8 9EA**

Telephone: National: Middlesbrough (01642) 300500

International: + 44 1642 300500

Website: www.basrid.co.uk

Email: enquiries@basrid.co.uk

BAS

MIDDLESBROUGH

UK